九州大学学術情報リポジトリ Kyushu University Institutional Repository

CHEMICAL AND PHYSICAL CHARACTERIZATION OF LOW-MOISTURED STARCH MELTS AT HIGH TEMPERATURE AND HIGH PRESSURE

井倉, 則之

https://doi.org/10.11501/3135195

出版情報:九州大学, 1997, 博士(農学), 論文博士 バージョン: 権利関係:

CHAPTER V

Effect of shearing force on physicochemical change of starch melts at an elevated temperature

V-1

Introduction

Many investigations have been done on starch properties heated under dry condition, and reviewed by Greenwood (1967) and Tomasik (1989). Several researches have been done on moist starch heating under wet-condition and usually heated treatment of starch under moist condition have been carried out at a temperature range from 50 to 120 °C by using an autoclave (Fukui & Nikuni, 1964; Kubota *et al.*, 1979; Bakshi & Singh, 1980). In the heated treatments of moist starches (moisture content, ca. $0.20 \sim 0.25$ g-H2O/g-solid), it is known that the physicochemical properties of the starches may be altered, such as, the raise of gelatinization temperature (Kubota *et al.*, 1979), the change of X-ray diffraction profile (Fukui & Nikuni, 1964). Such the heated treatment has not been in use for industrial starch processing itself, however the above event may be taken place for actual processing of starchy foods. In the novel development of starchy material processing by extrusion-cooking (Dolan *et al.*, 1989; Mackey & Ofoli, 1990a, b), moist starchy material is assumed to be fused at a high temperature and is processed under powerful kneading in an air-tight barrel of

the extrusion cooker. In this case, the shearing-force on starch melt must be given by the kneading. While the effect of shearing-force on starch melt has not been revealed because it is so complicated phenomenon that the kneading behaviour cannot analyze to date.

I consider that the shearing-force is simplified by use of a capillary tube viscometer, in other words the shearing-force occur when the starch melts flow through a capillary tube only. In this chapter I investigate the effect of shearing-force on various starch melts at an elevated temperature using a capillary tube viscometer.

Materials and Methods

V-2-1 Starches

Potato, sweet potato, corn and wheat starches used in this study were the same as described in Chapter II-2-1. The moisture content of these starches were adjusted to 0.20, 0.25 g-H2O/g-solid by same method as Chapter III-2-1.

V-2-2 Flow tester

A flow tester (CFT-500C, SHIMADZU Co., Kyoto, Japan) equipped with a capillary tube (1.0 mm in inside diameter, 15.0 mm in length) or a stopper plate was used to prepare heated and heated sheared starch specimens. A cross-sectional view of the flow tester cell was shown in Fig. V-1. An o-ring was attached to the bottom of the plunger for preventing steam from leakage. The flow tester can regulate the heating temperature and pressure by a plunger on starch specimen mounted in a reservoir (the cell block was composed of a reservoir and a plunger).



Fig. V-1 Cross-sectional view of a flow tester cell.

V-2-3 Measurement of flow properties and heated sheared specimen preparation

A 1.7 g of moisturized starch was moulded into a cylindrical shape (10.8 mm in diameter, ca. 15 mm in length) with a hand press. The moulded specimen was placed in the reservoir pre-heated at 150 °C and then mounted with the plunger for pressurization. Then starch was maintained at 150 °C for 15 min, at which the starches melt sufficiently from results of Chapter III. After cooling down, the starch specimen was taken out as heated specimen (ground to fine). On the other hand, the starch melt was extruded through the capillary tube by a plunger at desired constant pressures (ranging from 20 to 50 MPa) and the resultant extrudates were used as heated sheared specimens (ground to fine). The flow rate was calculated form the displacement of extrusion stroke divided by the required time, as shown in Fig. V-2.

V-2-4 Detection of pyrolysis products

Each 0.5g of intact, heated or heated sheared specimen was dissolved respectively with 50 ml of 1 N KOH at 30 °C for 24 hour. After centrifugal separation of insoluble fine, the spectrum of the centrifugate was scanned from 230 to 600 nm with a spectrophotometer (UV-160, SHIMADZU Co., Kyoto, Japan) in order to detect pyrolysis products such as furfural (absorbance at 277 nm) (Jencks, 1959; Kainuma *et al.*, 1973).



Fig. V-2 A typical chart for measurement of flow rate. Flow rate was calculated from $\Delta X/\Delta T$.

V-2-5 Determination of the degree of gelatinization

The degree of gelatinization was determined by BAP (β -amylasepulluranase) method. The degree of gelatinization was given in percent based on the ratio of digestion degree to complete gelatinization (Kainuma *et al.*, 1981).

V-2-6 Cold water solubility

Based on Kainuma *et al.*(1967), each 0.5 g of intact, heated and heated sheared specimen was suspended with 15 ml of distilled water at 30 °C for 3 hour with slow shaking. Then the suspension was centrifuged and solubilized starch in the centrifugate was determined by phenol-sulfuric acid method (Dubois *et al.*, 1956). Cold water solubility was then given in percent based on dried starch weight.

V-2-7 Glucose detection

A 0.5 g of intact, heated and heated sheared specimens were suspended with 15 ml of distilled water at 30 °C for 3 h with slow shaking. After centrifugation, D-glucose amount in the supernatant was determined by slightly modified glucose-oxidase method (Kingsley & Getchell, 1960) (Glucose-B Test Kit, WAKO PURE CHEMICAL INDUSTRIES Ltd., Osaka, Japan). To estimate a small amount of glucose, amounts of specimen solution were scaled up to 1 ml instead of specified amount of 0.1 ml of the Kit and simultaneously amount of other reagent was also scaled up to corresponding volume of the specimen solution. Glucose content was given in percent based on dried starch weight.

V-2-8 Gel filtration

Based on Chinnaswamy & Bhattacharya (1986), each 80 mg of intact, heated and heated sheared specimen was suspended with 8 ml of distilled water and gelatinized with 10 N NaOH solution, and then neutralized with 1N HCl. In this experiment the extrudates by pressure of 50 MPa (20 MPa on sweet potato starch at 0.25 g-H2O/g-solid, because it was impossible to measure the flow rate for its high fluidity) were used as the heated sheared specimens. After the starch solution was diluted to five times with distilled water and was centrifuged (15,000×G, 10 min), a 5 ml of the supernatant was charged on a Sephacryl S-500 gel column (16 mm in inside diameter, 98 cm in packing height, Pharmacia Biotech Co., Uppsala, Sweden) and eluted with distilled water at a flow rate of 20 ml/h and collected each fraction of 5 ml. Dextran T2000 and T500 (2000 and 500 kDa, Pharmacia Biotech Co., Uppsala, Sweden) and sucrose (0.342 kDa, WAKO PURE CHEMICAL INDUSTRIES Ltd., Osaka, Japan) were used as the standardmolecular-weight markers. Eluted starch in each fraction was determined by phenol-sulphuric acid method.

V-2-9 Viscometry

In order to determine viscometric molecular weight of intact, heated and heated sheared specimen, viscometry with an Ubbelohde viscometer was done at 20 °C for specimen solution (dissolved with 1 N KOH) at concentration ranging from 0.05 to 0.25 % (w/v) in accordance with Leach (1963). In this experiment the extrudates by pressure of 50 MPa (20 MPa on sweet potato starch at 0.25 g-H2O/g-solid, because it was impossible to measure the flow rate for its high fluidity) were used as the heated sheared specimens. Based on resultant intrinsic viscosity, relative molecular weight was estimated by the equation of $[\eta]=KM^{\alpha}$ ($[\eta]$, intrinsic viscosity (ml/g); *K* and α , constant; *M*, molecular weight). Two constants of *K* and α were used 1.18×10⁻³ and 0.89 respectively, based on the values of amylose by Cowie (1960).

V-3

Results and Discussion

V-3-1 Flow curves of starch melts

Figure V-3 shows the flow curves under various specified pressures

(expressed as the pressure difference) applied on the plunger. The fluidity of 4 varieties of starch melts was in order of low viscosity of sweet-potato melt to high viscosity of potato starch melt and the same order was given in the both cases of 0.20 g-H2O/g-solid and 0.25 g-H2O/g-solid. The starch specimen that flowed through the capillary tube was used as heated sheared specimens. As shown in Fig. V-3, both flow curves of corn and sweet-potato starches with 0.25 g-H2O/g-solid were changed suddenly to sharp slopes at a flow rate of ca. 1.8×10^{-6} m³/sec. This may be explained that the flow tester used reaches to the maximum flow rate (the limit of the flow tester used) at the neighborhood of the indicated flow rate, and proper phenomena considered as the dotted lines on Fig. V-3.

V-3-2 Pyrolysis products

Figure V-4 shows the results of spectral analysis scanned from 230 to 600 nm for all heated and heated sheared specimens, based on intact starches. Comparing the spectra profiles of respective intact starch (curve-a in Fig. V-4), only a negligible small peak at ca. 270 nm in B-c (sweet-potato, heated sheared specimen) was detected. However, the profiles of intact (a), heated (b) and heated sheared (c) starch were almost the same. Thus, pyrolysis products were considered not to be formed by the heated treatment at 150 °C for 15 min and the heated sheared treatment at 150 °C.









a, Intact; b, heated treatment; c, heated sheared treatment.

76

V-3-3 Determination of the degree of gelatinization

Table V-1 summarizes the degree of gelatinization of 4 varieties of starches with 0.20 and 0.25 g-H2O/g-solid. Voids in data shown in the column of Table V-1 could not be obtained with the flow tester since the pressure drop of starch melt was more than given pressure on plunger $(3 \sim 10 \text{ MPa at } 0.20 \text{ g-H2O/g-}$ solid and $3 \sim 8$ MPa at 0.25 g-H2O/g-solid) while data of sweet potato at 0.25 g-H2O/g-solid more than at 30 MPa could not be obtained because of too high fluidity. The degree of gelatinization was less than 2.1% for all intact starches. The degree of gelatinization of heated specimens gave $24.7 \sim 40.6$ % for starches with 0.20 g-H2O/g-solid and $36.1 \sim 50.2$ % for 0.25 g-H2O/g-solid. On the other hand, the degree of gelatinization of heated sheared specimens showed quite a high value, i.e. 90 % and 95 % were given for starches with 0.20 and 0.25 g-H2O/g-solid, respectively. However, the degree of gelatinization was not affected by the measure of shearing force within the limit of the present experiments. As a result, the effect of shearing force on starch melt at 150 °C produces almost complete gelatinization.

V-3-4 Cold water solubility

Table V-2 summarizes the cold water solubility of 4 varieties of starches with

0.20 and 0.25 g-H2O/g-solid. Voids in Table V-2 could not be obtained by the same reason as V-3-3 on the degree of gelatinization. Intact starches with 0.20 and 0.25 g-H2O/g-solid showed a little solubility of 1.8 to 5.6 % while those of heated starch specimens gave 4.1 to 7.5 %. For heated starch specimens, the specimens of 0.25 g-H2O/g-solid seems to give a higher cold water solubility than those of 0.20 g-H2O/g-solid. Based on heated specimens, heated sheared specimens gave considerably high solubility, i.e. around 10 times higher than that of heated specimens. Wheat starch specimens of 0.20 and 0.25 g-H2O/g-solid which done heated sheared treatment shows a lower solubility than that of other starch specimens. However, the solubility of almost every heated sheared specimens, except potato and wheat starch with 0.25 g-H2O/g-solid, was considered to be independent from the rate of shearing force which corresponded to the extrusion pressure donated in Table V-2. The solubility of potato and wheat starch with 0.25 g-H2O/g-solid increased with increase in the rate of shearing force. It was revealed that the shearing force under 150 °C markedly affected the cold water solubility as a result. The increase in cold water solubility ordinary results from gelatinization of the starch. Because the complete gelatinization of these starches, as mentioned above, are produced by the heated sheared treatment, the solubility of these specimens can markedly increase.

с ·	0.20 g-H2O/g-solid			0.25 g-H2O/g-solid				
Specimens	potato	sweet potato	corn	wheat	potato	sweet potato	corn	wheat
Intact	1.0	1.8	0.0	2.1	1.0	1.8	0.0	2.1
Heated	24.7	28.8	38.4	40.6	36.1	58.7	49.9	50.2
3 (MPa)*						91.9		
4						92.7		
6						85.2		
8						84.4		
10					92.3	87.2	89.9	93.1
20	88.2	91.8	84.1	89.8	99.9	96.7	95.2	92.1
30	81.2	73.8	87.5	89.1	96.6		93.7	96.1
40	91.0	81.6	84.3	89.7	93.4		99.7	96.1
50	89.9	78.9	86.3	92.5	96.7		87.0	92.4

Table V-1 The degree of gelatinization (%) of treated starches.

* Heated sheared specimens prepared under various extrusion pressure at 3 - 50 (MPa). The measure of shearingforce on the starch melt was assumed to be in proportion to the extrusion pressure (flow rate).

Specimens	0.20 g-H2O/g-solid					0.25 g-H2O/g-solid			
	potato	sweet potato	corn	wheat	pota	ato	sweet potato	corn	wheat
Intact	0.04	0.07	0.07	0.43	0.	04	0.07	0.07	0.43
Heated	1.8	5.6	3.5	3.7	4.	1	7.5	7.5	6.6
3 (MPa)*							51.5		
4							53.2		
6							60.1		
8							57.6		
10					49.	7	58.0	37.4	29.2
20	34.9	53.8	46.9	25.6	50.	2	61.2	37.4	31.3
30	27.8	47.6	48.5	26.7	50.	2		38.5	33.4
40	31.4	51.0	47.2	29.0	54.	1		37.5	36.5
50	38.8	51.5	50.4	32.7	64.	4		44.2	39.5

Table V-2 Cold water solubility (%) of treated starches.

* Heated sheared specimens prepared under various extrusion pressure at 3 - 50 (MPa). The measure of shearing-force on the starch melt was assumed to be in proportion to the extrusion pressure (flow rate).

V-3-5 Glucose detection

Table V-3 summarizes the results of glucose formation of 4 varieties of starches with 0.20 and 0.25 g-H2O/g-solid. Voids in Table V-3 could not be obtained by the same reason as V-3-3 on the degree of gelatinization. Only 0.001 ~ 0.005 % of glucose were detected in intact starch. In heated specimens of potato, corn and wheat starches, $0.007 \sim 0.020$ % of glucose were detected and in sweet potato starch 0.042 % of glucose was detected. In heated sheared specimens, glucose content increased to $2\sim 5$ times that of intact and heated specimens. The fact conducts that starch melt may be release a slight amount of glucose only by heated sheared treatment and starch molecules may be depolymerized into small molecule by heated sheared treatment. From the result that the pyrolysis products were not detected by heated sheared treatment, the depolymerization of the starches did not accompany the produce of pyrolysis products, like as furfurals. Furthermore from the results of the increase in the liberation rate of glucose, the increase in cold water solubility can be promoted not only the gelatinization but also the depolymerization of the starch.

V-3-6 Gel filtration

Figure V-5 and V-6 show gel-filtration profiles for 0.20 and 0.25 g-H2O/gsolid starches (intact, heated and heated sheared specimens for four kinds of starches), respectively. In the case of 0.20 g-H2O/g-solid starches, molecular weight distributions of heated specimens of potato and wheat starch were little difference from intact starches, while those of sweet potato and corn starches were slightly shifted to low molecular weight. Molecular weight distribution of heated sheared specimens, however, were obviously shifted to low molecular weight, especially that of sweet potato starch had no void volume. The fact in Fig. V-5 seems that huge-molecule of intact starches may depolymerize into small molecules by heated sheared treatment. In the case of 0.25 g-H2O/g-solid starches, similar distribution patterns with 0.20 g-H2O/g-solid were obtained. From this result, there were no great differences between 0.20 and 0.25 g-H2O/g-solid on molecular weight distribution by gel filtration.

V-3-7 Viscometry

Table V-4 summarizes the viscometry results on molecular weight of intact, heated and heated sheared specimens. Intrinsic viscosity of heated specimens of potato and wheat starches were decreased slightly, while those of sweet potato and corn starches were markedly decreased from those of intact starches. In heated specimens molecular weight was more decreased as moisture content increased. Intrinsic viscosity of heated sheared specimens of each starches were more markedly decreased as compared with heated specimens. Particularly in sweet potato and corn starches, molecular weight of heated sheared specimen were 0.86×10^5 and 1.69×10^5 at 0.20 g-H2O/g-solid and 1.16×10^5 and 0.89×10^5 at 0.25 g-H2O/g-solid, respectively based on 5.27×10^5 of intact specimen. The fact seems that starch molecule containing low moisture may be depolymerized by heated treatment at 150 °C for 15 min and given shear force may arise markedly the depolymerization of starch molecule.

Specimens	0.20 g-H2O/g-solid				0.25 g-H2O/g-solid				
	potato	sweet potato	corn	wheat	potato	sweet potato	corn	wheat	
Intact	0.000	0.001	0.001	0.005	0.000	0.001	0.001	0.005	
Heated	0.007	0.042	0.020	0.016	0.015	0.040	0.025	0.016	
3 (MPa)*						0.179			
4						0.222			
6						0.197			
8						0.197			
10					0.025	0.217	0.043	0.043	
20	0.009	0.200	0.043	0.027	0.031	0.219	0.044	0.035	
30	0.011	0.203	0.042	0.029	0.031		0.043	0.062	
40	0.014	0.212	0.046	0.028	0.042		0.054	0.041	
50	0.013	0.213	0.060	0.028	0.035		0.068	0.040	

Table V-3 Glucose content (%) of treated starches.

* Heated sheared specimens prepared under various extrusion pressure at 3 - 50 (MPa). The measure of shearing-force on the starch melt was assumed to be in proportion to the extrusion pressure (flow rate).



Fig. V-5 Gel filtration profiles of intact (○), heated (△) and heated sheared (■) starches at 0.20 g-H2O/g-solid on Sephacryl S-500 column.
A, potato; B, sweet potato; C, corn; D, wheat.

58





Table V-4 Intrinsic viscosity and viscosimetric average molecular weight of various starches.

Molecular weight $\times 10^5 * ([\eta] (ml/g))$									
Spacimona		0.20 g-H	2O/g-solid	0.25 g-H2O/g-solid					
Specimens	Intact	Heated H	leated sheared	Heated	Heated sheared				
potato	10.47 (269)	9.86 (255)	5.39 (149)	7.42 (198)	5.19 (144)				
sweet potato	5.27 (146)	2.57 (77)	0.86 (29)	1.90 (59)	1.16 (38)				
corn	5.27 (146)	3.41 (99)	1.69 (53)	1.72 (54)	0.89 (29)				
wheat	6.05 (165)	5.11 (142)	2.79 (83)	4.19 (119)	2.64 (79)				

* Calculated from Mark-Houwinck-Sakurada equation $[\eta] = KM^{\alpha}(K=1.18\times10^{-3}, \alpha=0.89)$

Summary

V-4

Potato, sweet potato, corn and wheat starch with 0.20 and 0.25 g-H2O/g-solid were treated with a flow tester under heated and heated sheared condition at 150 °C for 15 min. Comparing with heated specimens, the degrees of gelatinization were markedly increased by heated sheared treatment. Cold water solubility of low moisturized starches increased by heated sheared treatment based on heated treatment. Small amount of glucose was detected in water-soluble fractions of heated and heated sheared specimens in spite of almost no detection in intact starches, while pyrolysis products did not detected. The increase in cold water solubility by heated sheared treatment can be due to not only gelatinization but also depolymerization, molecular cleavage, of the starches. The fact of depolymerization of starch was also supported from gel filtration profiles. By viscometry, the viscometric molecular weights of intact potato, sweet potato, corn and wheat starch were more decreased by heated sheared treatment than heated treatment. The considerable depolymerization of starch ware to starch were to starch weated to starch were to starch weated t

88

CHAPTER VI

Effect of longer heating time on depolymerization of low moisturized starch melts

VI-1

Introduction

In Chapter V, the cold water solubility increased by heated and heated sheared treatments at 150 °C, and these starch melts are depolymerized, while pyrolysis products don't detected at these conditions. Comparing heated treatment with heated sheared treatment, the effects of shearing force on cold water solubility and depolymerization of starch melts are considerably greater than that of heating only. Many factors, however, can act on the properties of food polymer melts except for temperatures and pressures in extrusion cooking. Time-temperature history and strain history are each of them. Morgan *et al.* (1989) established a theoretical model for soy protein dough viscosity, with time-temperature history and strain history as parameters. Mackey & Ofoli (1990) investigated the dough rheology of importance of time-temperature history and strain history in viscosity analysis. However, there are few research about the effect of these histories on the cold water solubility and the depolymerization of starch melts.

In this chapter noticing the time-temperature history, I investigate the effect of heating time on the cold water solubility and the depolymerization of low moisturized starches melting at 150 °C. Furthermore, I attempt to compare the effect of heating time with shearing force to the starches.

Materials and Methods

VI-2-1 Starches

Potato, sweet potato, corn and wheat starches used in this study were the same as described in Chapter II-2-1. The moisture content of these starches were adjusted to 0.20 and 0.25 g-H2O/g-solid by same method as Chapter III-2-1.

VI-2-2 Heated and heated sheared treatment

A flow tester (CFT-500C, SHIMADZU Co., Kyoto, Japan) equipped with a capillary tube (1.0 mm in inside diameter, 15.0 mm in length) or a stopper plate was used to prepare heated and heated sheared starch specimens, as described in Chapter V-2-2. A 1.7 g of starch which molded to a cylindrical shape (10.8 mm in diameter, ca. 15 mm in length) was placed in the cylinder pre-heated at 150 °C and then mounted with the plunger for pressurization. Then starch was maintained at 150 °C for 15, 30, 60, 90 and 120 min with keeping the cylinder airtight. After cooling down, the starch specimen was taken out as heated specimen (ground to fine). On the other hand, the starch melt was extruded through the capillary tube at 50 MPa by a plunger and the resultant extrudates were used as heated sheared specimens (ground to fine).

VI-2-3 Cold water solubility

The cold water solubility was measured and given in percent based on dried starch weight by the same method as described in Chapter V-2-5.

VI-2-4 Gel Filtration

The procedure of the gel filtration was same as described in Chapter V-2-8. Eluted starch in each fraction was determined by phenol-sulphuric acid method, and the absorption maxima (λ max) of the iodine-polysaccharide complexes were scanned by spectrophotometer (UV-160, SHIMADZU Co., Kyoto, Japan) (Chinnaswamy & Bhattacharya, 1986).

VI-3

Results and Discussion

VI-3-1 Cold water solubility

Figure VI-1 shows cold water solubility of heated and heated sheared specimens of four varieties of starches with 0.20 and 0.25 g-H2O/g-solid. Intact, zero minute heating, starches were little soluble in cold water ($0.04 \sim 0.4 \%$). By means of heating for 15 min, these starches became some soluble in cold water ($2 \sim 20 \%$). As the heating time was long, the solubility of heated specimens was increased. The inclinations of solubilities by heated treatments





were different from origin of starches, sweet potato starch was highest (the solubility was about $55\sim 63$ % after 120 min heated) and potato starch was lowest (the solubility was about $10\sim 15$ % after 120 min heated). The less water in specimens also affected to the solubilities. The solubilities at 0.25 g-H2O/g-solid over these heating times was higher than that at 0.20 g-H2O/g-solid. Furthermore heated sheared specimens showed higher cold water solubility (35 ~ 65 %). To obtain similar degree of solubility to heated sheared specimens, more 120 min heated treatment was required. Considering that the heating time was 15 min at heated sheared treatment, the shearing force through the capillary tube might greatly influence the increases in cold water solubility.

VI-3-2 Gel filtration

Figures VI-2 and VI-3 show gel-filtration profiles of starches at 0.20 and 0.25 g-H2O/g-solid (intact and heated specimens), respectively. In intact specimens, almost carbohydrates was eluted as a void volume. Except sweet potato starch, there is no significant change between 15 min heated specimens and intact specimens. In respect to 15 min heated sweet potato starches, a peak of void volume decreased and carbohydrates of lower molecular weight was eluted after the void volume. After 60 min heating, the peak of void volume in all starches decreased and/or disappeared. Heating the starches for 120 min, the

peak of void volume of sweet potato and corn starches disappeared and the peak of void volume of potato and wheat starches decreased. It is obvious that high molecular weight of intact starch was shifted to low-molecular weight with an increase in heating time. The fact in Fig. VI-2 and VI-3 seems that hugemolecule of intact starches breakdown to small molecules by longer heating time.

Figures VI-4 and VI-5 show comparisons of molecular distributions between the specimens with longer heating time and heated sheared specimens. In Chapter V, I clarified that the starches were depolymerized by heated sheared treatment. Gel filtration profiles of heated specimens with longer heating time were similar to the profiles of heated sheared specimens. In result, to obtain similar elution patterns of the heated sheared specimens, 60 min heated treatment need except potato starch with 0.25 g-H2O/g-solid (120 min heated treatment needed). As mentioned in cold water solubility, in spite of only 15 min heating, the starch molecule of heated sheared specimens depolymerized into same degree of $60\sim$ 120 min heated specimens. From this fact, the shearing force through the capillary tube might greatly influence the increases in degree of depolymerization.

VI-3-3 λ max of iodine-polysaccharide complex

Figure VI-4 and VI-5 simultaneously show λmax profiles of iodinepolysaccharide complex of intact specimens, specimens with longer heating time and heated sheared specimens. Similar λ max patterns were observed between the specimens with longer heating time and the heated sheared specimens with similar elution patterns. In result, the specimens with similar degrees of depolymerization had similar molecular state regardless of the treatments of only heated for longer time and heated sheared. With respect to intact specimens, the λ max rose to more than 645 nm, which was generally absorbance of amylose with long chain length (Bailey & Whelan, 1961), around 20 fraction (potato starch) and 25 fraction (another starches). So that, the void volumes which appeared before $20 \sim 25$ fractions were estimated as almost amylopectin, and the fractions after the void volume (around $25 \sim 35$) were estimated as almost amylose. On heated and heated sheared specimens, the λ max reached to 645 nm around 25 fraction (potato starch) and 30 fraction (corn and wheat starches). Furthermore λ max of sweet potato starch didn't reach 645 nm in all fractions, barely reached to 600 nm around 40 fraction. It was suggested that the shifts of λ max peak were due to depolymerization of amylose and amylopectin. In other words, as amylopectin which occupied the void volume in intact starch would depolymerize into lower molecule and then elute after 25 fraction, λ max of depolymerized amylopectin might be higher absorption than one of amylose. Furthermore, as amylose also would depolymerize into lower molecule, λ max of amylose might be decreased.



Fig. VI-2 Gel filtration profiles of heated starches at 0.20 g-H2O/g-solid on Sephacryl S-500 column. A, potato; B, sweet potato; C, corn; D, wheat

 \bigcirc , intact; \bigcirc , 15 min; \triangle , 60 min; \blacktriangle , 120 min



Fig. VI-3 Gel filtration profiles of heated starches at 0.25 g-H2O/g-solid on Sephacryl S-500 column.
A, potato; B, sweet potato; C, corn; D, wheat O, intact; ●, 15 min; △, 60 min; ▲, 120 min

86



Fig. VI-4 Gel filtration profiles and λ_{max} of treated starches at 0.20 g-H₂O/g-solid on Sephacryl S-500 column. A, potato; B, sweet potato; C, corn; D, wheat O, —, intact; Δ , —, 60 min heated; \blacksquare , —, heated sheared

66




Summary

Low moisturized potato, sweet potato, corn and wheat starches were treated with a flow tester under heated and heated sheared conditions. The starches depolymerized into lower molecule by longer heating time at 150 °C. With an increase in heating time, the cold water solubility of starches increased and the degree of depolymerization progressed. Comparing heated treatment with longer heating time and heated sheared treatment, $60 \sim 120$ min heating was necessary for heated specimens to obtain similar cold water solubility and degree of depolymerization of heated sheared specimens. These results conducted that heated sheared treatment strongly promoted the depolymerization of low moist starches under high temperature as compared with heated treatment only. From the results of λ max of iodine-polysaccharide complex, there was almost same molecular state between heated for longer time and heated sheared treatment. Both amylose and amylopectin depolymerized into lower molecule by both treatments.

VI-4

CHAPTER VII

Effect of time-temperature and strain history on flow property and depolymerization of starch melts

VII -1

Introduction

As described in Chapter VI, it is necessary to consider the effect of timetemperature history and strain history on extrusion cooking. Some researches have been performed the effect of time-temperature history and strain history on the effect of dough rheology. Hayashi *et al.* (1992) measured the influence of time-temperature history and strain history on low moisturized soy protein isolate using capillary tube viscometer. They revealed the strain history was more influential on the change of dough rheology at lower moisture content (below 0.30 g-H2O/g-solid) while the time-temperature history was more influential at higher moisture content (above 0.41 g-H2O/g-solid). In Chapter V and VI, the effect of shearing force and time-temperature history on cold water solubility and depolymerization of starch melts at 150 °C were investigated. Then the cold water solubility increased and the huge starch molecules were depolymerized by shearing force and longer heating treatment at high temperature. However the effects of time-temperature history and strain history were different from the varieties of starches. Potato starch was the most less effect by longer heating treatments of four varieties of the starches. Then, in this chapter I investigate the effect of time-temperature history and strain history on pressure drops through capillary tube and on the cold water solubility and the depolymerization of potato starch melts.

Materials and Methods

VII-2-1 Starches

VII-2

Potato starch used in this study was the same as described in Chapter II-2-1. The moisture content was adjusted to 0.16, 0.20 and 0.25 g-H2O/g-solid by same method as Chapter III-2-1.

VII-2-2 Extrusion experiment

The capillary tube viscometer used for the measurements of flow properties and heated sheared treatments was the same as described in Chapter III-2-2. A reciprocating extrusion experiment was performed in order to observe the effect of strain history on the measured pressure drop and alteration of starch (approximate procedure was shown in Fig. VII-1). The viscometer can use the reciprocating extrusion experiment for its symmetrical and highly air-tight structure. A capillary tube which has 0.75 mm in radius and 20 mm in length was equipped in the viscometer. A 4.0 g of the moisturied starch was moulded into a cylindrical shape (1.08 cm in diameter and about 3.0 cm in length) using a hand press and placed into the upper specimen reservoir. The reservoir was heated to 150 °C in advance and the measurements of flow properties were performed at 150 °C, at which the starches melt sufficiently from results of Chapter III. A pressure of 15 MPa was applied to the specimen by both the upper and lower plunges (Fig. VII-1a). After the specimen was kept for 15 min in the reservoir for melt them, the lower plunger was pulled down to prepare a dead volume for the extruded specimen (Fig. VII-1b). Then the specimen was extruded through the capillary tube at 0.2 cm³s⁻¹ under a constant plunger speed of 0.2 cm s⁻¹ at the higher plunger drive pressure (100 MPa) (Fig. VII-1c). The string-like extruded specimen in the lower reservoir was pressurized again plunger at 15 MPa for 1 min in order to pack extrudate. By this procedure, the exturdate in the lower reservoir was exposed to almost the same conditions as that just before the first extrusion (Fig. VII-1d). The same procedure was repeated 37 times, taking a total time of 60 min including 15 min of initial-heating time.

Single extrusion was also carried on in order to observe the effect of timetemperature history on measured pressure drop and alteration of starch. A 4.0 g of the specimen moulded into cylindrical shape was placed into the upper reservoir. After the various initial heating times at 15 MPa pressure, the specimen extruded to the bottom reservoir at the same flow rate as in the reciprocating extrusion experiment. The initial-heating times in the reservoir were 15, 20, 30, 40, 50 and 60 min, which were equivalent to the time required for 1, 5, 13, 21, 29 and 37 extrusion strokes, respectively.

d b c a 15 MPa 100 MPa 15 MPa specimen 0000 0000 0000 0000 0000 000 0000 0000 0000 0000 0000 000 X Х Х open space for extudate 15 MPa 15 MPa

Fig. VII-1 Procedure of reciprocating extrusion.

VII-2-3 Cold water solubility

The cold water solubility was measured and given in percent based on dried starch weight by the same method as described in Chapter V-2-5.

VII-2-4 Gel filtration

The procedure of the gel filtration was same as described in Chapter V-2-8. Eluted starch in each fraction was determined by phenol-sulphuric acid method.

VII-3

Results and Discussion

VII-3-1 Measured pressure drop of starch melts

Figure VII-2 shows measured pressure drop profiles for reciprocating and single extrusion of potato starch with various moisture content. The measured pressure drop decreased by first 5 times strokes in the reciprocating extrusion at each moisture content. Then the measured pressure drops maintained constant values after 15 or 20 times strokes. It is considered that the strain history and time-temperature history would be affected these decrease in pressure drop when reciprocating extrusion was carried on. Then the single extrusion was performed in order to observe the effect of time-temperature history on the

measured pressure drop of starch melts. The measured pressure drop decreased also as increased in initial-heating times. In this case the slopes of the decrease were gentle compared with the reciprocating extrusion at each moisture content. The differences between them of 0.16 and 0.20 g-H2O/g-solid were larger than of 0.25 g-H2O/g-solid. This reason why these differences occurred was that so the water in the starch acted as a lubricant at 0.25 g-H2O/g-solid, the effect of the strain history could be small, but the effect of the time-temperature history could be large as described in Chapter VI. On the other hand at 0.16 and 0.20 g-H2O/g-solid, so the water was less to act as a lubricant that the starch granules could be more injured by reciprocating extrusion and then the effect of the strain history could be large.

VII-3-2 Cold water solubility

Figure VII-3 shows cold water solubility profiles for reciprocating and single extrusion of potato starch with various moisture content. The cold water solubility of reciprocating extrudate at 0.16 and 0.20 g-H2O/g-solid increased rapidly to about 70 % by 5 times strokes, then after 13 times strokes those maintained constant values. That at 0.25 g-H2O/g-solid increased to 55 % by 5 times strokes, however, after 13 times strokes that decreased slightly. It was same reason as described in above section why the strain history could be more effective to the starches at lower moisture content on a breakage of the starch

granules. From this result, the strain history could affected to the cold water solubility of the extrudates of the starch melts. On the specimens at 0.25 g-H2O/g-solid after 13 times strokes, the reason of the cold water solubility decreased slightly could be a retrogradation of the specimens when the incubating procedure. The cold water solubilities of single extrudate decreased from about 30 % at first 15 min as increased in initial-heating time at each moisture content. This was reason why both the decrease of the shearing force and the retrogradation of specimens as mentioned above.

VII-3-3 Gel filtration

Figure VII-4 and VII-5 show gel filtration profiles for reciprocating and single extrusion of potato starch with various moisture content, respectively. The specimens of single extrusion after 15 min was used as a control at each moisture content. The molecular weight distributions of the reciprocating extrusion shifted to lower molecular weight as the extrusion strokes increased at each moisture content (Fig. VII-4). Especially the specimens at 0.16 g-H2O/g-solid showed great decrease of the molecular weight by the reciprocating extrusion. Then the strain history could affect to the depolymerization of starch melts. The molecular weight distributions of single extrusion at 0.16 g-H2O/g-solid showed nearly same patterns in spite of initial-heating time. On the other hand, those at 0.20 and 0.25 g-H2O/g-solid shifted to lower molecular weight. Then the time-

temperature history could affect to the depolymerization of starch melts in higher moisture content. Comparing reciprocating extrusion with single extrusion at 0.25 g-H2O/g-solid, so there were few different, that the timetemperature history can be more effective on the depolymerization of starch melts than the strain history at higher moisture content in this limited condition. However at low moisture content, the strain history can be more effective on the depolymerization of starch melts.



Fig. VII-2 Measured pressure drop profiles for reciprocating (open symbol) and single (closed symbol) extrusion of potato starch with various moisture content at 150°C. \bigcirc , \bigcirc , 0.16; \triangle , \blacktriangle , 0.20; \square , \blacksquare , 0.25 g-H2O/g-solid.



Fig. VII-3 Relationship between cold water solubility and reciprocating (open symbol) or single (closed symbol) extrusion of potato starch with various moisture content at 150°C.
O, ●, 0.16; △, ▲, 0.20; □, ■, 0.25 g-H2O/g-solid.



Fig. VII-4 Gel filtration profiles of reciprocating extrusion at 150°C at various moisture content on Sephacryl S-500 column. A, 0.16; B, 0.20; C, 0.25 g-H2O/g-solid.
O, one time extrusion; ■, 5 times extrusion; △, 21 times extrusion; ●, 37 times extrusion.

113





Summary

VII-4

The effects of time-temperature and strain history on the potato starch melts at 150 °C were investigated by use of the capillary tube viscometer. The reciprocating extrusion after 15 min heating and single extrusion after various initial-heating time were performed for investigating them effects. The measured pressure drop of single extrusion decreased gently as the initialheating time increased, while the measured pressure drop of reciprocating extrusion decreased rapidly as the extrusion strokes increased. At 0.25 g-H2O/g-solid, however, there was small difference between reciprocating extrusion and single extrusion. The reason why water in the potato starch could act as a lubricant. The cold water solubility of the reciprocating extrudate at 0.16 and 0.20 g-H2O/g-solid increased to about 80% by 5 times strokes, while that at 0.25 g-H2O/g-solid increased 55 %. The molecular weight distribution of the reciprocating extrudate shifted to low-molecular weight at lower moisture content (0.16 g-H2O/g-solid). On the other hand the cold water solubility of the single extrudate decreased as initial-heating time increased. The molecular weight distribution of the single extrudate shifted to low-molecular weight at higher moisture content (0.25 g-H2O/g-solid), but the degree of depolymerization of starch melts were nearly same between the reciprocating extrusion and the single extrusion in this moisture content. From these results, the time-temperature history could be more effective on the cold water solubility

and the degree of depolymerization of starch melts at higher moisture content, while the strain history could be more effective to these at lower moisture content.

CHAPTER VIII

Conclusion

Importance of thermal processing using starchy materials tends to increase in food industry from year to year, with increase in variation of foods. However relatively many operating procedure of the thermal processing, such as extrusion cooking, can depend on experience, because physical properties of the materials processing at high temperatures and pressures are difficult to measure. Then the thermal properties of starches with low moisture content are studied in order to obtain one of basic information on food production using starchy materials. The starches used in this study are potato, sweet potato, corn and wheat starches, which are widely used in food industry, since they can easily obtain in large quantities at a low cost.

These starches with low moisture are commonly solid state under room temperature and atmospheric pressure. It is, however, believe that the low moisturized starch can fuse by heating without evaporation. This melting phenomenon, which is considered that crystallite regions of starch granules melt, greatly relates to the moisture content of the starch. Therefore, the effect of water state in starch on the thermal phase transition of starch was investigated using differential scanning calorimeter. There are only one phase transition peak, which can be considered gelatinization of starches, or two phase transition peaks, which of lower temperature can be considered gelatinization, and which of higher temperature can be considered melting of starch crystallites, were observed in each starches. As the moisture content decreased, the area of the gelatinization peak decreased, but the peak temperature kept constant. The gelatinization peak disappeared between 0.25 and 0.50 g-H2O/g-solid. The peak temperature of melting of starch crystallites increased with the decrease in the moisture content. The moisture contents at which the freezable water appeared first by DSC measurement were 0.47, 0.43, 0.39 and 0.39 g-H2O/g-solid in potato, sweet potato, corn and wheat starches, respectively. The ranges of the moisture content at which the gelatinization peak disappeared corresponded to that at which the freezable water appeared in these starches. It is concluded that gelatinization of the starches required the freezable water. Namely under low moisture content, the starches could not gelatinize but melt.

It is clarified that the moisture content of starch affected to melting of starch crystallites at high temperature. The starch melts, however, could be also affected by an applied pressure which can be often necessary to a food processing, such as in extrusion cooking. Some information about the thermo-mechanical properties include flow-starting temperature (T_s), which is measured when the specimens start to extrude through a capillary tube by raising temperature at applying some pressure with a flow tester. Then T_s of low moisturized starches were measured

using a capillary tube viscometer under varying moisture content (W) and applied pressure (P).

 T_s was increased with decreasing moisture content and applied pressure. There was no significant difference between starch varieties. T_s converged into a temperature (T_c ; 270.9 °C) at a pressure (P_c ; 0.32 MPa). Because T_s was in inverse proportion to the moisture content and logarithm of the applied pressure, T_s was expressed as,

$$Ts = Tc - (a + b W) \log (P / Pc)$$

where coefficients, *a* and *b* were 36.8 and 1.68×10^2 . The lines calculated from the equation were in a good agreement with experimental data.

Next, in order to further fundamental studies on the properties of starch melts, the flow properties of potato and corn starch melts (melting through 150 °C, 15 min) with low moisture were characterized using a capillary tube viscometer. By use of measured flow rates (Q, m³s⁻¹), and pressure drops of capillary tube (ΔPc , MPa) and orifice (ΔPo , MPa), the relationships between the flow rate and the pressure drop in the capillary tube (ΔPd , MPa) were obtained. The flow curves of both starch melts showed good linearly on logarithmic scales. These starch melts, however, gave a yield stress, especially at low moisture content. Then both flow curves satisfied an equation by Herschel-Bulkley power-law model after exchanging the flow rate and the pressure drop to apparent shear rate ($\dot{\chi}_{a}$, s⁻¹) and shear stress (τ_w , MPa), respectively. The flow properties were good representative by Herschel-Bulkley power-law model and these curves varied with the moisture content. The flow properties between potato and corn starch melts were different even though they were same moisture content, especially that was reflected in the consistency index.

In extrusion cooking, food polymers are subjected to not only heat, but also shearing-force by kneading in an extrusion barrel. It must be considered how the shearing-force also affect the food polymers to obtain optimal products. Then low moisturized starches were treated with a flow tester under heated and heated sheared condition at 150 °C for 15 min. Cold water solubility of low moisturized starches increased by heated sheared treatment based on heated treatment, while pyrolysis products did not detected. Small amount of glucose was detected in water-soluble fractions of heated and heated sheared specimens in spite of almost no detection in intact starches. Comparing with heated specimens, the degrees of gelatinization were markedly increased by heated sheared treatment. By viscometry, the viscometric molecular weights of intact potato, sweet potato, corn and wheat starch were more depolymerized by heated sheared treatment than heated treatment. These facts were also supported from gel filtration profiles. As the results from glucose formation, viscometric molecular-weight depolymerization and gel-filtration profiles, the considerable depolymerization in starch molecules is yielded by the physical shearing force on starch melt despite starch varieties.

Furthermore in extrusion cooking, so a reidence time in a extrusion barrel varies by varying of feed rate, that the effect of time-temperature history and strain history on materials also vary. Then the effects of time-temperature history and strain history on the physicochemical change of low moisturized starches are investigated.

The viscosity of starch melts tended to decrease with an increase in heating time from the results of measured pressure drops. With an increase in heating time, the cold water solubility of starches increased and the degree of depolymerization progressed. With an increase in moisture content, cold water solubility also increased and depolymerization also progressed. Comparing heated treatment with longer heating time and heated sheared treatments, $60 \sim$ 120 min heating was necessary for heated specimens to obtain similar cold water solubility and degree of depolymerization of heated sheared specimens. These results conducted that strain history could strongly promote the depolymerization of low moisturized starches under high temperature as compared with time-temperature history. Indeed the measured pressure drop of reciprocating extrusion decreased rapidly as the extrusion strokes increased, while the measured pressure drop of single extrusion decreased gently as the initial-heating time increased. On the starch with higher moisture content, however, there was small difference between reciprocating extrusion and single extrusion. Furthermore, cold water solubility greatly increased and degree of depolymerization of starch are greatly promoted with an increase in extrusion

stroke time. From these results, the time-temperature history could be more effective on the cold water solubility and the degree of depolymerization of starch melts at higher moisture content, while the strain history could be more effective to these at lower moisture content.

Recently, the utilization of starch for degradable bioplastics is interested throughout the world. Some products, such as a cushion and a container, are already produced using an extruder and come into the market (Shiraishi *et al.*, 1992). This study can be available for the development of apparatus and the process control of production of not only the food products but also the bioplastic products.

REFERENCES

- Anderson R. A., H. F. Conway, V. F. Pfeifer and E. L. Griffin (1969).
 Gelatinization of corn grits by roll- and extrusion-cooking. *Cereal Science Today*, 14(1), 4.
- Bagley E. B. (1957). End corrections in the capillary flow of polystyrene. Journal of Applied Physics, 28, 624-627.
- Bailey J. M. and W. J. Whelan (1961). Physical properties of starch. I. Relationship between iodine stain and chain length. *The Journal of Biological Chemistry*, 236, 969-973.
- Bakshi A. and R. P. Singh (1980). Kinetics of water diffusion and starch gelatinization during rice parboiling. *Journal of Food Science*, **45**, 1387-1392.
- Bhattacharya M. and M. A. Hanna (1987). Kinetics of starch gelatinization during extrusion cooking. *Journal of Food Science*, **52**(3), 764-766.
- Biliaderis C. G., T. J. Maurice and J. R. Vose (1980). Starch gelatinization phenomena studied by differential scanning calorimetry. *Journal of Food Science*, **45**, 1669-1674,1680.
- Biliaderis C. G., C. M. Page, T. J. Maurice and B. O. Juliano (1986). Thermal characterization of rice starches: A polymeric approach to phase transitions of granular starch. *Journal of Agricultural and Food Chemistry*, 34, 6-14.
 Borch J. and R. H. Marchessault (1968). Light scattering by starch granules.

Journal of Colloid and Interface Science, 27(3), 355-359.

- Bryce D. J. and C. T. Greenwood (1963a). Aspects of the thermal degradation of starch. *Stärke/Starch*, **15**(5), 166-170.
- Bryce D. J. and C. T. Greenwood (1963b). The thermal degradation of starch. Part III.) The formation of decomposition products from starch and related materials at temperature between 175 °C and 400 °C. *Stärke/Starch*, **15**(10), 359-363.
- Cervone N. W. and J. M. Harper (1978). Viscosity of an intermediate moisture dough. *Journal of Food Process Engineering*, **2**, 83-95.
- Chen A. H., Y. C. Jao, J. W. Larkin and W. E. Goldstein (1978). Rheological model of soy dough in extrusion. *Journal of Food Process Engineering*, 2, 337-342.
- Chiang B. -Y. and J. A. Johnson (1977). Gelatinization of starch in extruded products. *Cereal Chemistry*, **54**(3), 436-443.
- Chinnaswamy R. and K. R. Bhattacharya (1986). Characteristics of gelchromatographic fractions of starch in relation to rice and expanded riceproduct qualities. *Stärke/Starch*, **38**(2), 51-57.
- Chinnaswamy R. and M. A. Hanna (1990). Macromolecular and functional properties of native and extrusion-cooked corn starch. *Cereal Chemistry*, 67(5), 490-499.
- Collison R. and W. G. Chilton (1974). Starch gelation as a function of water content. *Journal of Food Technology*, **9**, 309-315.

- Conway H. F., E. B. Lancaster and G. N. Bookwalter (1968). How extrusion cooking varies product properties. *Food Engineering*, **40**(11), 102.
- Cowie J. M. G. (1961). Studies on amylose and its derivatives. Part I. Molecular size and configuration of amylose molecules in various solvents. *Makromolecule Chemistry*, **42**, 230-247.
- Dail R. V. and J. F. Steffe (1990). Rheological characterization of crosslinked waxy maize starch solutions under low acid aseptic processing conditions using tube viscometry techniques. *Journal of Food Science*, **55**(6), 1660-1665.
- Davidson V. J., D. Paton, L. L. Diosady and G. Larocque (1984a). Degradation of wheat starch in a single screw extruder: Characteristics of extruded starch polymers. *Journal of Food Science*, **49**, 453-458.
- Davidson V. J., D. Paton, L. L. Diosady and L. J. Rubin (1984b). A model for mechanical degradation of wheat starch in a single-screw extruder. *Journal* of Food Science, **49**, 1154-1157.
- Dolan K. D., J. F. Steffe and Morgan R. G. (1989). Back extrusion and simulation of viscosity development during starch gelatinization. *Journal of Food Process Engineering*. 11, 79-101.
- Dolan K. D. and J. F. Steffe (1990). Modeling rheological behavior of gelatinizing starch solutions using mixer viscometry data. *Journal of Texture Studies*, 21, 265-294.

Donovan J. W. (1979). Phase transitions of the starch-water system.

Biopolymers, 18, 263-275.

- Dubois M., K. A. Gilles, J. K. Hamilton, P. A. Rebers and F. Smith (1956).
 Colorimetric method for determination of sugars and related substances.
 Analytical Chemistry, 28, 350-356.
- Duckworth R. B. (1971). Differential thermal analysis of frozen food systems. I.
 The determination of unfreezable water. *Journal of Food Technology*, 6, 317-327.
- French D. (1984). Organization of starch granules. In "Starch: Chemistry and Technology," 2nd ed. Academic Press, Inc., Orlando, pp. 184-247.
- Fujio Y., N. Hayashi and I. Hayakawa (1991). Effect of moisture content on flow behaviour of molten soy-protein isolate under an elevated temperature. *International Journal of Food Science and Technology*, 26, 45-51.
- Fukui T. and Z. Nikuni (1964). Heat-moisture treatment of sweet potato starch. *Nihon Nogei Kagaku Kaishi*, **38**, 226-230 (in Japanese).
- Ghiasi K., R. C. Hoseney and E. Varriano-Marston (1982). Gelatinization of wheat starch. III. Comparison by differential scanning calorimetry and light microscopy. *Cereal Chemistry*, **59**(4), 258-262.
- Gloyna D., S. Schreck, F. Schierbaum and G. Westphal (1991). Zum thermishen Verhalten von Glucanen. Teil 1: Thermoanalytische Untersuchungen an Stärken und stärkehaltigen Systemen. *Stärke/Starch*, **43**(11), 431-437.
- Gomez M. H. and J. M. Aguilera (1983). Changes in the starch fraction during extrusion-cooking of corn. *Journal of Food Science*, **48**, 378-381.

- Gomez M. H. and J. M. Aguilera (1984). A physicochemical model for extrusion of corn starch. *Journal of Food Science*, **49**, 40-43, 63.
- Greenwood C. T. (1967). The thermal degradation of starch. Advances in Carbohydrate Chemistry, 22, 483-515.
- Hari P. K., S. Garg and S. K. Garg (1989). Gelatinization of starch and modified starch. *Stärke/Starch*, **41**(3), 88-91.
- Hayashi N., I. Hayakawa and Y. Fujio (1990). Development and evaluation of an extrusion viscometer for polymer melt. *Journal of the Faculty of Agriculture, Kyushu University*, **35**, 73-9.
- Hayashi N., I. Hayakawa and Y. Fujio (1991). Entrance effect correction on the flow of moisturized soy protein isolate melt in an extrusion viscometer. *International Journal of Food Science and Technology*, 26, 567-574.
- Hayashi N. (1992). Studies on melt rheology of protein at an elevated temperature. *Kyushu University, Dr. Thesis.*
- Hayashi N., K. Noma, I. Hayakawa and Y. Fujio (1992). Influence of timetemperature history and strain history on the melt rheology of soy protein isolate at an elevated temperature. *International Journal of Food Science and Technology*, 27, 297-304.
- Hayashi N., I. Hayakawa and Y. Fujio (1993). Flow behaviour of soy protein isolate melt with low and intermediate moisture levels at an elevated temperature. *Journal of Food Engineering*, 18, 1-11.

Hizukuri S. (1977). Denpun to Mizu. In "Denpun Kagaku Handbook," Asakura

Syoten, Tokyo, pp. 25-51.

- Jao Y. C., A. H. Chen, D. Lewandowski and W. E. Irwin (1978). Engineering analysis of soy dough rheology in extrusion. *Journal of Food Process Engineering*, 2, 97-112.
- Jencks W. P. (1959). Studies on the mechanism of oxime and semicarbazone formation. *Journal of the American Chemical Society*, **81**, 475-481.
- Kainuma K., T. Oda and S. Suzuki (1967). Phosphate derivatives of starch. I.
 Synthesis of phosphorus-crosslinked starch with phosphorus pentooxide.
 Denpun Kogyo Gakkaishi, 14(1), 24-28.
- Kainuma K., T. Oda and S. Suzuki (1968). Observation of changes of starch granules during gelatinization by a novel photopastegraphy method. I. Design of the photopastegraph. *Denpun Kogyo Gakkaishi*, 16(2), 51-54 (in Japanese).
- Kainuma K., T. Furukawa and S. Suzuki (1973). Changes in the chemical and physical properties of starch during dextrinization. *Denpun Kagaku*, 20, 1-8 (in Japanese).
- Kainuma K., A. Matsunaga, M. Itagawa and S. Kobayashi (1981). New enzyme system -beta-amylase-pullulanase- To determine the degree of gelatinization and retrogradation of starch or starch products. *Journal of the Japanese Society of Starch Science*, **28**(4), 235-240 (in Japanese).
- Kingsley G. R. and G. Getchell (1960). Direct ultramicro glucose oxidase method for determine of glucose in biologic fluids. *Clinical Chemistry*, **6**,

466-475.

- Kirchoff G. S. C. (1811). Acad. Imp. Sci. St. Petersbourg, Mem., 4, 27 (cited in Whistler R. L. and J. R. Daniel (1984). Molecular structure of starch. In "Starch: Chemistry and Technology," 2nd ed., Academic Press, Inc., Orlando, pp. 153-182).
- Krueger B. R., C. A. Knutson, G. E. Inglett and C. E. Walker (1987). A differential scanning calorimetry study on the effect of annealing on gelatinization behavior of corn starch. *Journal of Food Science*, **52**(3), 715-718.
- Kubota K., Y. Hosokawa, K. Suzuki and H. Hosaka (1979). Studies on the gelatinization rate of rice and potato starches. *Journal of Food Science*, 44, 1394-1397.
- Leach H. W. (1963). Determination of intrinsic viscosity of starches. *Cereal Chemistry*, **40**(6), 593-600.
- Levine I. N. (1983). Solids and liquids. In "Physical chemistry," 2nd ed., McGraw-Hill, New York, pp. 827-864.
- Lim J. K. (1989). Studies on the characteristics of thermo-treated wheat starch and gluten under pressure. *Kyushu University, Dr. Thesis.*
- Lorenz K. and J. A. Johnson (1972). Starch hydrolysis under high temperatures and pressures. *Cereal Chemistry*, **49**, 616-628.
- Mackey K. L. and R. Y. Ofoli (1990a). Rheology of low- to intermediatemoisture whole wheat flour doughs. *Cereal Chemistry*, **67**(3), 221-226.

- Mackey K. L. and R. Y. Ofoli (1990b). Rheological modeling of corn starch doughs at low to intermediate moisture. *Journal of Food Science*, **55**(2), 417-423.
- Mercier C. and P. Feillet (1975). Modification of carbohydrate components by extrusion-cooking of cereal products. *Cereal Chemistry*, **52**(3), 283-297.
- Meyer K. H., W. Brentano and P. Bernfeld (1940). Recherches sur l'amidon II. Sur la nonhomogénéité de l'amidon. *Helvetica chimica acta*, **23**, 845-854.
- Miller B. S., R. I. Derby and H. B. Trimbo (1973). A pictorial explanation for the increase in viscosity of a heated wheat starch-water suspension. *Cereal Chemistry*, **50**, 271-280.
- Morgan R. G., J. F. Steffe and R. Y. Ofoli (1989). A generalized viscosity model for extrusion of protein doughs. *Journal of Food Process Engineering*, 11, 55-78.
- Morgan W. L. (1940). Pasting and identification of starches. *Industrial and Engineering Chemistry*, **12**, 313-317.
- Muffet D. J. and H. E. Snyder (1980). Measurement of unfrozen and free water in soy proteins by differential scanning calorimetry. *Journal of Agricultural* and Food Chemistry, 28, 1303-1305.
- Nakamura M. (1977). Denpun toha. In "Denpun Kagaku Handbook," Asakura Syoten, Tokyo, pp. 3-6 (in Japanese).
- Nakamura K., T. Hatakeyama and H. Hatakeyama (1981). Studies on bound water of cellulose by differential scanning calorimetry. *Textile Research*

Journal, 51, 607-613.

- Noguchi S. (1992). Ketsugosui to Jiyusui. In "Syokuhin to Mizu no Kagaku," Saiwai Syobo, Tokyo, pp. 227-263 (in Japanese).
- Ogura T. (1977). Kako Denpun. In "Denpun Kagaku Handbook," Asakura Syoten, Tokyo, pp. 496-522 (in Japanese).
- Okechukwu P. E., M. A. Rao, P. O. Ngoddy and K. H. Mcwatters (1991). Flow behavior and gelatinization of cowpea flour and starch dispersions. *Journal* of Food Science, 56(5), 1311-1315.
- Owusu-Ansah J., F. R. van de Voort and D. W. Stanley (1983). Physicochemical changes in cornstarch as a function of extrusion variables. *Cereal Chemistry*, 60(4), 319-324.
- Owusu-Ansah J., F. R. van de Voort and D. W. Stanley (1984). Textural and microstructural changes in corn starch as a function of extrusion variables. *Canadian Institute of Food Science and Technology Journal*, **17**(2), 65-70.
- Prey V., W. Eichberger and H. Gruber (1977). Die thermische Zersetzung von D-Glucose. Teil 1. Die trockene Pyrolyse von D-Glucose im Stickstoffstrom.
 Stärke/Starch, **29**(2), 60-65.
- Prey V. and H. Gruber (1977a). Die thermische Zersetzung von D-Glucose. Teil
 2. Die langsame Pyrolyse von D-Glucose unter Stickstoff und Wasserstoff. *Stärke/Starch*, **29**(3), 96-98.
- Prey V. and H. Gruber (1977b). Die thermische Zersetzung von D-Glucose. Teil3. Die Ausbeuten an flüchtigen Produkten und die quantitative

Zusammensetzung der Pyrolyseprodukte. Stärke/Starch, 29(4), 135-138.

- Qu D. and S. S. Wang (1994). Kinetics of the formations of gelatinized and melted starch at extrusion cooking conditions. *Stärke/Starch*, **46**(6), 225-229.
- Remsen C. H. and J. P. Clark (1978). A viscosity model for a cooking dough. Journal of Food Process Engineering, 2, 39-64.
- Ross K. D. (1978). Differential scanning calorimetry of nonfreezable water in solute-macromolecule-water systems *Journal of Food Science*, **43**, 1812-1815.
- Sandhya Rani M. R. and K. R. Bhattacharya (1989). Rheology of rice-flour pastes: Effect of variety, concentration, and temperature and time of cooking. *Journal of Texture Studies*, **20**, 127-137.
- Schoch T. J. and E. C. Maywald (1956). Microscopic examination of modified starches. Analytical Chemistry, 28(3), 382-387.
- Sharma N., M. A. Hanna and Y. R. Chen (1993a). Flow behavior of wheat flour-water dough using capillary rheometer. I. Effect of capillary geometry. *Cereal Chemistry*, **70**(1), 59-63.
- Sharma N., M. A. Hanna and D. B. Marx (1993b). Flow behavior of wheat flour-water dough using capillary rheometer. II. Effects of water, protein, mix, and rest time. *Cereal Chemistry*, **70**(1), 63-67.

- Shiraishi N., Y. Tani, K. Kudo and K. Fukuda (1992). Denpun Genryo no Bioplastic. In "*Bioplastic no Subete*," Kogyo Chosakai, Tokyo, pp. 35-68 (in Japanese).
- Skelland, A. H. P. (1967). Determination of flow properties. In "Non-Newtonian Flow and Heat Transfer," John Wiley & Sons, New York, pp. 27-67.
- Snedecor, G. W. and W. G. Cochran (1972). Polynomial regression. In *"Statistical Methods,"* 6th ed. Transl. by Hatamura, M., T. Okuno and Y. Tsumura, Iwanami syoten, Tokyo, pp. 398-415 (in Japanese).
- Stevens D. J. and G. A. H. Elton (1971). Thermal properties of the starch water system. I. Measurement of heat of gelatinization by differential scanning calorimetry. *Stärke /Starch*, **23**(1), 8-11.
- Tang J. and X. -L. Ding (1994). Relationship between functional properties and macromolecular modifications of extruded corn starch. *Cereal Chemistry*, **71**(4), 364-369.
- Thompson A., M. L. Wolfrom and E. J. Quinn (1953). Acid reversion in relation to isomaltose as a starch hydrolytic product. *Journal of the American Chemical Society*, **75**, 3003-3004.
- Thompson A., K. Anno, M. L. Wolfrom and M. Inatome (1954). Acid reversion products from D-glucose. *Journal of the American Chemical Society*, **76**, 1309-1311.
- Tomasik P., S. Wiejak and M. Palasinski (1989). The thermal decomposition of carbohydrates. Part II. The decomposition of starch. *Advances in*

Carbohydrate Chemistry and Biochemistry, 47, 279-343.

- Ueno Y., M. Izumi and K. Kato (1976). Studies on pyrodextrinization of corn starch. *Stärke/Starch*, **28**(3), 77-82.
- Urbanski G. E., L. S. Wei, A. I. Nelson and M. P. Steinberg (1983). Rheology models for pseudoplastic soy systems based on water binding. *Journal of Food Science*, **48**, 1436-1439.
- Wang S. S., W. C. Chiang, B. Zhao, X. G. Zheng and I. H. Kim (1991). Experimental analysis and computer simulation of starch-water interactions during phase transition. *Journal of Food Science*, 56(1), 121-124.
- Watson S. A. (1964). Determination of starch gelatinization temperature. Methods in Carbohydrate Chemistry, 4, 240-242.
- Zobel H. F. (1984). Gelatinization of starch and mechanical properties of starch pastes. In "Starch: Chemistry and Technology," 2nd ed. Academic Press, Inc., Orlando, pp. 285-309.

ACKNOWLEDGMENT

I am particularly indebted to Professor Yusaku Fujio and Associate Professor Isao Hayakawa in Kyushu University for their help in this experiments and the preparation of this thesis and the many useful suggestions for its improvement. I wish to thank Professor Mitsuo Higuchi in Kyushu University for the many useful suggestions in the preparation of this thesis.

I also wish to thank Associate Professor N. Hayashi in Saga University for training for experiments of a capillary tube viscometer. I would like to express my gratitude to the members of Food Process Engineering Laboratory in Kyushu University. My thanks are especially given to Mr. T. Katoh for the experimental techniques and advices and giving me comfortable experimental circumstances.

Most of all, I would like to express my deep heartful thanks to my mother and to the memory of my father. I would not have been possible to finish writing this thesis without their encouragement. It is a great pleasure to dedicate this thesis to my family.


