Bioremediation of highly toxic arsenic via carbon-fiber-assisted indirect As(III) oxidation by moderately-thermophilic, acidophilic Fe-oxidizing bacteria

Okibe, Naoko

Department of Earth Resources Engineering, Faculty of Engineering, Kyushu University

Fukano, Yuken

Department of Earth Resources Engineering, Faculty of Engineering, Kyushu University

<http://hdl.handle.net/2324/4737409>

出版情報 : Biotechnology Letters. 41 (12), pp.1403-1413, 2019-10-26. Springer
バージョン :
権利関係 :

2 **Title:**

3 Bioremediation of highly toxic arsenic via carbon-fiber-assisted indirect As(III) oxidation by
4 moderately-thermophilic, acidophilic Fe-oxidizing bacteria [Revised]

5
6 Naoko OKIBE*, Yuken FUKANO

7
8 Department of Earth Resources Engineering, Faculty of Engineering, Kyushu University, 744
9 Motoooka, Nishi-ku, Fukuoka 819-0395, Japan

10
11 *Corresponding author.

12 Tel. and Fax: + 81 92 802 3312

13 E-mail address: okibe@mine.kyushu-u.ac.jp (Naoko OKIBE)

14
15 **Keywords:** Bioremediation, Arsenic, As(III), Oxidation, Scorodite, Acidophile, Fe-oxidizing
16 bacteria, carbon-fiber

Abstract

Objective To enable removal of highly toxic As(III) from acidic waters by inducing indirect microbial As(III) oxidation by Fe-oxidizing bacteria via carbon-assisted redox-coupling between As(III) oxidation and Fe^{3+} reduction.

Results Carbon-fiber (CF) was shown to function as an electron-mediator to catalyze chemical (abiotic) redox-coupling between As(III) oxidation and Fe^{3+} reduction. Accordingly, by taking advantage of Fe^{3+} regeneration by Fe-oxidizing bacteria, it was possible to promote oxidative removal of As(III) as ferric arsenate at moderate temperature. This reaction can be of use under the situation where a high-temperature treatment is not immediately available. Arsenic once concentrated as ferric arsenate on carbon-fibers can be collected to undergo phase-transformation to crystalline scorodite as the next re-solubilization/re-crystallization step at a higher temperature (70°C).

Conclusions While extremely acidophilic Fe-oxidizing bacteria are widely found in nature, the As-oxidizing counterparts, especially those grown on moderately-thermophilic and mesophilic temperatures, are hardly known. In this regard, the finding of this study could make a possible introduction of the semi-passive, low-temperature As-treatment using readily available Fe-oxidizing bacteria.

Introduction

Arsenic (As) is the 20th most abundant element in the Earth's crust and is often found as sulfide minerals such as enargite (Cu_3AsS_4), tennantite ($\text{Cu}_{12}\text{As}_4\text{S}_{13}$) and arsenopyrite (FeAsS) (Ehrlich and Newman 2009; Mandal and Suzuki 2002). Since As is dissolved in water as As(III) or As(V) and the former more toxic/mobile than the latter (especially at acidic pH), As(III) is generally first oxidized to As(V) prior to immobilization (Cullen and Reimer 1989; Matschullat 2000). Mining-impacted highly-acidic waters often contain As(III) and its effective remediation approach needs to be developed.

Mineralization of soluble As into scorodite ($\text{Fe}^{\text{III}}\text{As}^{\text{V}}\text{O}_4 \cdot 2\text{H}_2\text{O}$) is considered to be one of the ideal approaches for long-term As storage due to the mineral's stability and low Fe demand (Langmuir et al. 2006; Riveros et al. 2001). Chemical scorodite synthesis is generally effective for concentrated As solutions (~hundreds of millimolar) using higher temperatures (mostly 95–160°C) either by hydrothermal methods (e.g. Monhemius and Swash 1999; Demopoulos et al. 1995) or by atmospheric methods (e.g. Filippou and Demopoulos 1997; Singhania et al. 2006; Fujita et al. 2009). On the other hand, use of microbiological reaction enables scorodite crystallization even under thermodynamically less feasible, milder conditions (e.g., lower temperatures, lower As concentrations) (Gonzalez-Contreras 2010, 2012; Okibe et al. 2013, 2014, 2017, 2018; Tanaka and Okibe 2018): e.g. By using the thermophilic, extremely acidophilic archaeon *Acidianus brierleyi* at 70°C, oxidation of As(III) (in the range of 3.3 – 20 mM) and Fe^{2+} were simultaneously progressed to form biogenic scorodite without addition of chemical oxidants. However, under situations where As(III)-contaminated waters cannot be immediately processed at this level of temperature (~70°C), a necessity arises to look for As-oxidizing acidophiles of lower growth temperatures. Among those autotrophic and heterotrophic As-oxidizers reported so far, the majority are neutrophilic bacteria with a few studies on acid-tolerant species such as *Thiomonas* spp. (Cavalca et al. 2013) and unknown acidophilic strains (Nakazawa and Hareyama 2007). Nonetheless, to our knowledge, there is yet no detailed study available on extremely-acidophilic As-oxidizers with moderately-thermophilic or mesophilic growth temperatures, which exhibit robust As(III) oxidation at the concentration of several millimolar.

To overcome unavailability of such useful microbes, this study investigated the possibility to indirectly induce As(III) oxidation via Fe^{2+} oxidation by readily available Fe-oxidizing acidophiles. As an electron-mediating catalytic material, carbon-fiber (CF) was studied. Carbon-fibers contain at least 90% carbon and are generally produced by pyrolysis of an

appropriate precursor, predominantly from polyacrylonitrile. While the use of CF in aircraft and automotive industries are well-known (Minus and Kumar 2005), it is worth investigating their potential applicability in water treatment, owing to their high physical strength and conductivity, as a durable electron-mediating redox catalyst.

Materials and methods

Microorganism

Three moderately-thermophilic, acidophilic Fe-oxidizing strains were used: *Acidimicrobium ferrooxidans* ICP^T (DSM 10331), *Sulfobacillus sibiricus* N1^T (DSM 17363), and *Sulfobacillus thermotolerans* Kr1^T (DSM 17362). The three strains were maintained and pre-grown aerobically at 45°C in heterotrophic basal salts (HBS) media (per liter; 450 mg (NH₄)₂SO₄, 50 mg KCl, 50 mg KH₂PO₄, 500 mg MgSO₄•7H₂O, 14 mg Ca(NO₃)₂•4H₂O, 142 mg Na₂SO₄; pH 2.0 with H₂SO₄) containing 0.02% yeast extract.

As(III) tolerance during heterotrophic growth (on yeast extract) of Fe-oxidizing strains

Each Fe-oxidizing strain (*Am. ferrooxidans*, *Sb. sibiricus* or *Sb. thermotolerans*) was inoculated (at 1.0 x 10⁷ cells/ml) in 100 ml of HBS media (pH 2.0) containing 0.02% yeast extract (in 300 ml flasks). As(III) was added (as NaAsO₂) to the media at 0, 1.3, 2.6, 6.5 or 13 mM. The flasks were incubated shaken at 100 rpm, 45°C. Samples were regularly taken to monitor cell density (using bacterial counting chamber). The experiments were conducted in duplicate flasks.

Evaluation of As-oxidizing ability of Fe-oxidizing strains

Each Fe-oxidizing strain (*Am. ferrooxidans*, *Sb. sibiricus* or *Sb. thermotolerans*) was pre-grown, harvested at the late-exponential phase, washed, and re-suspended (at 1.0 x 10⁸ cells/ml in order to ease the detection of As(III) oxidation) in 200 ml of fresh HBS medium (pH 2.0) containing 0.02% yeast extract, 6.5 mM As(III), with or without 9 mM Fe²⁺ (as FeSO₄•7H₂O) (in 500 ml flasks). The flasks were incubated shaken at 100 rpm, 45°C. Samples were regularly taken to monitor cell density (using bacterial counting chamber), pH, Eh (vs. SHE) and concentrations of As(III) (Nano-Band Explorer stripping voltammetry; GL Sciences), Fe(II) (o-phenanthroline method), As_{total} and Fe_{total} (ICP-OES; PerkinElmer Optima8300). The experiments were conducted in duplicate flasks.

Evaluation of chemical (abiotic) Fe- and As-oxidizing capability of CF

Milled CF (CFMP-30X, Nippon Polymer; 1% (w/v)) was added into 200 ml of HBS medium (pH 2.0) containing 0.02% yeast extract (in 500 ml flasks).

Cell-free controls: Either 9 mM Fe^{2+} , 9 mM Fe^{3+} , 6.5 mM As(III), 6.5 mM As(V) or 9 mM Fe^{2+} plus 6.5 mM As(III) was added to each flask to test the chemical oxidation/absorption effect of CF on individual ions.

Microbial cultures: Either 9 mM Fe^{2+} , 6.5 mM As(III) or 9 mM Fe^{2+} plus 6.5 mM As(III) was added to each flask to test the indirect CF-assisted As(III) oxidation via microbial Fe^{2+} oxidation. In Fe^{2+} -containing media, *Am. ferrooxidans* cells were inoculated at 1.0×10^7 cells/ml. In Fe^{2+} -free media, cells were inoculated at 1.0×10^8 cells/ml, as no growth was expected during incubation.

Solid analysis

Precipitates on the CF surface were collected and freeze-dried overnight for scanning electron microscope observation (SEM; KEYENCE VE-9800; Vacuum Device MSP-1S for Au-Pd sputtering) and X-ray diffraction analysis (XRD; Rigaku Ultima IV; $\text{CuK}\alpha$ 20 mA, 40 kV). To quantify the elemental composition of the precipitates, the sample was embedded into resin, polished and measured by SEM-EDX (HITACHI SU-70; 6.0 kV; 30 sec for each point) using the Phi-Rho-Z method (Packwood and Brown 1981). The sample was also mixed with boron nitride to form tablets, to perform X-Ray near edge structure (XANES) analysis. The Fe K-edge XANES spectra (fluorescence mode; 6800–7200 eV) and As K-edge XANES spectra (fluorescence mode; 11600–12000 eV) at SAGA-LS (1.4 GeV, 75.6 m), using standards of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ (Wako chemicals; No. 7782-63-0), Fe_2O_3 (Wako chemicals; No. 1309-37-1), NaAsO_2 (Wako chemicals; No. 7784-46-5), KH_2AsO_4 (Wako chemicals; No. 7784-41-0), chemically synthesized $\text{FeAsO}_4 \cdot 2\text{H}_2\text{O}$ (Tanaka and Okibe 2018) and bacterial cells.

Phase transformation of amorphous As-precipitates into crystalline scorodite

Carbon-fibers were repeatedly used according to the reaction shown in Fig. 3 (Fe^{2+} + As(III) with cells; 45°C) until 77 mg-Fe and 68 mg-As (per g-CF) were accumulated as amorphous $\text{Fe}^{\text{III}}\text{-As}^{\text{V}}$ precipitates. In order to dissolve this precipitate to produce more

concentrated As- and Fe-containing solution (to facilitate scorodite mineralization), 1.4 g (dry-weight) of the CF-precipitate mixture was put into 40 mL acidic water (pH 1.0 with H₂SO₄) in 100 mL flasks, incubated shaken at 100 rpm at ambient temperature (the complete dissolution of the precipitate would give 41 mM Fe and 27 mM As in the 40 mL solution). At 14 hours, CFs were removed from the leachate by filtration and scorodite-seeds were fed at 3% (w/v) instead. The leachate was then further incubated at 70°C. In the control experiment, CF was not removed at 14 h.

Results and discussion

As(III) tolerance of Fe-oxidizing strains during heterotrophic (Fe²⁺-free) growth.

The highest cell densities were recorded with the heterotrophic Fe-oxidizer *Am. ferrooxidans* (Clark and Norris 1996), compared to the other two heterotrophic Fe-/S-oxidizing *Sulfobacillus* spp. (Melamud et al. 2003; Bogdanova et al., 2006): Its growth was not much affected by the presence of up to 2.6 mM As(III), but was significantly inhibited by 6.5 mM As(III) (Fig. 1a). In the case of *Sb. sibiricus*, 6.5 mM As(III) completely inhibited its growth (Fig. 1b). *Sb. thermotolerans* showed relatively robust growth in the presence of elevated concentrations of As(III), even at 13 mM As(III) (Fig. 1c). Nonetheless, the growth of *Am. ferrooxidans* at 6.5 mM As(III) was still comparable (Fig. 1a) to the other two *Sulfobacillus* spp. without As(III) (Fig. 1b, c). Some acidophiles were shown to possess the arsenic resistance mechanism encoded by the *ars* operon (Dopson et al. 2003) and its presence was also suggested in *Am. ferrooxidans* based on the complete genome sequence (Clum et al. 2009).

[Fig. 1 inserted here]

Evaluation of As-oxidizing ability in Fe-oxidizing strains

In order to ease the detection of microbial As(III) oxidation activity, the initial cell density was set 10-times higher in this test (at 1.0 x 10⁸ cells/ml) (Fig. 2). In Fe²⁺-free media, no further cell growth was observed (Fig. 2e) and no obvious microbial As(III) oxidation was noted (Fig. 2d). In Fe²⁺-containing media, although rapid microbial Fe²⁺ oxidation (Fig. 2a) resulted in further cell growth (Fig. 2c), no As(III) oxidation was detected (Fig. 2b). Unlike some thermo-acidophilic Fe-oxidizing archaea (e.g., *Ac. brierleyi* and some *Sulfolobus* spp.; Okibe et al. 2014;

Vega-Hernandez et al. 2019) the obvious As(III) oxidase activity was detected in neither of moderate-thermophiles tested in this study (at least under the conditions tested): i.e., in addition to the three Fe-oxidizing strains mentioned, no apparent As-oxidizing activity was observed in others including *Ferropasma acidiphilum* Y (DSM 12658), *Acidiplasma* Fv-Ap and *Acidithiobacillus caldus* KU (DSM8584) (data not shown). So far in majority of cases, As(III) oxidase activity is known in neutrophiles (Cavalca et al. 2013), while there are a few cases with acid-tolerant species such as *Thiomonas* sp. and *Acidiphilium* sp. (Battaglia-Brunet et al. 2011; Wakao et al. 1994). However, when *Th. cuprina* H65 (DSM 5495T) and *Ap. multivorum* AIU301 (JCM 8867) were tested under highly-acidic condition (pH 2.0), their growth and As(III) oxidation were completely inhibited (Okibe et al. unpublished data). With regard to extreme acidophiles, neither mesophilic Fe-oxidizer *At. ferrooxidans* nor moderately-thermophilic mixed cultures were shown to exhibit As(III) oxidation (Barrett et al. 1993). Overall, the results from previous and present studies indicate that the existence of As-oxidizing ability in moderately-thermophilic and mesophilic acidophiles is yet largely unknown.

Hence, although no direct microbial As(III) oxidation was possible using these moderate thermophiles, *Am. ferrooxidans* was selected for further studies owing to its robust growth and Fe-oxidizing ability in acidic As(III) solution. The observation that a mere generation of Fe³⁺ did not induce As(III) oxidation indicates the presence of a kinetic restriction in the reaction shown in Eq. 1. Although Eq. 1 is thermodynamically favored according to the standard redox potentials shown in Eqs. 2-3, such a kinetic restriction needs to be overcome by the addition of an electron-mediating catalyst. Kamde et al. (2018) reported that As(III) oxidation was induced via microbial Fe²⁺ oxidation (by *Acidothiobacillus ferrooxidans*) without using such a catalyst. In their study, however, a highly excessive amount of Fe²⁺ (2 g/L; 36 mM) was added to trigger oxidation of a small amount of As(III) (5 mg/L; 0.07 mM), with the final product of jarosite and schwertmannite. Nonetheless, since our study targets almost equivalent molar amounts of As and Fe, the necessity of an effective electron-mediator is emphasized.

[Fig. 2 inserted here]

Carbon-fiber-assisted As(III) oxidation coupled with Fe³⁺ reduction in microbial cultures

In cell-free controls:

When only Fe²⁺ ions were initially added to CF, nearly a half were oxidized to Fe³⁺ by day 1 (Fig. 3a), suggesting that CF naturally possesses chemical catalytic effect for Fe²⁺ oxidation (using atmospheric O₂ as e-donor). While it was not evident from the Fe_{total} concentration profile (Fig. 3b), a tiny portion of the resultant Fe³⁺ ions (but not original Fe²⁺ ions) were found to be adsorbed onto the CF surface (Fig. 3b), according to the XANES analysis (Fig. 4a-4). No precipitate deposition on the CF surface was noted by SEM observation (data not shown). While when only As(III) ions were initially added to CF, CF displayed neither obvious chemical As-oxidizing effect (Fig. 3c) nor As adsorption effect (Fig. 3d). In fact, the XANES analysis did not detect the presence of As on the CF surface (Fig. 4b-5).

When Fe²⁺ and As(III) ions were simultaneously added to CF, nearly a half of Fe²⁺ ions were chemically oxidized by day 1 (Fig. 1a). Although not clearly seen from the Fe_{total} concentration change (Fig. 3b), an aliquot of generated Fe³⁺ were immobilized onto the CF surface based on the XANES analysis (Fig. 4a-6). Under this condition, no major changes in the concentration of As(III) and As_{total} were noticed from Fig. 3c and 3d, respectively. A separate experiment showed that As(V) ions do not absorb onto the CF surface without Fe addition (data not shown). Therefore, it was suggested from the XANES result that a small fraction of As(III) was oxidized to As(V) and co-precipitated with Fe³⁺ on the CF surface (Fig. 4b-6), while the formation of precipitates was not visible by SEM (data not shown). Lastly, when Fe was initially added as Fe³⁺ together with As(III), Fe²⁺ ions appeared and gradually increased (Fig. 3a), coincided with a gradual decrease in the As(III) concentration (Fig. 3c). This indicates that As(III) oxidation was facilitated on the CF surface via chemical redox-coupling with Fe³⁺ reduction. A similar observation was made by Barrett et al. (1993), wherein a kinetic restriction of As(III) oxidation coupled with Fe³⁺ reduction was overcome by the presence of semi-conductive pyrite mineral. Oxidation of 3.3 mM As(III) to As(V) (Fig. 3c) was accompanied with “apparent” reduction of 3 mM Fe³⁺ to Fe²⁺ (Fig. 3a), although theoretically, 6.6 mM of Fe³⁺ needs to be reduced to Fe²⁺ (according to Eq. 1). This difference indicates the occurrence of Fe-cycling (i.e., chemical Fe²⁺ oxidation by atmospheric O₂ [Eq. 4] and Fe³⁺ reduction coupled with As(III) oxidation [Eq. 1]) in the system. Generation of As(V) in the presence of Fe³⁺ allowed removal of

approx. 2 mM Fe (22%; Fig. 3b) and 1.5 mM As (23%; Fig. 3d) as Fe^{III}-As^V precipitates (Fig. 4a-6; Fig. 4b-6) as visualized by SEM (Fig. 5e).

In microbial cultures:

When only Fe²⁺ ions were initially added to CF, oxidation of Fe²⁺ was promptly completed by day 1 accompanied by cell growth (Fig. 3e), after which Fe³⁺ predominated the Fe species owing to microbial activity (Fig. 3a). This led to the removal of about 60% of Fe by day 8 (Fig. 3b) on the CF surface in the form of Fe^{III}-precipitates (Fig. 4a-1; Fig. 5b). When only As(III) ions were initially added to CF, about 40% of As(III) was unexpectedly oxidized to As(V) (Fig. 3c). Since neither microbial As-oxidizing ability of *Am. ferrooxidans* (Fig. 2) nor the chemical (abiotic) catalytic activity of CF for As(III) oxidation was clearly noted (cell-free controls in Fig. 3), it was not expected that As(III) is oxidized to As(V) on the CF surface in the presence of cells. It can be hypothesized that *Am. ferrooxidans* originally possesses a negligible extent of As-oxidizing activity (possibly via a negligible amount of carryover Fe³⁺ on the cell surface, but not clearly detectable under the conditions tested), which can be amplified and visualized by the presence of CF. However, this hypothesis must be validated by further detailed experiments. Although not clearly visible from the As_{total} concentration change (Fig. 3d), an aliquot of the resultant As(V) ions were shown to be adsorbed onto the CF surface according to the XANES result (Fig. 4b-2).

When Fe²⁺ and As(III) ions were simultaneously added, Fe²⁺ oxidation was rapidly completed by day 1 (Fig. 3a). As(III) oxidation readily proceeded via Fe³⁺ reduction (Fig. 3c), owing to continuous Fe³⁺ regeneration by microbes (Fig. 3a) according to Eq. 5. As a result, about 70% Fe (6.5 mM; Fig. 3b) and 60% As (4 mM; Fig. 3d) were effectively removed by day 8 in the form of Fe^{III}-As^V precipitates (Fig. 4a-3; b-3) as observed by SEM (Fig. 5c). The precipitate was amorphous (by XRD analysis) with the average elemental composition of As: Fe: O = 1: 1.8 : 5.4 (Fig. 6). In our parallel tests started with double amount of Fe²⁺ (18 mM) and As(III) (13 mM), both ions were completely oxidized on the 1% CF surface (data not shown). Therefore, the use of 1% CF is unlikely the rate-limiting factor in this study. Rather, the absolute amount of Fe³⁺ may affect the effectiveness of the coupling reaction. However, further investigations are needed to

clarify this. When Fe³⁺, instead of Fe²⁺, was initially added together with As(III), the trends in Fe²⁺/Fe_{total} and As(III)/As_{total} concentrations were identical to those observed in the cell-free counterpart. The initial planktonic-cell count was dramatically decreased (Fig. 3e), likely due to the lack of energy source as well as cell attachment/encrustation on CF via formation of Fe^{III}-As^V precipitates (Fig. 5d). Since the initial cell number was unchanged when cells were simply mixed with CF without the addition of Fe and As (data not shown), it is suggested that deposition of amorphous Fe^{III}-As^V precipitates has a role to ‘glue’ cells onto the CF surface. The later slight recovery of planktonic cell counts (after day 3; Fig. 3e) may be due to a gradual supply of Fe²⁺ to the cells.

The above results can be summarized as follows:

- (i) Regardless of the presence of Fe³⁺, no As(III) oxidation was observed in catalyst-free bulk solution (neither abiotic nor biotic).
- (ii) The effect of CF catalyst on individual ion (Fe²⁺ or As(III)) was different: Abiotic Fe²⁺ oxidation was catalyzed but to a limited extent. Abiotic As(III) oxidation, on the other hand, was not observed.
- (iii) In solutions containing both Fe³⁺ and As(III), abiotic As(III) oxidation proceeded via Fe³⁺ reduction on the CF catalyst. This led to the As removal but to a limited extent. The presence of Fe-oxidizing cells unaffected this trend.
- (iv) Continuous regeneration of Fe³⁺ by Fe-oxidizing cells were essential to facilitate As(III) oxidation on the CF catalyst. This enabled effective As removal as Fe^{III}-As^V precipitate.

[Fig. 3, 4, 5, 6 inserted here]

Phase transformation of amorphous As-precipitates into crystalline scorodite

Carbon-fibers coated with amorphous Fe^{III}-As^V precipitates (Fig. 7c-1) were transferred into a smaller volume of acidic water (pH 1.0) and incubated at ambient temperature to temporarily resolubilize Fe³⁺ and As(V) to produce the 4-times concentrated solution. The theoretical peak concentration (upon complete solubilization) of 41 mM Fe and 27 mM As were

expected, but were not visible in Fig. 7a and b, respectively, due to the simultaneous occurrence of re-solubilization and re-crystallization. When CFs were replaced with scorodite-seeds and incubation temperature increased to 70°C at 14 h, the final As removal was 91% at 170 h. Chemically-synthesized scorodite-seed crystals (Fig. 7c-2) became evenly coated with newly generated secondary layers (Fig. 7c-4). In the control test, CFs were not pulled out at 14 h (no seeds added) but the incubation temperature raised to 70°C. In this case, Fe³⁺ and As(V) quickly re-crystallized onto the CF surface to form riziform particles similar to biogenic scorodite particles observed in our previous studies (Okibe et al. 2014). In either case, the products were identified as scorodite as shown in Fig. 8. During the phase transformation from amorphous precipitate to crystalline scorodite, the ratio of Fe/As was reduced from 1.8 (according to the EPMA analysis; Fig. 6) to 1.3 (calculated from liquid analysis data; Fig. 7ab).

A preliminary investigation on CF-assisted As(III) oxidation (at 45°C) by Fukano et al. (2015), was followed by studies employing the concept of this carbon-assisted indirect microbial As(III) oxidation using activated carbon (AC) both at a lower (45°C; Hotta et al. 2017) and a higher (65°C; Vega-Hernandez et al. 2019) temperature. Amorphous Fe³⁺/As(V)-precipitates generally showed high affinity to the carbon surface as observed with CFs in this study (Fig. 5c; Fig.6; Fig. 7c-1) and also with ACs (Okibe et al. unpublished data). Due to the structural differences between CF and AC (i.e., the latter with higher porosity and surface area; Manocha 2003), amorphous Fe³⁺/As(V)-precipitates were difficult to re-solubilize from ACs (Okibe et al., unpublished data). Therefore, in the case that carbon-free scorodite minerals are to be produced for the sake of waste volume reduction (as well as carbon materials are to be recycled), the use of CF rather than AC may be more favorable. Also, due to their high physical strength (Minus and Kumar 2005), deformation of CFs was not noticed by SEM observation after days of vigorous shaking, while ACs seemed to be less physically resistant.

In conclusion, based on the overall findings, the following As-removal procedure can be proposed (Fig. 9): Under the situations where the on-site high-temperature scorodite production is not immediately feasible, or direct scorodite crystallization is infeasible due to the low As(III)-contamination level on site, the first As-removal can be realized as amorphous Fe^{III}-As^V precipitates, using a combination of electron-mediating carbon material and locally available Fe-oxidizing bacteria. This step can be done at moderate temperatures (also at mesophilic temperatures; Okibe et al. unpublished data) as a semi-passive, first on-site treatment. For safer

As storage as crystalline scorodite, the CF-precipitate mixture can be transported for the further re-solubilization, concentration and re-crystallization process at higher temperatures (~70°C).

[Fig. 7, 8, 9 inserted here]

References

- Barrett J, Ewart DK, Hughes MN, Poole RK (1993) Chemical and biological pathways in the bacterial oxidation of arsenopyrite. FEMS Microbiol Rev 11:57–62
- Battaglia-Brunet F, El Achbouni H, Quemeneur M, Hallberg KB, Kelly DP, Joulain C (2011) Proposal that the arsenite-oxidizing organisms *Thiomonas cuprina* and '*Thiomonas arsenivorans*' be reclassified as strains of *Thiomonas delicata*, and emended description of *Thiomonas delicata*. Int J Syst Evol Microbiol 61:2816–2821
- Boekestein A, Stadhouders AM, Stols ALH, Roomans GM (1983) A comparison of ZAF-correction methods in quantitative X-ray microanalysis of light-element specimens. Ultramicroscopy 12:65–68
- Bogdanova TI, Tsaplina IA, Kondrat'eva TF, Duda VI, Suzina NE, Melamud VS, Tourova TP, Karavaiko GI (2006) *Sulfobacillus thermotolerans* sp. nov., a thermotolerant, chemolithotrophic bacterium. Int J Syst Evol Microbiol 56:1039–1042
- Cavalca L, Corsini A, Zaccheo P, Andreoni V, Muyzer G (2013) Microbial transformations of arsenic: perspectives for biological removal of arsenic from water. Future Microbiol 8:753–768
- Clark DA, Norris PR (1996) *Acidimicrobium ferrooxidans* gen. nov., sp. nov.: Mixed-culture ferrous iron oxidation with *Sulfobacillus* species. Microbiol UK 142:785–790.
- Clum A, Nolan M, Lang E, Glavina Del Rio T, Tice H, Copeland A, Cheng JF, Lucas S, Chen F, Bruce D, Goodwin L, Pitluck S, Ivanova N, Mavrommatis K, Mikhailova N, Pati A, Chen A, Palaniappan K, Göker M, Spring S, Land M, Hauser L, Chang YJ, Jeffries CC, Chain P, Bristow J, Eisen JA, Markowitz V, Hugenholtz P, Kyrpides NC, Klenk HP, Lapidus A (2009) Complete genome sequence of *Acidimicrobium ferrooxidans* type strain (ICP). Stand Genomic Sci 1:38–45

348 Cullen WR, Reimer KJ (1989) Arsenic speciation in the environment. Chem Rev 89:713–764
349
350 Demopoulos GP, Droppert DJ, Van Weert G (1995) Precipitation of crystalline scorodite
351 (FeAsO₄·2H₂O) from chloride solutions. Hydrometallurgy 38:245–261
352
353 Dopson M, Baker-Austin C, Koppineedi PR, Bond PL (2003) Growth in sulfidic mineral
354 environments: metal resistance mechanisms in acidophilic micro-organisms. Microbiology 149:
355 1959–1970.
356
357 Ehrlich HL, Newman DK (2009) Geomicrobiology, fifth ed. CRC Press, Boca Roton.
358 Filippou D, Demopoulos GP (1997) Arsenic immobilization by controlled scorodite precipitation.
359 JOM 49:52–55
360
361 Fujita T, Taguchi R, Kubo H, Shibata E, Nakamura T (2009) Immobilization of arsenic from novel
362 synthesized scorodite – Analysis on solubility and stability. Mater Trans 50:321–331
363
364 Fukano Y, Hirajima T, Sasaki K, Okibe N (2015) Mechanism of indirect chemical oxidation of
365 highly toxic As(III), in the presence of carbon fiber via direct microbial Fe(II) oxidation.
366 Proceedings of International Symposium on Earth Science and Technology 2015, pp163–165
367
368 Gonzalez-Contreras P, Weijma J, Buisman CJN (2012) Continuous bioscorodite crystallization in
369 CSTRs for arsenic removal and disposal. Water Res 46:5883–5892
370
371 Gonzalez-Contreras P, Weijma J, Weijden RVD, Buisman CJN (2010) Biogenic scorodite
372 crystallization by *Acidianus sulfidivorans* for arsenic removal. Environ Sci Technol 44:675–680
373
374 Hotta Y, Hirajima T, Sasaki K, Okibe N (2017) Activated carbon-assisted oxidation and
375 immobilization of highly toxic arsenite. International Symposium on Earth Science and
376 Technology 2017, pp 380–381
377
378 Kamde K, Pandey RA, Thul ST, Dahake R, Shinde VM, Bansawal A (2018) Microbially assisted
379 arsenic removal using *Acidothiobacillus ferrooxidans* mediated by iron oxidation. Environ
380 Technol Inno 10:78–90

381

382 Langmuir D, Mahoney J, Rowson J (2006) Solubility products of amorphous ferric arsenate and
 383 crystalline scorodite ($\text{FeAsO}_4 \cdot 2\text{H}_2\text{O}$) and their application to arsenic behavior in buried mine
 384 tailings. *Geochim Cosmochim Acta* 70:2942–2956

385

386 Mandal BK, Suzuki KT (2002) Arsenic round the world: a review. *Talanta* 58: 201–235

387

388 Manocha SM (2003) Porous carbons. *Sadhana* 28:335–348

389

390 Matschullat J (2000) Arsenic in the geosphere — a review. *Sci Total Environ* 249:297–312

391

392 Melamud VS, Pivovarova TA, Tourova TP, Kolganova TV, Osipov GA, Lysenko AM,
 393 Kondrat'eva TF, Karavaiko GI (2003) *Sulfobacillus sibiricus* sp. nov., a new moderately
 394 thermophilic bacterium. *Microbiology* 72:605–612

395

396 Minus ML, Kumar S (2005) The processing, properties, and structure of carbon fibers. *JOM*
 397 57:52–58

398 Monhemius AJ, Swash PM (1999) Removing and stabilizing As from copper refining circuits by
 399 hydrothermal processing. *JOM* 51:30–33

400

401 Nakazawa H, Hareyama W (2007) Biological oxidation of arsenite in strong acid water. *Res*
 402 *Process* 54:182–186

403

404 Okibe N, Koga M, Morishita S, Tanaka M, Heguri S, Asano S, Sasaki K, Hirajima T (2014)
 405 Microbial formation of crystalline scorodite for treatment of As(III)-bearing copper refinery
 406 process solution using *Acidianus brierleyi*. *Hydrometallurgy* 143:34–41

407

408 Okibe N, Koga M, Sasaki K, Hirajima T, Heguri S, Asano S (2013) Simultaneous oxidation and
 409 immobilization of arsenite from refinery waste water by thermoacidophilic iron-oxidizing
 410 archaeon, *Acidianus brierleyi*. *Miner Eng* 48:126–134

411

412 Okibe N, Morishita S, Tanaka M, Sasaki K, Hirajima T, Hatano K, Ohata A (2017) Bioscorodite

crystallization using *Acidianus brierleyi*: Effects caused by Cu(II) present in As(III)-bearing copper refinery wastewaters. Hydrometallurgy 168:121–126

Packwood RH, Brown JD (1981) A Gaussian expression to describe $\phi(\rho z)$ curves for quantitative electron probe microanalysis. X-Ray Spectrometry 10:138-146

Riveros PA, Dutrizac JE, Spencer P (2001) Arsenic disposal practices in the metallurgical industry. Can Metall Q 40:395–420

Singhania S, Wang Q, Filippou D, Demopoulos GP (2006) Acidity, valency and third-ion effects on the precipitation of scorodite from mixed sulfate solutions under atmospheric-pressure conditions. Metall Mater Trans B 37:189–197

Tanaka M, Okibe N (2018) Factors to enable crystallization of environmentally stable bioscorodite from dilute As(III)-contaminated waters. Minerals 8:23

Tanaka M, Okibe N, Sasaki K (2018) Behavior of sulfate ions during biogenic scorodite crystallization from dilute As(III)-bearing acidic waters. Hydrometallurgy 180:144–152

Vega-Hernandez, Weijma J, Buisman CJN (2019) Immobilization of arsenic as scorodite by a thermoacidophilic mixed culture via As(III)-catalyzed oxidation with activated carbon. J Hazard Mater 368:221–227

Wakao N, Nagasawa N, Matsuura T, Matsukura H, Matsumoto T, Hiraishi A, Sakurai Y, Shiota H (1994) *Acidiphilium multivorum* sp. nov., an acidophilic chemoorganotrophic bacterium from pyritic acid mine drainage. J Gen Appl Microbiol 40:143–159

Acknowledgments

This work was supported by JX Nippon Mining & Metals. The XAFS experiments were performed at the SAGA Light Source (Kyushu University Beam Line; BL06, No. 2014IHK025). *Acidiplasma* sp. Fv-Ap was kindly provided by Prof. D. B. Johnson (Bangor University, UK).

Figure Legends

Fig. 1 Inhibitory effect of As(III) on heterotrophic (Fe^{2+} -free) growth of *Am. ferrooxidans* (a), *Sb. sibiricus* (b) and *Sb. thermotolerans* (c). Initial conditions: $[\text{As(III)}] = 0 \text{ mM}$ ($\times$), 1.3 mM ($\circ$), 2.6 mM ($\blacktriangle$), 6.5 mM ($\blacklozenge$) or 13 mM ($-$); 1.0×10^7 cells/ml. Data points are mean values from duplicate cultures.

Fig. 2 Evaluation of As-oxidizing ability in Fe-oxidizing strains ($\bullet$ *Am. ferrooxidans*; $\times$ *Sb. sibiricus*, $\triangle$ *Sb. thermotolerans*; $-$ cell-free control). Changes in the Fe^{2+} concentration (a), As(III) concentration (b, d) and cell density (c, e) were monitored. Initial conditions: $[\text{As(III)}] = 6.5 \text{ mM}$; 1.0×10^8 cells/ml; $[\text{Fe}^{2+}] = 9 \text{ mM}$ (a-c) or $[\text{Fe}^{2+}] = 0 \text{ mM}$ (d, e). Data points are mean values from duplicate cultures.

Fig. 3 Carbon-fiber-assisted As(III) oxidation/immobilization induced by microbial Fe^{2+} oxidation. Changes in the concentration of Fe^{2+} (a), Fe_{total} (b), As(III) (c), As_{total} (d) and cell density (e) are shown. Carbon-fiber was added at 1% (w/v) in all cases. Cell-free controls (broken lines): Fe^{2+} ($-$), As(III) (Δ), Fe^{2+} plus As(III) ($\circ$), Fe^{3+} plus As(III) ($\square$). Microbial cultures (solid lines): Fe^{2+} ($\square$), As(III) ($\blacktriangle$), Fe^{2+} plus As(III) ($\bullet$), Fe^{3+} plus As(III) ($\blacksquare$). *Am. ferrooxidans* cells were inoculated at 1.0×10^7 cells/ml if media initially contained Fe^{2+} . Otherwise, cells were inoculated at 1.0×10^8 cells/ml, as no cell growth was expected in the absence of Fe^{2+} . Data points are mean values from duplicate cultures.

Fig. 4 Normalized XANES spectra at the Fe K-edge (a) and As K-edge (b) for CF samples collected after the reaction with respective ions (with or without cells) shown in Fig. 3. Standards: $\text{Fe}^{\text{II}}\text{SO}_4 \cdot 7\text{H}_2\text{O}$ (a); $\text{Fe}^{\text{III}}_2\text{O}_3$ (a); $\text{NaAs}^{\text{III}}\text{O}_2$ (b), $\text{KH}_2\text{As}^{\text{V}}\text{O}_4$ (b), chemically synthesized $\text{FeAsO}_4 \cdot 2\text{H}_2\text{O}$ and bacterial cells.

Fig. 5 SEM images of CF before (a) and after (b-e) the As(III) oxidation/immobilization reaction shown in Fig. 3. Microbial cultures: (b) $\text{Fe}^{2+} + \text{As(III)}$, (c) Fe^{2+} only, (d) $\text{Fe}^{3+} + \text{As(III)}$.

Cell-free control: (e) $\text{Fe}^{3+} + \text{As(III)}$.

Fig. 6 Backscattered electron image of a CF section covered with $\text{Fe}^{\text{III}}\text{-As}^{\text{V}}$ precipitates

Cross points 1–3 indicate the beam spot positions for quantitative analysis.

Fig. 7 Dissolution of amorphous $\text{Fe}^{3+}/\text{As(V)}$ -precipitate on CF and its phase transformation into crystalline scorodite. Changes in Fe_{total} (a) and As_{total} (b) concentrations and SEM morphological observation (c) are shown. The arrow on the graph (a) indicates the time 14 h and temperature shift from ambient to 70°C. At 14 h, CFs were pulled-out from the solution and instead, 3% scorodite-seeds were fed ($\blacktriangle$). In control, CFs were left in the solution and no seeds were added ($\times$). The SEM images were taken at 0 h (c-1), 14 h (c-2), and 170 h (c-3, 4), corresponding to the timing indicated on graphs (a) and (b).

Fig. 8 XRD patterns of the final As-precipitates shown in Fig. 7c-3 (a) and Fig. 7c-4 (b). Grey vertical lines are assigned to scorodite (JCPDS 37-0468). The broad peak at around 20-30° (b) derives from CF.

Fig. 9 Proposed flowsheet of carbon-assisted As-remediation process. Fe-oxidizing ability of indigenous acidophilic microbes can be combined with electron-mediating carbon material to induce As(III) oxidation in acidic conditions. On-site semi-passive As-removal can be possible as amorphous $\text{Fe}^{3+}/\text{As(V)}$ -precipitates at lower temperatures as the first step. These precipitates can be further processed off-site (by acid re-solubilization, concentration and re-crystallization) for safer As disposal as scorodite ($\text{Fe}^{\text{III}}\text{As}^{\text{V}}\text{O}_4 \cdot 2\text{H}_2\text{O}$).