

Suppressed hydrogen embrittlement of high-strength Al alloys by Mn-rich intermetallic compound particles

Xu, Yuantao

Department of Mechanical Engineering, Kyushu University

Toda, Hiroyuki

Department of Mechanical Engineering, Kyushu University

Shimizu, Kazuyuki

Department of Physical Science and Materials Engineering, Iwate University

Wang, Yafei

Department of Mechanical Engineering, Kyushu University

他

<https://hdl.handle.net/2324/6792843>

出版情報 : Acta materialia. 236, pp.118110-, 2022-09-01. Elsevier

バージョン :

権利関係 :

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18

Suppressed hydrogen embrittlement of high-strength Al alloys by Mn-rich intermetallic compound particles

3 Yuantao Xu ^{a,b*}, Hiroyuki Toda ^{a*}, Kazuyuki Shimizu ^c, Yafei Wang ^a, Baptiste Gault
4 ^{d,e}, Wei Li ^{b*}, Kyosuke Hirayama ^f, Hiro Fujihara ^a, Xuejun Jin ^b, Akihisa Takeuchi ^g,
5 Masayuki Uesugi ^g

6 ^a*Department of Mechanical Engineering, Kyushu University, Fukuoka 819-0395, Japan*

7 ^b*Shanghai Key Laboratory of Materials Laser Processing and Modification, Shanghai Jiao Tong
8 University, Shanghai 200240, PR China*

9 ^c*Department of Physical Science and Materials Engineering, Iwate University, Morioka 020-8551,
10 Japan*

11 ^d*Max-Planck-Institut für Eisenforschung, Max-Planck-Straße 1, 40237 Düsseldorf, Germany*

12 ^e*Department of Materials, Royal School of Mines, Imperial College, Prince Consort Road,
13 London SW7 2BP, United Kingdom*

14 ^f*Department of Materials Science and Engineering, Kyoto University, Kyoto 606-8501, Japan*

15 ^g*Japan Synchrotron Radiation Research Institute, Hyogo 679-5198, Japan*

16 ^{*}*Corresponding author. Tel.: +81-928023246; E-mail: xu.yuantao.158@m.kyushu-u.ac.jp*

17 *(Yuantao Xu); toda@mech.kyushu-u.ac.jp (Hiroyuki Toda); weilee@sjtu.edu.cn (Wei Li)*

Abstract

19 The pursuit of strong and ductile Al alloys with superior resistance to hydrogen
20 embrittlement (HE) is practically significant across the aerospace and transportation
21 industries among others. Unfortunately, effective ways to progress on the strength-HE
22 trade-off for Al-alloys remain elusive. A strategy of suppressing HE by introducing

23 intermetallic compound (IMC) particles to achieve hydrogen redistribution in various
24 trapping sites was proposed. Here, we systematically induce the precipitation of a
25 constant volume fraction of intermetallic compound (IMC) particles by adding one of
26 14 elements in a ternary Al-Zn-Mg high-strength alloy. We show a strong correlation
27 between hydrogen trapping energies of the IMC obtained from ab initio calculations
28 with the resistance to HE. Mn-rich $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles exhibit the highest hydrogen
29 trapping energy (0.859 eV/atom), leading to a decrease by approximately 5 orders of
30 magnitude in the hydrogen occupancy in η_2 (MgZn_2) phase interfaces and grain
31 boundaries, where HE cracks initiate. The Mn-addition did not deteriorate the
32 ductility and most $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles remained intact during plastic deformation
33 which was revealed by in-situ 3D X-ray tomography. Hydrogen-induced strain
34 localization at η_2 phase interfaces and grain boundaries were inhibited due to strong
35 hydrogen trapping capacity of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$, hence preventing HE cracks initiation.
36 Our approach effectively suppresses hydrogen-induced cracks without sacrificing the
37 ductility, and our strategy can help the design roadmap of HE-tolerant high-strength
38 metallic alloys.

39 Keywords: Hydrogen embrittlement; Hydrogen trapping; Intermetallic compound
40 particles; Aluminum alloys; Ductility

41 **1. Introduction**

42 Degradation of the mechanical properties of structural materials due to hydrogen
43 intake has become the main concern for key components in many industries, such as
44 nuclear energy [1-4], aerospace [5,6], oil and gas [7]. Hydrogen causes cracking [4,5],

45 hydride precipitation [1-3], embrittlement [8], and other harmful effects [9], thereby
46 limiting the service life of parts, increasing operating costs, and creating potentially
47 unsafe working conditions. Al-Zn-Mg alloys have attracted significant research
48 interest for structural applications in aerospace, transportation, and many other
49 industries owing to their high strength and low density [10,11]. However, their low
50 resistance to stress corrosion cracking and hydrogen embrittlement (HE) severely
51 affects the service life and applications [12-14].

52 Environmentally assisted HE in high-strength 7xxx series aluminum alloys leads
53 to low ductility and catastrophic failure in structural applications [11,15,16]. The
54 dissolved hydrogen atoms can easily penetrate surface oxide layer and diffuse into
55 various trapping sites (e.g., dislocations, vacancies, grain boundaries, and precipitates)
56 in the Al alloys [17]. Hydrogen not only reduces the ductility but can also change the
57 fracture mode from ductile to brittle, macroscopically featuring as intergranular or
58 transgranular quasi-cleavage fractures [18-20]. Intergranular fracture (IGF) is
59 primarily associated with the hydrogen segregated at the grain boundary that weakens
60 the interface bonding strength (hydrogen-enhanced decohesion (HEDE) [20]). The
61 mechanisms of quasi-cleavage fracture (QCF) remain controversial due to the lack of
62 direct experimental evidence, for which the HEDE mechanism, hydrogen-enhanced
63 localized plasticity (HELP) [21] mechanism, and hydrogen-accelerated spontaneous
64 microcracking at precipitate interfaces have been proposed [22].

65 The effects of various trapping sites such as micro pores, grain boundaries,
66 dislocations, vacancies, precipitates, and IMC particles on HE mechanism of Al alloys

67 were widely investigated [13,17,22-24]. A high density of micro pores can store
68 hydrogen and contribute to ductile fracture [23]; however, a small amount of
69 dissolved hydrogen can cause brittle fracture [24]. Controlling the distribution of
70 dissolved hydrogen between grain boundaries, dislocations, and vacancies in
71 Al-Zn-Mg alloys was proven ineffective in suppressing HE [17]. The precipitate
72 interfaces (Al-MgZn₂) was reported to be a more preferable hydrogen trap site
73 compared to other defects in terms of binding energy and hydrogen partitioning,
74 which leads to spontaneous hydrogen-accumulated QCF [22]. The design concept of
75 IMC particles primarily focused on their role in grain refinement in Al alloys [25-27],
76 whereas little information was reported regarding their role in the HE suppression of
77 Al alloys. A recent study showed that the Al₇Cu₂Fe particles are effective hydrogen
78 traps to reduce the trapped hydrogen at the precipitate interfaces and confirmed to be
79 able to suppress QCF; however, the improvement of the ductility was not satisfactory
80 due to the brittle nature of Al₇Cu₂Fe particles. Therefore, achieving a superior HE
81 resistance without sacrificing the ductility remains a challenge in Al alloys and
82 exploring suitable IMC particles that can realize the balance between hydrogen
83 trapping ability and brittle nature seems a potential route to effectively control HE.

84 Here, we propose a hydrogen redistribution approach by introducing IMC
85 particles as strong hydrogen trapping site, which significantly reduces trapped
86 hydrogen at precipitate interfaces and grain boundaries and suppresses QCF and IGF
87 originating from hydrogen segregation. First-principles calculations are employed to
88 calculate the binding energies between hydrogen and various IMC particles formed by

89 adding a fourth alloying element to Al-Zn-Mg alloys. The effect of IMC particles on
90 the hydrogen partitioning behaviors among various trap sites during plastic
91 deformation are investigated by 3D X-ray technique and first-principles calculations.
92 In addition, the role of IMC particles in initiation and propagation of
93 hydrogen-induced QCF and IGF are discussed, and the mechanism of how IMC
94 particles can act as strong hydrogen traps for resisting HE is clarified.

95 **2. Materials and methods**

96 To investigate the effects of IMC particles on the hydrogen partitioning and
97 embrittlement behaviors, various IMC particles were formed by adding a fourth
98 element, such as 1.00 Nb, 0.94 Mo, 1.00 V, 0.15 Ca, 0.09 Y, 0.15 Sr, 0.10 Ni, 1.19 Zr,
99 0.15 Fe, 0.26 Cr, 1.02 Ti, 0.19 Co, 0.94 Sc, or 1.91 Mn to the Al-10.0 Zn-1.06 Mg
100 (wt.%) Al alloys. The element content was designed to obtain IMC particles with a
101 volume fraction of approximately 0.28%. The detailed thermomechanical treatment
102 process is presented in Figure S1. The corresponding alloys were prepared by
103 homogenization at 500 °C for 24 h after casting and then hot rolling at 450 °C with a
104 rolling reduction of 50%. A solution-aging process was performed as follows: first, a
105 solution treatment was conducted at 500 °C for 5 h. Subsequently, an over-aging
106 treatment was performed at 120 °C for 40 h and 180 °C for 7 h. To investigate the
107 influence of the pre-charged hydrogen content on the embrittlement behavior,
108 specimens with different hydrogen contents were prepared using LH and HH
109 treatments. The specimens with HH content were charged using electrical discharge
110 machining (EDM) cutting in distilled water, while the specimens with LH content

111 were prepared by EDM cutting in oil. The pre-charged hydrogen contents were
112 approximately 6.97 mass ppm and 1.40 mass ppm for the specimens after HH and LH
113 treatments, respectively, the total hydrogen content was analyzed by the vacuum
114 fusion method, which are similar to literature values [13]. The hydrogen concentration
115 in the Mn-added Al alloys after HH and LH treatments were also measured by thermal
116 desorption apparatus (TDA) method, the corresponding desorption curves were shown
117 in Figure S2.

118 The gauge length of in-situ tensile specimens was 0.7 mm, and these specimens
119 had cross-sectional dimensions of 0.6 mm × 0.6 mm. The deformation and fracture
120 behaviors were observed using high-resolution X-ray tomography during in-situ
121 tensile tests at BL20XU of Spring-8 in Japan; the detailed experimental setup is
122 shown in Figure S3. In-situ tensile tests (strain rate $\sim 3 \times 10^{-3} \text{ s}^{-1}$) were conducted using
123 a DEBEN CT 500 machine at room temperature. 3D images were taken using
124 monochromatic 20 keV X-rays; the detailed methods used for tomography
125 observation and in-situ tensile tests are reported in the literature [13].

126 Transmission electron microscopy (TEM; JEOL JEM 2100F/ARM 200F) was
127 used to characterize the detailed microstructure of the precipitates, IMC particles, and
128 Al matrix. Scanning electron microscope (SEM) (TESCAN MIRA3) equipped with
129 an electron back-scatter diffraction (EBSD) detector was performed to analyze strain
130 distribution and phase features by transmission Kikuchi diffraction (TKD) technique.
131 Thin foils were prepared for TEM and EBSD observations by electro-polishing using
132 Struers (Tenupol-5) equipment at -30 °C and 15 V; the electrolyte was 7% perchloric

133 acid and 93% ethanol. Atom probe tomography (APT) measurements were performed
134 using a local electrode atomic probe (LEAP 4000 HR) to obtain the spatial
135 distribution of elements and the number density and size of nanoparticles. APT data
136 was obtained at 50 K under ultrahigh vacuum (4.5×10^{-11} Torr), a pulse fraction of 0.2,
137 and a repetition rate of 200 kHz. The APT data was reconstructed using IVASTM 3.6.2
138 software.

139 Hydrogen trapping at MgZn₂ precipitates interface and various intermetallic
140 compound particles was calculated using first-principles calculations. The
141 first-principles calculations were conducted within the DFT framework using the
142 Vienna ab initio simulation package (VASP 5.2) with the Perdew-Burke-Ernzerhof
143 generalized gradient approximation exchange-correlation density functional. The
144 Monkhorst-Pack algorithm was selected for the Brillouin-zone k-point samplings. A
145 plane-wave energy cutoff of 360 eV was used with a first-order Methfessel-Paxton
146 smearing scheme, employing a smearing parameter of 0.2 eV. The total energy
147 converged to 10^{-6} eV in all the calculations. The relaxed atomic configurations were
148 obtained by the conjugate gradient method in which the search terminated when the
149 forces on all atoms were below 0.01 eV/Ang. The crystal structure parameters and
150 sampling k-point mesh of various particles, and the details of calculation process can
151 be found in the Supplementary Materials 1.1.

152 The hydrogen trap sites in this study were grain boundaries, dislocations, pores,
153 vacancies, precipitate interfaces, and IMC particles. To quantitatively analyze these
154 trap site densities, the area of the grain boundaries, dislocation densities, pore

155 morphology, vacancy concentrations, area of precipitate interfaces, and volume
156 fractions of IMC particles were obtained using a combination of experimental
157 techniques and mathematical models, which are detailed in the Supplementary
158 Materials 1.2.

159 **3. Results and discussion**

160 *3.1 Trapping energies of IMC particles to hydrogen and their HE resistances*

161 Various IMC particles were formed by adding a fourth element such as Nb, Mo,
162 V, Ca, Y, Sr, Ni, Zr, Fe, Cr, Ti, Co, Sc, or Mn to Al-10.0Zn-1.06Mg alloys.
163 First-principles density functional theory (DFT) was employed to calculate the
164 trapping energies of various IMC particles to hydrogen, and the corresponding results
165 are shown in Figure 1. The hydrogen trapping energies of various defect structures,
166 such as edge/screw dislocations [28], grain boundaries [29], vacancies [30],
167 precipitates [22,31], and micro pores [32] are also summarized. The maximum
168 hydrogen trapping energy in the interior of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ was 0.859 eV/atom, much
169 higher than that in other IMC particles and defect structures, which indicates that it
170 can be used as a strong hydrogen trapping site for absorbing a large amount of
171 hydrogen at interstitial sites.

172 The HE resistances of samples with and without IMC particles were evaluated
173 using in-situ tensile tests. In-situ tensile stress–displacement curves for the
174 standard-state, Sc-added, and Mn-added Al alloys after low-hydrogen (LH) and
175 high-hydrogen (HH) treatments are shown in Figure 2(a). The mechanical properties
176 of the standard-state and Sc-added Al alloys were severely affected by the hydrogen

177 content, where the elongation were dramatically reduced after the HH treatment,
178 compared to the LH treatment. However, in the Mn-added alloys, the elongation
179 remained almost unchanged after the HH treatment, compared to the LH treatment,
180 which means that the Mn-added Al alloys overcomes hydrogen-induced ductility loss.
181 Detailed fractography analysis revealed that the fractional areas of IGF and QCF were
182 50.9% and 46.0% in the standard-state Al alloys and 9.3% and 11.5% for the
183 Mn-added Al alloys after the HH treatment, with 81.7% and 75.0% reduction,
184 respectively. This confirms that the Mn-added Al alloys significantly improves HE
185 resistance (Figure 2(b)). The effect of a fourth element such as Nb, Mo, V, Ca, Y, Sr,
186 Ni, Zr, Fe, Cr, Ti, Co, Sc, or Mn on the HE fracture area is shown in Figure 2(c); the
187 corresponding fracture morphology is presented in Figure 3 and Figure S4. The
188 relationships between hydrogen trapping energies of IMC particles and fractional
189 areas of QCF are summarized in Figure 2(d). Fractional areas of QCF were
190 significantly reduced with the increase of trapping energies of different IMC particles
191 in the Al alloys treated by HH. Compared with the addition of the other elements, the
192 Mn-added Al alloys exhibited the best HE resistance owing to the highest trapping
193 energy between the $Al_{11}Mn_3Zn_2$ particles and hydrogen.

194 HE occurred in the 7 xxx series Al alloy (Al-10.1Zn-1.2Mg) with hydrogen
195 content of 0.41 mass ppm [12], and also appeared in LH-treated standard-state Al
196 alloys (1.40 mass ppm) in this work (Figure 3). It was reported that the introduction of
197 Mn-rich particles by adding Mn to Al-Zn-Mg alloys under hydrogen-free conditions
198 results in a slight decrease in ductility [33,34]. However, the introduced Mn-rich

199 particles in LH-treated Mn-added Al alloys contributes to a significant increase in
200 ductility compared with LH-treated standard-state Al alloys, which reconfirms that
201 strong hydrogen trapping capacity of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles.

202 *3.2 Hydrogen partitioning behavior*

203 The microstructures of the standard-state and Mn-added Al-Zn-Mg alloys were
204 investigated (Figure 4(a-b)). The standard-state alloys primarily consisted of MgZn_2
205 and Al matrix, while the Mn-added Al alloys was primarily comprised of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$,
206 MgZn_2 , and Al matrix (Figure 4(a-b), Figure S5, and Figure 5), which were identified
207 using high-resolution transmission electron microscopy (HRTEM) and atom probe
208 tomography (APT) analysis. MgZn_2 has a hexagonal close-packed (hcp) structure, and
209 its edge and side surfaces of the plate are coherent and semi-coherent along the
210 $[112]_{\text{Al}}$ zone axis, respectively. The orientation relationship between MgZn_2 and the
211 matrix is $[\bar{1}12]_{\text{Al}} // [2\bar{1}10]_{\text{MgZn}_2}$. $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ has an orthorhombic structure; the
212 orientation relationship between it and the matrix is $[011]_{\text{Al}} // [2\bar{2}1]_{\text{Al}_{11}\text{Mn}_3\text{Zn}_2}$. The
213 number density of η_2 (MgZn_2) precipitates in standard-state and Mn-added Al alloys
214 are 1.13×10^{23} and $0.78 \times 10^{23} \text{ m}^{-3}$, and their equivalent spherical particle radius are 6.5
215 and 7.4 nm, respectively, which were determined via APT (Figure 5). The average
216 grain sizes were measured to be 124 and 75 μm for the standard-state and Mn-added
217 Al alloys, respectively (Figure 6). 3D perspective views of IMC particles and micro
218 pores obtained by high-resolution X-ray tomography are shown in Figure 4(c). These
219 parameters were used in the calculation of hydrogen occupancy of the corresponding
220 trap site.

221 The hydrogen partitioning behavior in the standard-state and Mn-added Al alloys
222 are shown in Figure 4(d). The hydrogen occupancy of a trap site depends on both the
223 trap density and trap binding energy, which were derived from experimental results
224 (Figure 4(a)-4(c)) and first-principles calculations. See the Supplementary Materials
225 1.2 for detailed calculation procedures of hydrogen occupancy of each hydrogen trap
226 site.

227 It was found that hydrogen atoms were mainly trapped at micro pores, η_2
228 precipitates, and vacancies in the standard-state alloys; however, the $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$
229 particles are the strongest hydrogen trap, which reduced the hydrogen occupancy at
230 other trap sites such as micro pores, η_2 precipitates, vacancies, and grain boundaries.
231 In particular, the hydrogen occupancy of η_2 interfaces and grain boundaries were
232 decreased by approximately 5 orders of magnitude (from 1.15×10^{-1} to 6.20×10^{-7} and
233 from 4.42×10^{-1} to 4.60×10^{-6} atomH/site, respectively), which contributes to the
234 suppression of hydrogen-induced QCF and IGF (Figure 2).

235 *3.3 Damage behavior of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles and hydrogen partitioning behavior* 236 *during deformation*

237 Figure 7(a)-7(h) show the damage behavior of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles in Mn-added
238 Al alloys after the HH treatment during in-situ tensile tests. 3D images around the
239 crack tip were obtained using high-resolution X-ray tomography. The observation
240 regions ahead of the hydrogen-induced quasi-cleavage crack tip and near the crack
241 ridge were approximately 5.7×10^2 and $4.3 \times 10^3 \mu\text{m}^3$, respectively, as shown in Figure
242 7(i). Particle debonding and fracture at different steps were classified by analyzing the

243 voids and their neighboring particles: debonding was confirmed if only one particle
244 was found adjacent to one void; however, particle fracture was identified if two
245 particles were connected to one void.

246 The damage ratios, R_d , are defined as follows:

$$247 \quad R_d(\text{fractured}) = n_F / n_{total} \times 100\% \quad (1)$$

$$248 \quad R_d(\text{debonded}) = n_D / n_{total} \times 100\% \quad (2)$$

$$249 \quad R_d = R_d(\text{fractured}) + R_d(\text{debonded}) \quad (3)$$

250 where n_F and n_D are the numbers of fractured and debonded particles,
251 respectively; n_{total} is the total number of IMC particles for each condition.

252 At a macroscopic tensile strain of 5.7%, the damage ratio of IMC particles near
253 the crack ridge was approximately 7% (2/28). With the further increase of tensile
254 strain to 9%, the damage ratio slightly increased to approximately 20% (2/10).
255 Therefore, most of these IMC particles remained intact during plastic deformation,
256 implying that these particles, with strong hydrogen trapping capacity, did not
257 deteriorate the ductility due to good damage resistance. It is thereby expected that the
258 IMC particles can effectively suppress hydrogen-induced cracks without sacrificing
259 the ductility. This is consistent with the significantly increased fracture strain of the
260 particles-containing Al alloys compared with the particles-free Al alloys (Figure 2(a)).

261 Figure 7(i) and 7(j) show the hydrogen partitioning behavior during deformation
262 in Mn-added Al alloys after the HH treatment. At the in-situ tensile strain of 3.6%, the
263 volume fractions of IMC particles at the regions ahead of the hydrogen-induced
264 quasi-cleavage crack tip and near the crack ridge were 1.54% and 0.26%, respectively.

265 Hydrogen partitioning calculations revealed that the hydrogen occupancy of the η_2
266 interfaces at the region ahead of the crack tip was approximately 8 orders of
267 magnitude lower than that near the crack ridge owing to the higher density of IMC
268 particles. This means that regions with a low density of IMC particles are prone to
269 crack nucleation and propagation (Figure 7(i)). $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles were the main
270 hydrogen trap, and the trapped hydrogen content could reach $2.0 \times 10^{25} \text{ atomH} \cdot \text{m}^{-3}$
271 (Figure S6), which was much higher than other trapping sites. The hydrogen
272 occupancy of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles remained almost unchanged before and after
273 deformation (3.6% strain). Moreover, they exhibited good damage resistance even at
274 high tensile strain (up to 9%). This confirms that the $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles are
275 beneficial for improving the HE resistance without harming the ductility during
276 deformation.

277 *3.4 Suppression of hydrogen-induced strain localization at grain boundaries*

278 Micro-deformation mechanisms of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles under HH and LH
279 conditions were revealed by transmission Kikuchi diffraction (TKD) technique and
280 TEM (Figure 8). $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles did not deform during tensile failure under HH
281 and LH conditions, strain concentration around $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles mainly resulted
282 from dislocations piled-up. The strain distributions around $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ and in Al
283 matrix remained almost the same when changing treatment conditions from LH to HH,
284 indicating that hydrogen-induced strain localization caused by the interaction of
285 hydrogen and dislocations was suppressed [13,35-37], which is mainly attributed to
286 strong hydrogen trapping capacity of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$.

287 The microstructures near the fracture surfaces of Mn-added and standard-state Al
288 alloys treated by HH after tensile failure are shown in Figure 9. The
289 hydrogen-induced cracks mainly propagated along the grain interiors in the Mn-added
290 Al alloys (Figure 9(a)), while they mainly propagated along the grain boundaries in
291 the standard-state Al alloys (Figure 9(e)). Hydrogen-induced cracks preferably
292 nucleated at IMC-poor regions, and IMC-rich regions could effectively blunt and
293 suppress hydrogen-induced cracks (Figure S7), which is consistent with the result at
294 3.6% tensile strain (Figures 7(i) and 7(j)). The piled-up dislocations at grain
295 boundaries were significantly reduced during tensile failure after adding Mn in
296 standard-state Al alloys (Figure 9(b)-(d) and 9(f)-(h)), supporting that the trapped
297 hydrogen at grain boundaries were remarkably decreased owing to the introduction of
298 $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$.

299 *3.5 Suppression of hydrogen-induced strain localization at η_2 phase interfaces*

300 As shown in Figure 10, strain maps were plotted by geometric phase analysis
301 (GPA) [38], inverse FFT patterns of HRTEM images were used to characterize
302 dislocations around η_2 phase interfaces. 10 HRTEM images (each image contains 2
303 precipitates) were collected for the HH-treated Mn-added Al alloys and HH-treated
304 standard-state Al alloys, respectively, and 20 precipitates were counted and analyzed
305 for each condition. Strain concentration around η_2 phase interfaces was not very
306 obvious in HH-treated Mn-added Al alloys subjected to tensile failure, however, the
307 strain values were very high for almost the entire η_2 phase interface in HH-treated
308 standard-state Al alloys subjected to tensile failure (Figure 10(c)-(f) and 10(j)-(m)).

309 Moreover, more significant dislocations pile up occurred near the η_2 phase interfaces
310 in HH-treated standard-state Al alloys, compared with that in HH-treated Mn-added
311 Al alloys (Figure 10(g) and 10(n)). Based on the analysis results of 20 precipitates
312 under each condition, it can be confirmed that the strain localization at η_2 phase
313 interfaces was effectively suppressed during tensile failure after adding Mn in
314 standard-state Al alloys, which indicates that the trapped hydrogen at η_2 phase
315 interfaces were largely removed by $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$. These results demonstrate that IMC
316 particles inhibit hydrogen-induced strain localization η_2 phase interfaces by
317 consuming most of the hydrogen, hence preventing HE cracks initiation.

318 The QCF mechanism induced by hydrogen in structural materials, such as ferritic,
319 martensitic, and austenitic steels, and nickel, can be explained by the HELP model
320 [39], where hydrogen-affected dislocations contribute to structural failure. However, a
321 QCF mechanism assisted by hydrogen in an Al-Mg-Zn alloy was reported [22];
322 hydrogen atoms tended to be trapped at the interfaces rather than at grain boundaries
323 and dislocations owing to the higher binding energy with hydrogen, which induced
324 hydrogen-accelerated spontaneous microcracking at aluminum-precipitate interfaces.
325 In this work, a similar fracture mechanism caused by precipitate interfaces decohesion
326 can also be used to explain the QCF. The hydrogen occupancy of the η_2 coherent
327 interface decreased from 8.4×10^{-10} in the unloaded state to 8.7×10^{-11} atomH/site at
328 3.6% in-situ tensile strain (the corresponding hydrogen concentration is 5.3×10^{-10}
329 atomH/nm²; the hydrogen trap interval for a coherent η precipitate interface is 6.1
330 atomH/nm², assuming that the hydrogen occupancy is equal to one [17,31]). The

331 hydrogen occupancy of the η_2 semi-coherent interface decreased from 1.84×10^{-5}
332 atomH/site in the unloaded state to 1.9×10^{-6} atomH/site (1.2×10^{-5} atomH/nm²). The
333 interfacial decohesion of η_2 precipitates initiates when the trapped hydrogen density
334 reaches 18.9 atomH/nm² [13,17], which is approximately 3.6×10^{10} and 1.6×10^6 times
335 higher than the hydrogen concentration at the coherent and semi-coherent interfaces
336 of η_2 precipitates in the Mn-added Al alloys, respectively. Moreover, it was observed
337 that hydrogen-induced strain localization at η_2 phase interfaces was suppressed after
338 adding Mn in standard-state Al alloys (Figure 10). As a result, the fractional areas of
339 QCF originating from the hydrogen-induced decohesion of precipitate interfaces was
340 remarkably reduced (Figure 2(b)).

341 Hydrogen trapped at grain boundaries decreases the cohesion strength of the
342 boundaries (HEDE model) and results in IGF, which is a common HE mechanism in
343 structural materials. The critical hydrogen concentration at the grain boundaries for
344 the initiation of intergranular cracks is approximately 2.8×10^{22} atomH·m⁻³ in
345 Al-Zn-Mg-Cu alloys [30]. The hydrogen content trapped at the grain boundaries in
346 Mn-added Al alloys in the unloaded and 3.6% tensile strain states were 4.04×10^{12} and
347 4.19×10^{11} atomH·m⁻³, respectively, which are much lower than the critical value
348 required for hydrogen-induced intergranular cracking. In addition, it was found that
349 hydrogen-induced strain localization at grain boundaries was inhibited after adding
350 Mn in standard-state Al alloys (Figure 9). Therefore, this is the main reason for the
351 significant reduction in the fractional areas of IGF (Figure 2(b)).

352 Hydrogen-induced strain localization at grain boundaries and η_2 phase interfaces

353 were suppressed due to strong hydrogen trapping capacity of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$, which
354 could remove hydrogen from the grain boundaries and η_2 phase interfaces. Therefore,
355 the Al alloys with Mn-rich particles exhibited the superior HE resistance by
356 eliminating 75.0% and 81.7% of hydrogen-induced QCF and IGF, respectively, and
357 suppressing hydrogen-induced ductility loss compared to the standard-state Al alloys.
358 Moreover, in terms of HE sensitivity ($El_{loss} = (El_{LH} - El_{HH})/El_{LH} \times 100\%$, El_{LH} and El_{HH}
359 are fracture elongations of LH and HH-treated specimens, respectively), the Al alloys
360 with Mn-rich particles showed lack of HE sensitivity, which indicates that most of the
361 hydrogen is occupied by Mn-rich particles and does not deteriorate the mechanical
362 properties.

363 IMC particles are often used to inhibit recrystallization during solution heat
364 treatment; however, they are detrimental to the mechanical properties of structural
365 materials, especially the ductility [40]. Although IMC particles such as $\text{Al}_7\text{Cu}_2\text{Fe}$ have
366 been proven to improve the HE resistance due to hydrogen trapping effect, this still
367 cannot solve the problem of ductility deterioration [13].

368 In this work, we proposed a strategy of suppressing HE by introducing IMC
369 particles to achieve hydrogen redistribution in various trapping sites, rather than
370 eliminating the hydrogen. IMC particles with HH trapping energies were designed
371 using first-principles calculations; Mn-rich $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles exhibit the highest
372 hydrogen trapping energy (0.859 eV/atom), leading to a decrease by approximately 5
373 orders of magnitude in the hydrogen occupancy in η_2 (MgZn_2) phase interfaces and
374 grain boundaries, where HE cracks initiate. Most $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles remained

375 intact during plastic deformation and exhibited good damage resistance.
376 Hydrogen-induced strain localization at grain boundaries and η_2 phase interfaces were
377 suppressed due to strong hydrogen trapping capacity of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$, hence preventing
378 HE cracks initiation. Superior HE resistance without sacrificing the ductility was
379 achieved through this hydrogen redistribution approach, which can also be applied to
380 a variety of high-strength structural materials containing IMC particles, such as iron,
381 titanium, and zirconium-based alloys.

382 **4. Conclusions**

383 We systematically induce the precipitation of a constant volume fraction of
384 intermetallic compound (IMC) particles by adding one of 14 elements in a ternary
385 Al-Zn-Mg high-strength alloy, the effect of IMC particles on HE resistances and HE
386 mechanisms were investigated. The main conclusions are as follows:

387 (1) A strong correlation between hydrogen trapping energies of the IMC obtained
388 from ab initio calculations with the resistance to HE was confirmed. The $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$
389 particles had a trapping energy value (0.859 eV/atom) that was much higher than that
390 of all known hydrogen trap sites, which caused the hydrogen occupancy at other trap
391 sites such as micro pores, η_2 precipitates, vacancies, and grain boundaries to be
392 significantly reduced. In particular, the hydrogen occupancy of η_2 interfaces and grain
393 boundaries were decreased by approximately 5 orders of magnitude compared to the
394 standard-state Al alloys (from 1.15×10^{-1} to 6.20×10^{-7} and from 4.42×10^{-1} to 4.60×10^{-6}
395 atomH/site, respectively).

396 (2) Hydrogen occupancy and damage ratio of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles changed

397 slightly when the tensile strain reached 3.6% and 9% after HH treatment (6.97 ppmw
398 H), respectively, suggesting that they did not deteriorate the ductility. In addition,
399 hydrogen-induced strain localization at grain boundaries and η_2 phase interfaces were
400 suppressed due to strong hydrogen trapping capacity of $Al_{11}Mn_3Zn_2$, hence preventing
401 HE cracks initiation. Therefore, the Al alloys with Mn-rich particles exhibited the
402 superior HE resistance by eliminating 75.0% and 81.7% of hydrogen-induced QCF
403 and IGF, respectively, and suppressing hydrogen-induced ductility loss compared to
404 the standard-state Al alloys.

405 **References**

- 406 [1] A. T. Motta, et al., Hydrogen in zirconium alloys: A review, *J. Nucl. Mater.* 518 (2019)
407 440-460.
- 408 [2] S. Sobieszczyk, Hydrogen-enhanced degradation and oxide effects in zirconium alloys for
409 nuclear applications, *Int. J. Hydrogen Energy* 6 (2011) 8619-8629.
- 410 [3] S. Suman, M. K. Khan, M. Pathak, R. N. Singh & J. K. Chakravarty, Hydrogen in Zircaloy:
411 Mechanism and its impacts, *Int. J. Hydrogen Energy* 40 (2015) 5976-5994.
- 412 [4] M. Shahzad, H. Qureshi, H. Waqas & N. Hussain, A case study of environmental assisted
413 cracking in a low alloy steel under simulated environment of pressurized water reactor,
414 *Mater. Des.* 32 (2011) 5154-5158.
- 415 [5] M. P. Brady, et al., Rapid diffusion and nanosegregation of hydrogen in magnesium alloys
416 from exposure to water, *ACS Appl. Mater. Interfaces.* 9 (2017) 38125-38134.
- 417 [6] A. S. H. Kabir, et al., Effect of post-weld heat treatment on microstructure, hardness, and
418 tensile properties of laser-welded Ti-6Al-4V, *Metall. Mater. Trans. A* 43 (2012) 4171-4184.
- 419 [7] Z. Tarzimoghadam, et al., Multi-scale and spatially resolved hydrogen mapping in a Ni-Nb
420 model alloy reveals the role of the δ phase in hydrogen embrittlement of alloy 718, *Acta*
421 *Mater.* 109 (2016) 69-81.
- 422 [8] G. McMahon, B. D. Miller & M. G. Burke, High resolution NanoSIMS imaging of
423 deuterium distributions in 316 stainless steel specimens after fatigue testing in high pressure

- 424 deuterium environment, *Npj Mater. Degrad.* 2 (2018) 1-6.
- 425 [9] I. I. Chernov, M. S. Staltsov & B. A. Kalin, Some problems of hydrogen in reactor structural
426 materials: A review, *Inorg. Mater. Appl. Res.* 8 (2017) 643-650.
- 427 [10] A. Heinz, A. Haszler, C. Keidel, et al., Recent development in aluminium alloys for
428 aerospace applications, *Mater. Sci. Eng. A* 280 (2000) 102-107.
- 429 [11] J. C. Williams, Jr. E. A. Starke, Progress in structural materials for aerospace systems. *Acta*
430 *Mater.* 51 (2003) 5775-5799.
- 431 [12] K. Shimizu, H. Toda, K. Uesugi, A. Takeuchi, Local deformation and fracture behavior of
432 high-strength aluminum alloys under hydrogen influence, *Metall. Mater. Trans. A* 51 (2020)
433 1-19.
- 434 [13] H. Su, H. Toda, K. Shimizu, et al., Assessment of hydrogen embrittlement via image-based
435 techniques in Al-Zn-Mg-Cu aluminum alloys, *Acta Mater.* 176 (2019) 96-108.
- 436 [14] H. Toda, T. Hidaka, M. Kobayashi, et al., Growth behavior of hydrogen micropores in
437 aluminum alloys during high-temperature exposure, *Acta Mater.* 57 (2009) 2277-2290.
- 438 [15] S. K. Dwivedi, M. Vishwakarma, Hydrogen embrittlement in different materials: a review,
439 *Int. J. Hydrogen Energy* 43 (2018) 21603-21616.
- 440 [16] J. T. Burns, S. Kim, R. P. Gangloff, Effect of corrosion severity on fatigue evolution in
441 Al-Zn-Mg-Cu, *Corros. Sci.* 52 (2010) 498-508.
- 442 [17] K. Shimizu, H. Toda, H. Fujihara, et al., Hydrogen partitioning behavior and related
443 hydrogen embrittlement in Al-Zn-Mg alloys, *Eng. Fract. Mech.* 216 (2019) 106503.
- 444 [18] M. L. Martin, B. P. Somerday, R. O. Ritchie, et al., Hydrogen-induced intergranular failure
445 in nickel revisited, *Acta Mater.* 60 (2012) 2739-2745.
- 446 [19] Z. Zhang, G. Obasi, R. Morana, et al., Hydrogen assisted crack initiation and propagation in
447 a nickel-based superalloy, *Acta Mater.* 113 (2016) 272-283.
- 448 [20] W. W. Gerberich, R. A. Oriani, M. J. Lji, et al., The necessity of both plasticity and
449 brittleness in the fracture thresholds of iron, *Philosophical Magazine A* 63 (1991) 363-376.
- 450 [21] H. K. Birnbaum, P. Sofronis, Hydrogen-enhanced localized plasticity-a mechanism for
451 hydrogen-related fracture, *Mater. Sci. Eng. A* 176 (1994) 191-202.
- 452 [22] T. Tsuru, K. Shimizu, M. Yamaguchi, et al., Hydrogen-accelerated spontaneous
453 microcracking in high-strength aluminium alloys, *Scientific Reports* 10 (2020) 1-8.

- 454 [23] H. Toda, H. Oogo, K. Uesugi, M. Kobayashi, Roles of pre-existing hydrogen micropores on
455 ductile fracture, *Mater. Trans.* 50 (2009) 2285-2290.
- 456 [24] M. S. Bhuiyan, et al., Influences of hydrogen on deformation and fracture behaviors of high
457 Zn 7XXX aluminium alloys, *Int. J. Fract.* 200 (2016) 13-29.
- 458 [25] I. Nikulin, A. Kipelova, S. Malopheyev, et al., Effect of second phase particles on grain
459 refinement during equal-channel angular pressing of an Al-Mg-Mn alloy, *Acta Mater.* 60
460 (2012) 487-497.
- 461 [26] R. Hu, T. Ogura, H. Tezuka, et al., Dispersoid formation and recrystallization behavior in an
462 Al-Mg-Si-Mn alloy, *J. Mater. Sci. Technol.* 26 (2010) 237-243.
- 463 [27] Y. B. Kim, Y. H. Chung, K. K. Cho, et al., Recrystallization behavior of
464 Al-2Li-3Mg-1Cu-0.12Zr-XMn (X= 0, 0.5) alloy, *Scr. Mater.* 36 (1997).
- 465 [28] M. Itakura, M. Yamguchi, K. Ebihara, K. Matsuda, H. Toda, First-principles calculations of
466 hydrogen trapping energy at screw and edge dislocations of aluminum [In preparation].
- 467 [29] T. Tsuru, M. Yamaguchi, K. Ebihara, et al., First-principles study of hydrogen segregation at
468 the MgZn₂ precipitate in Al-Mg-Zn alloys, *Comput. Mater. Sci.* 148 (2018) 301-306.
- 469 [30] L. Ismer, M. S. Park, A. Janotti, et al., Interactions between hydrogen impurities and
470 vacancies in Mg and Al: A comparative analysis based on density functional theory, *Phys.*
471 *Rev. B* 81 (2010) 139902.
- 472 [31] T. Tsuru, M. Yamaguchi, K. Ebihara, et al., First-principles study of hydrogen segregation at
473 the MgZn₂ precipitate in Al-Mg-Zn alloys, *Comput. Mater. Sci.* 148 (2018) 301-306.
- 474 [32] M. Yamaguchi, T. Tsuru, K. Ebihara, et al., Surface energy reduction by dissociative
475 hydrogen adsorption on inner surface of pore in aluminum, *J. Jpn. Inst. Light Met.* 68 (2018)
476 588-595.
- 477 [33] D. S. Park, S. W. Nam, Effects of manganese dispersoid on the mechanical properties in
478 Al-Zn-Mg alloys, *J. Mater. Sci.* 30 (1995) 1313-1320.
- 479 [34] D. H. Lee, J. H. Park, S. W. Nam, Enhancement of mechanical properties of Al-Mg-Si alloys
480 by means of manganese dispersoids, *Mater. Sci. Tech.* 15 (1999) 450-455.
- 481 [35] Y. Liang, P. Sofronis, N. Aravas, On the effect of hydrogen on plastic instabilities in metals,
482 *Acta Mater.* 51(2003) 2717-2730.
- 483 [36] M. Dadfarnia, A. Nagao, S. Wang, et al., Recent advances on hydrogen embrittlement of

- 484 structural materials, *Int. J. Fracture* 196 (2015) 223-243.
- 485 [37] I. M. Robertson, P. Sofronis, A. Nagao, et al., Hydrogen embrittlement understood, *Metall.*
486 *Mater. Trans. A* 46 (2015) 2323-2341.
- 487 [38] M. J. Hÿtch, E. Snoeck, R. Kilaas, Quantitative measurement of displacement and strain
488 fields from HREM micrographs, *Ultramicroscopy* 74 (1998) 131-146.
- 489 [39] M. L. Martin, M. Dadfarnia, A. Nagao, et al., Enumeration of the hydrogen-enhanced
490 localized plasticity mechanism for hydrogen embrittlement in structural materials, *Acta*
491 *Mater.* 165 (2019) 734-750.
- 492 [40] Q. G. Wang, C. H. Caceres, J. R. Griffiths, Damage by eutectic particle cracking in
493 aluminum casting alloys A356/357, *Metall. Mater. Trans. A* 34 (2003) 2901-2912.

494 **Acknowledgments**

495 This work was supported by JST, CREST Grant Number JPMJCR 1995 Japan and JSPS
496 KAKENH Grant Number JP21H04624. The synchrotron radiation experiments were performed at
497 SPring-8 with the approval of Japan Synchrotron Radiation Research Institute through proposal
498 number 2020A1796/1084.

499 **Additional information**

500 The authors declare no competing financial interests. Correspondence and requests for
501 materials should be addressed to Prof. Toda.

502 **Data availability**

503 The data that support the findings of this study are available from the corresponding author
504 upon request.

505 **Figure Captions**

506 **Figure 1 Excellent trapping energies of IMC particles to hydrogen.** The trapping energies of
507 various intermetallic compound particles to hydrogen were calculated by first-principles density
508 functional theory (DFT). The hydrogen trapping energies of various defect structures, such as
509 dislocations [28], grain boundaries [29], vacancies [30], precipitates [22,31], and micro pores [32],

510 were derived from references. $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ shows advantages in hydrogen trapping compared to
511 other IMC particles and defect structures.

512 **Figure 2 Superior HE resistance results from introducing IMC particles. a,**
513 Stress-displacement curves for standard-state, Sc-added and Mn-added Al alloys after
514 low-hydrogen (LH) and high-hydrogen (HH) treatments, Mn-added Al alloys exhibited a superior
515 HE resistance without sacrificing the ductility after HH treatment. **b,** Fracture morphology of
516 standard-state and Mn-added Al alloys after HH treatment, suppressing hydrogen-induced QCF
517 and IGF by introducing IMC particles was achieved. **c,** Fractional areas of QCF and IGF for
518 standard-state, Nb-added, Mo-added, V-added, Ca-added, Y-added, Sr-added, Ni-added, Zr-added,
519 Fe-added, Cr-added, Ti-added, Co-added, Sc-added and Mn-added Al alloys under HH treatments.
520 **d,** The relationships between the added elements, maximum trapping energies and fractional areas
521 of QCF fracture are summarized, the higher trapping energy with hydrogen, the lower fractional
522 area of QCF, which indicates that QCF was effectively suppressed by introducing IMC particles,
523 especially the IMC particles formed by adding Mn.

524 **Figure 3 Fracture surfaces after preliminary tensile tests of HH and LH specimens. a,**
525 Standard state, Sc-added and Mn-added Al alloys after HH treatments. **b,** Standard state, Sc-added
526 and Mn-added Al alloys after LH treatments.

527 **Figure 4 Hydrogen redistribution driven by IMC particles. a, b,** Distribution and crystal
528 structure of MgZn_2 precipitates and $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles in Mn-added Al alloys observed by
529 HRTEM. **c,** 3D perspective views of IMC particles and micro pores obtained by high-resolution
530 X-ray tomography in Zr-added and Mn-added Al alloys. **d,** Hydrogen trapping occupancy before
531 and after adding Mn/Zr elements derived from thermodynamic equilibrium condition and
532 first-principles calculations, the formed $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles after Mn addition caused hydrogen
533 occupancy of the η_2 interfaces and grain boundaries to decrease by approximately 5 orders of
534 magnitude compared to that of the standard-state Al alloys.

535 **Figure 5 APT results. a,** Mn-added Al alloys. **b,** Standard-state Al alloys.

536 **Figure 6 EBSD results. a,** Standard-state Al alloys. **b,** Mn-added Al alloys.

537 **Figure 7 Damage behavior of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles and hydrogen partitioning behavior**
538 **during deformation after HH treatment. a-d,** CT images of the Mn-added Al alloys at each
539 nominal strain on a x-z virtual cross section. **e, f,** Corresponding to the partial enlarged view in **a**

540 and **b, g, h**, 3D imaging around crack tip in Zernike imaging in Mn-added Al alloys. **i**, Hydrogen
541 partitioning calculations for the regions ahead of hydrogen-induced quasi-cleavage crack tip and
542 near the crack ridge in Mn-added Al alloys under the in-situ tensile strain of 3.6%. **j**, Hydrogen
543 partitioning behavior among lattice, vacancies, dislocations, grain boundaries, IMC particles, η_2
544 precipitates and micro pores in Mn-added Al alloys before and after loading.

545 **Figure 8 Micro-deformation mechanisms of $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles under HH and LH**
546 **conditions. a**, Phase, KAM and TEM images of Mn-added Al alloys before tensile deformation,
547 TEM image was taken from 011 crystal zone axis of Al matrix. **b**, Phase, KAM and TEM images
548 taken from the crack tip region of HH-treated Mn-added Al alloys after tensile failure, strain
549 concentration around $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles mainly resulted from dislocations piled-up. **c**, Phase,
550 KAM and TEM images taken from the crack tip region of LH-treated Mn-added Al alloys after
551 tensile failure. **d**, KAM distributions in Al matrix and $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$ particles of HH/LH-treated
552 Mn-added Al alloys before and after tensile failure. The strain distributions around $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$
553 and in Al matrix remained almost unaffected when changing treatment conditions from LH to HH.

554 **Figure 9 Suppression of hydrogen-induced dislocations piled-up at grain boundaries by**
555 **$\text{Al}_{11}\text{Mn}_3\text{Zn}_2$. a, e**, Microstructures near the fracture surfaces of Mn-added and standard-state Al
556 alloys treated by HH after tensile failure, respectively. The cracks mainly propagated along the
557 grain interiors in Mn-added Al alloys, while they mainly propagated along the grain boundaries in
558 standard-state Al alloys. **b**, TEM BF image cut from area **b** in **a**. **c, d**, TEM BF and DF images
559 corresponding to the area **c** in **b**. **f**, TEM BF image cut from area **f** in **e**. **g, h**, TEM BF and DF
560 images corresponding to the area **g** in **f**. The piled-up dislocations at grain boundaries were
561 significantly reduced during tensile failure after adding Mn in standard-state Al alloys, indicating
562 that hydrogen-induced strain localization at grain boundaries was suppressed by $\text{Al}_{11}\text{Mn}_3\text{Zn}_2$
563 particles.

564 **Figure 10 Suppression of hydrogen-induced strain localization at η_2 phase interfaces by**
565 **$\text{Al}_{11}\text{Mn}_3\text{Zn}_2$. a, h**, Microstructures near the fracture surfaces of Mn-added and standard-state Al
566 alloys treated by HH after tensile failure, respectively. **b**, TEM BF image cut from area **b** in **a**. **c, d**
567 HRTEM images corresponding to the area **c** and **d** in **b**. **e, f**, Corresponding strain maps of
568 geometric phase analysis (GPA) (in-plane rigid-body rotation, ω_{xy}) for HRTEM images **c** and **d**,

569 respectively. **g**, Inverse FFT and FFT patterns corresponding to HRTEM image **c**, inverse FFT
570 pattern derives from $(\bar{1}\bar{1}\bar{1})$ reflection. **i**, TEM BF image cut from area **i** in **h**. **j**, **k**, HRTEM images
571 corresponding to the area **j** and **k** in **i**. **l**, **m**, Corresponding strain maps of geometric phase analysis
572 (GPA) (in-plane rigid-body rotation, ω_{xy}) for HRTEM images **j** and **k**, respectively. **n**, inverse
573 FFT and FFT patterns corresponding to HRTEM image **j**. Strain maps were plotted with respect to
574 an internal reference lattice by $g_1 = (11\bar{1})_{matrix}$ and $g_2 = (200)_{matrix}$. Dislocations mainly
575 bypassed η_2 precipitates in Mn-added and standard-state Al alloys treated by HH. Density of edge
576 dislocations around the η_2 phase interfaces in Mn-added Al alloys is significantly lower than that
577 in standard-state Al alloys after tensile failure, moreover, the results of the strain distributions
578 originating from strain maps are also similar to that. The strain localization at η_2 phase interfaces
579 was effectively inhibited during tensile failure after adding Mn in standard-state Al alloys.

580 **Extended Data Figure S1 Schematic diagrams of the thermomechanical treatment process. a**,
581 High-hydrogen treatment. **b**, Low-hydrogen treatment.

582 **Extended Data Figure S2 Desorption curves of the Mn-added Al alloys after HH and LH**
583 **treatments.**

584 **Extended Data Figure S3 Experimental setup for the imaging X-ray microtomography. a**,
585 Schematic diagram. **b**, A pneumatic material test rig specially designed for X-ray
586 micro-tomography at the synchrotron radiation facility.

587 **Extended Data Figure S4 Fracture surfaces after preliminary tensile tests of HH specimens.**
588 Nb-added, Mo-added, V-added, Ca-added, Y-added, Sr-added, Ni-added, Zr-added, Fe-added,
589 Cr-added, Ti-added and Co-added Al alloys after HH treatments.

590 **Extended Data Figure S5 TEM results. a**, Standard-state Al alloys. **b**, Corresponding to the
591 partial area **b** in **a**. **c**, Mn-added Al alloys. **d**, Corresponding to the partial area **d** in **c**.

592 **Extended Data Figure S6 Hydrogen partitioning behavior in HH-treated Mn-added Al alloys**
593 **during deformation. a**, Hydrogen partitioning calculations for the region ahead of
594 hydrogen-induced quasi-cleavage crack tip under the in-situ tensile strain of 3.6%. **b**, Trapped
595 hydrogen contents among lattice, vacancies, dislocations, grain boundaries, IMC particles, η_2
596 precipitates and micro pores before and after loading.

597 **Extended Data Figure S7 Suppression of hydrogen-induced cracks by Al₁₁Mn₃Zn₂.** **a,**
598 Microstructures near the fracture surfaces of Mn-added Al alloys treated by HH after tensile
599 failure. The cracks mainly propagated along the grain interiors in Mn-added Al alloys. **b,**
600 Corresponding to the partial magnification images of the area **1** and **2** in **a**. **c, d,** Corresponding to
601 the partial magnification and mapping images of the area **c** and **d** in **b**, the IMC-rich region can
602 effectively blunt and suppress hydrogen-induced cracks.

603 **Extended Data Figure S8 3D Mapping of equivalent plastic strain, vacancy concentrations**
604 **and dislocation densities in the Mn-added Al alloys at load strain 0.0 to 3.6% on a x-z virtual**
605 **section. a,** Equivalent plastic strain. **b,** Vacancy concentration. **c,** Geometrically necessary
606 dislocations (GND). **d,** Statistically stored dislocations (SSD).

607

608

609

610

611