

An Analysis of the Photocatalytic Activities of ZnO Nanoparticles: Factors Influencing Dye Degradation

Asraf Ibna Helal
Nano Research Centre

Neogi, Newton
Nano Research Centre

Kristi Priya Choudhury
Nano Research Centre

MD. Golam Sazid
Nano Research Centre

<https://doi.org/10.5109/7157937>

出版情報 : Proceedings of International Exchange and Innovation Conference on Engineering & Sciences (IEICES). 9, pp.21-27, 2023-10-19. 九州大学大学院総合理工学府
バージョン :
権利関係 : Creative Commons Attribution-NonCommercial-NoDerivatives 4.0 International



An Analysis of the Photocatalytic Activities of ZnO Nanoparticles: Factors Influencing Dye Degradation

Asraf Ibna Helal^{1,2*}, Newton Neogi¹, Kristi Priya Choudhury¹, MD. Golam Sazid¹

¹Nano Research Centre, Bangladesh

²Department of Statistics, Shahjalal University of Science and Technology, Sylhet-3114, Bangladesh

*Corresponding author email: asraf16@student.sust.edu

Abstract: *Nanometal oxides exhibit size-dependent properties that set them apart from their larger counterparts. Nanomaterials have a considerable advantage due to their small size and high ratio of surface area to volume, which makes them suitable for photocatalysis and permits the breakdown of a variety of dyes. As a result of their photocatalytic activity, the use of zinc oxide nanoparticles (NPs) in environmental applications is gaining importance. The photocatalytic efficiency of ZnO NPs was evaluated by determining the progress of dye degradation, such as Methylene Blue (MB), Methyl Orange (MO), and Rhodamine B (RB). Multiple research studies have presented findings that support this specific area of inquiry. Various characteristics of ZnO NPs, such as their crystalline phase, particle size, and surface area, have a significant effect on their photocatalytic properties. Our study will demonstrate the effect of the NP sizes and others factors on dye degradation. In this case, we gathered data from various research projects for data analysis. Our analysis includes descriptive analysis, chi-square test, correlation, and one-way ANOVA Analysis of Variance (ANOVA) using those data. This study concludes the effect of different factors on dye degradation efficiency.*

Keywords: NPs; ZnO NPs, Photocatalytic properties; Dye degradation.

1. INTRODUCTION

Metal oxide nano sized materials are recently shown efficient in different purposes [1]. Metal oxide NPs (MONs) are being explored now in photocatalytic applications [2]. Among various MONs, ZnO NPs are the most studied topic in the field of nanoscience. Because of the high photocatalytic activity of ZnO NPs toward a number of different azo dyes, it is feasible that these particles could find use in waste water treatment [3]. ZnO nanostructures have been shown to be attractive photocatalyst candidates for use in photodegradation because they are non-toxic, affordable, and much more effective at absorbing light from a broad range of the solar spectrum [4]. The bandgap energy of ZnO nps plays an essential role in defining the photocatalytic activity of substances [5]. When subjected to blacklight, ZnO NPs accelerated the degradation of reactive orange and MB, RB, reactive blue, MO, and methyl red. During the dye degradation of MB, modified ZnO NPs showed off their excellent photocatalytic characteristics [6]. MB was effectively broken down by Mg-doped ZnO NPs when these were exposed to both visible light and ultraviolet light. When exposed to UV and visible light, respectively, Ce-doped ZnO NPs were able to photo catalyze the breakdown of several dyes in an effective manner [7]. Research has been conducted on the photocatalytic degradation of MB by a ZnO-based metal organic framework (MOF). The fact that more than 90 percent of the dyes were degraded is an encouraging outcome. In a system that uses photocatalysis, the transformation or reaction takes place on the surface of the catalyst. When photons activate a photocatalyst with energies that are equivalent to or greater than the bandgap energy of the photocatalyst, the energy of the photon is absorbed by the electrons in the photocatalyst. When the energy level exceeds the bandgap energy, electrons can be excited

from the valence band to the conduction band, resulting in the creation of a vacancy known as a "hole" in the valence band. It is noteworthy that the energy level of the bandgap cannot produce the hole. The bandgap symbolizes the energy difference among the valence and conduction bands. Moreover, semiconductor holes do not immediately release hydroxide radicals. Photocatalysis is a process in which a semiconductor material produces hydroxide radicals through the interaction of photoexcited electrons and holes with water molecules or other reactants. The energy level of the bandgap can not exhibit a direct proportionality to the emission of hydroxide radicals [8] [9]. ZnO NPs are only industrially employed in sunscreens that require UV protection because of the photocatalytic properties of the material [10]. When ZnO is subjected to ultraviolet radiation, the result is the production of reactive free radicals [11]. When a material is subjected to UV radiation, the electrons in ZnO are the ones that are ultimately accountable for the production of electron-hole pairs. The particle size, shape, and manufacturing method all had an impact on the photocatalytic properties of ZnO in the UV-induced degradation of dyes like MO [12]. It is possible to improve the overall efficiency of the photocatalytic process by making adjustments to the particle size and shape of ZnO photocatalysts, as well as the production conditions and manufacturing procedures. Our industries produce a huge amount of waste water [13]. Among these dye-contaminated waters, some are more harmful. So, before disposing of it, it must be treated. By using the photocatalytic property of ZnO NPs, dye degradation can take place as a treating agent. Various ZnO NPs such as Graphene/ZnO, GO/ZnO, α -Fe₂O₃/ZnO, ZnO/-Mn₂O₃, ZnO/WO₃, Eu/ZnO, etc. are proven as efficient photocatalysts in water treatment by doing dye degradation. But which parameters are directly related to the degradation efficiency variation is still a topic of observation. We investigated data to find the

factors affecting dye degradation efficiency through our analysis of the data. For that we had to conduct descriptive analysis, chi-square test, correlation and one way ANOVA test. A sort of data analysis called descriptive analysis helps in precisely defining, showing, or summarizing data points so that patterns can emerge that fulfill all of the needs of the data. This type of analysis can also be used to summarize the data [14]. The chi-square test is a statistical procedure that compares observed and expected results [15]. The objective of this test is to determine whether a discrepancy between observed and expected data is due to coincidence or a relationship between the variables being examined. The correlation coefficient measures the intensity of the assumed linear association between the variables under consideration [16]. One-way ANOVA is typically employed when there is a single independent variable or factor, and the objective is to determine whether variations or various levels of that factor have a measurable impact on a dependent variable [17]. The study aims to find the factors are significantly associated with the dye degradation efficiency of ZnO NPs.

2. METHODOLOGY

We have 47 data of ZnO NPs for data analysis. There 4 variables of the data such as, Size, Efficiency, Dye name and Duration of work of ZnO NPs. There, we perform descriptive and cross-sectional study analysis to make our result more precise and to find factor affecting the efficiency of NPs. Also, perform correlation to make sure that the result of association. We use SPSS-version 25 for the data analysis. We make the variables categorical for convenience of the data analysis. We make the variables categorical for convenience of the data analysis.

Table 1: Table of categorical variables introduction

Variables Name	Category	Description
Efficiency of NPs	Most Efficient	Which efficiency is 80% or more
	Efficient	Efficiency less than 80%
Size of NPs	1 is (≤ 30)	Size is 30 nm or less
	2 is (> 30)	Size is above 30
Dye Name	1	MO
	2	MB
	3	RB
Duration of dye degradation	Not time consuming	Time less or equal to 3 hr
	Time consuming	Time greater than 3 hr

3. COLLECTED DATA

Table 2: ZnO NPs Table of Different Size and Efficiency.

Nanoparticle	Size (nm)	Dye name	Efficiency (%)	Time (min)	Ref.
Graphene/ZnO	23.6	MO	97.10	360	[18]
GO/ZnO	35	MO	95	120	[19]

α -Fe ₂ O ₃ /ZnO	56.7	MO	100	180	[20]
ZnO/-Mn ₂ O ₃	50	MO	90	210	[21]
2% ZnO/WO ₃	19.28	MO	100	180	[22]
1 mol% Eu/ZnO	5.67	MO	95.30	180	[23]
ZnO (0.4g/l)	17.3	MO	95	120	[24]
ZnO nano powder	27	MO	98.10	45	[25]
ZnO powder	50	MO	80	120	[25]
Fe ₃ O ₄ /ZnO core/shell magnetic NPs	25-30	MO	83	360	[26]
Cu/ZnO	28.5	MO	88	240	[27]
ZnO nanorods on indium-tin oxide substrate	80-90	MO	71	150	[28]
ZnO NP	15-25	MO	81	100	[29]
porous graphene/ZnO nanocomposite	32-72	MO	100	150	[30]
ZnO:Eu(1%)-W	16.2	MO	10	150	[31]
ZnO:Eu(10%)-M	5.6	MO	100	60	[31]
ZnO:Eu(3%)-W	16.2	MO	62	150	[31]
ZnFe ₂ O ₄ @ZnO	17	MO	99	240	[32]
Ag-ZnO	64.32	MO	92	30	[33]
Cu-doped ZnO nanorods	9.46	MO	99	120	[34]
ZnO NPs	20-30	MB	81	240	[35]
FSP-derived ZnO NPs	47	MB	70	60	[36]
ZnO NPs (M8-ZnO)	22	MB	90	120	[37]
ZnO NPs synthesized by ppt method	30	MB	81.02	180	[38]
ZnO NPs synthesized by sol-gel method	28	MB	92.48	180	[38]
ZnO-Si	32	MB	90	60	[39]
ZnO@GO	15 \pm 5	MB	98.50	15	[40]
Gd doped ZnO	39.63	MB	93	90	[41]
Ni-Th-ZnO	30.58	MB	93	180	[42]
Zn ₉₈ Ca ₂ O	26.09	MB	89	120	[43]
Mn-ZnO	28.6	MB	88	120	[44]
ZnO NP grown on silica	33.8-89.8	MB	71.70	150	[45]
ZnONp**	98	MB	78	60	[46]
amine modified ZnO NPs	7.51	MB	93.80	25	[47]
polyaniline/ZnO nanocomposite	10-30	MB	94	360	[48]
ZnO NP	28	RB	95	70	[49]
ZnE4T (spherical NPs)	29	RB	84	120	[50]

ZnE5T (nanosheets)	31	RB	78	120	[50]
ZnE6T (hexagonal prismatic NPs)	32	RB	75	120	[50]
ZnO Nps	18.3	RB	74	180	[51]
CR –ZnONPs	13.33	RB	98	200	[52]
ZnO NPs	20.37	RB	46	180	[53]
Ag–ZnO	30	RB	85	300	[54]
5- SeZO	7.91	RB	99.21	150	[55]
CAB-ZnO	21	RB	60	480	[56]
ZnO nanofiber	78	RB	60	120	[57]
ZnO nanoparticle	30	RB	28	120	[57]

4. RESULTS & DISCUSSION

We perform bar plot for those variables in Chi-square test Which shows the result given below,

Figure 1 shows the descriptive analysis of Efficiency wise size of ZnO NPs. Where we see 12.77% most efficient NPs size are less than or equal to 30 and 53.19% efficient NPs size are greater than 30. On the other hand, 17.02% most efficient NPs size are less than or equal to 30 and 17.02% efficient NPs size are greater than 30.




Fig. 1. Size vs Efficiency bar chart




Fig. 2: Dye vs Efficiency bar chart

Figure 2 shows that 8.51% most efficient NPs of our data degrade MO dye and shows their efficiency, where 34.04% NPs shows their best efficiency by degrading MO dye. The percentage of most efficient and percentage of efficient NPs in degradation of MB dye are 6.38% and 25.53% respectively. Also, we see the percentage of most

efficient and rate of efficient NPs in RB degradation are 14.89% and 10.64% respectively.




Fig. 3: Duration of dye degradation vs Efficiency bar chart

Figure 3 shows that 27.66% most efficient NPs are not time consuming and 2.13% are time consuming. On the other hand, 51.06% efficient NPs are not time consuming and 19.15% are time consuming.

We perform Chi-square test for finding associated variables with the efficiency of ZnO NPs in SPSS. Where we see the result as,

Table 3: Chi-square test result

Variables	Chi-square test with Efficiency	P-value
	Chi-square value	
Size of NP	4.739 ^a	0.029
Dye	6.279 ^a	0.043
Duration of dye degradation	2.378 ^a	0.242

Where we see that the P-value of Size of ZnO NPs and P-value of Dye of Chi-square test with efficiency are 0.045 and 0.044 respectively. We interpret that there are significant association of ZnO NPs size and degraded dye with the dye degradation efficiency. That means there are effects of NPSs size and variation of dye on degradation efficiency of ZnO NPSs. We also see that the p value of duration of dye degradation is 0.242, which means there is no effect of duration in efficiency of dye degradation of ZnO NPs.

Now we check the strength of the association. We consider the symmetric measure of chi-square test table for checking the strength. We have two associated variables, which are Size and Dye. The symmetric tables are

Table 4: Table of Symmetric Measures of Size & Efficiency

	Value	Approximate Significance
Nominal by Phi	-.318	.029
Nominal by Cramer's V	.318	.029
N of Valid Cases	47	

The table 4 is 2 by 2 in size because the variables (Size and Efficiency) hold two labels. So, we consider the Phi-coefficient value. We know for the value of Phi-coefficient under 0.2, Between 0.2 and 0.3 and above 0.3 interpret weak, moderate and strong association respectively. We see the Phi value for size and efficiency is -0.318. The value 0.318 interpret that there is strong association between Size and Efficiency. The negative sign interpreted opposite relation between those variables. That means if the size increase, the efficiency of photocatalysis will decrease. If the size decrease, the efficiency will increase.

Table 5: Table of Symmetric Measures of Dye & Efficiency

			Value	Approximate Significance
Nominal	by	Phi	.365	.043
Nominal		Cramer's V	.365	.043
N of Valid Cases			47	

The tables are two by three in size. Because Dye has three labels. So, we consider the Cramer's V coefficient for interpreting the result. The value of Cramer's V is 0.365, which shows the strong relationship between Dye and Efficiency. Because, we know if the value is above 0.3, it will interpret the strong association.

To be sure about the Size vs Efficiency negative association, we perform the Bivariate correlation between size and efficiency of ZnO NPs. Where we see,

Table 6: Table of Correlation

		Correlations	
		Efficiency	Size of NPS
		Categorical	Categorical
Efficiency	Pearson	1	-.318
	Correlation		
Categorical	Sig. (2-tailed)		.030
Sum of Squares		9.830	-3.234
	and Cross-products		
	Covariance	.214	-.070
	N	47	47
Size	Pearson	-.318	1
of NP	Correlation		
Categorical	Sig. (2-tailed)	.030	
Sum of Squares		-3.234	10.553
	and Cross-products		
	Covariance	-.070	.229
	N	47	47

The table 6 shows the correlation between Efficiency and Size of ZnO NPs is -0.318. So, we found the negative correlation between size and efficiency. Thus, there is a negative relation among these variants. If the size increases, the efficiency of ZnO will decrease. If the size decreases, the efficiency will increase.

To find the best degraded dye by photocatalysis with ZnO NPs, we perform One Way ANOVA between Dye and Efficiency. Findings given below,

Table 7: Descriptive Analysis Table of One-way ANOVA Test

	N	Mean	Std. Deviation	Std. Error
MO	20	1.8000	.41039	.09177
MB	15	1.8000	.41404	.10690
RB	12	1.4167	.51493	.14865
Total	47	1.7021	.46227	.06743

From One way ANOVA we see the P-value is 0.43, which also shows the variables are significant. Then we see in the table 7 RB dye have minimum mean. Thus, the RB is most feasible dye for the dye degradation among our studied dyes. The mean values of another two dyes are approximately similar. Now we find the feasible degraded dye between MO and MB.

To obtain the significant mean difference between different dye we see the table of Post Hoc Test from One Way ANOVA, which revealed the mostly degraded dye in dye degradation which is catalyzed by ZnO NPs. The table is given below,

Table 8: Table of Post Hoc Test

		Mean		
(I) Dye Name	(J) Dye Name	Difference (I-J)	Std. Error	Sig.
MO	MB	.00000	.15027	1.000
	RB	.38333*	.16065	.021
MB	MO	.00000	.15027	1.000
	RB	.38333*	.17039	.030
RB	MO	-.38333*	.16065	.021
	MB	-.38333*	.17039	.030

The table 8 shows that there was no significant mean difference between MO and MB. Because the mean difference is near to 0. Two dyes are equivalently degraded in degradation. So, the other parameters such as cost and availability of dye will determine their feasibility.

We found that there was a relationship between the amount of time the experiment was carried out for, the type of dye that was used, and the size of the ZnO NPs that were used. The Chi-square test demonstrated the existence of an association that is statistically significant between size and effectiveness. A substantial association

was found between dye and efficiency, according to the findings of the Chi-square test, which was also conducted. However, there was not a significant association between the

amounts of time it took for the dye degradation. Using the Chi-square test and the correlation, we were able to determine that there is a significant and negative link between size and efficiency. In addition to this, we discovered that there is a meaningful connection between the Dye and the photocatalytic efficiency of ZnO NPs. When it came to the degradation of dye catalyzed by ZnO NPs, we found that RB was the most feasible and effective in dye degradation. When it came to the degradation of the dye, MO and MB were equivalently identical to one another. As the correlation between size and efficiency was negative, we reached at the finishing that the size of ZnO NPs is strongly associated with an inversely related and significant connection.

5. CONCLUSION

In the conclusion we have descriptive analysis of ZnO NPs. We observed the dye-degradation by ZnO NPs with Size, Dye and Duration of work. There was significant relation between size & efficiency from Chi-square test. The relation between dye & efficiency from Chi-square test was also significant. But there was no significant between Duration of dye degradation and Efficiency. From Chi-square test and Correlation, we found strong and inverse relationship of size with efficiency. Also, we had strong relation between Dye & Efficiency of ZnO NPs. We found that RB was most feasible for dye degradation of ZnO NPs. MO and MB were equivalent in dye degradation. So, we conclude that the size of ZnO NPs have strong and opposite relation. The Dye has strong relation with the efficiency. RB is most efficient degraded dye.

6. REFERENCES

- [1] T. Yanagida, Material design of metal oxide nanowires and their promises, *Correlated Functional Oxides: Nanocomposites and Heterostructures*, (2016) 195–204.
- [2] N. Krobkrong, T. Thaweechai, W. Sirisaksoontorn, Nanodot MoS₂@3DOM TiO₂ composites for their photocatalytic application Nanodot MoS₂@3DOM TiO₂ composites for their photocatalytic application, *Proceedings of International Exchange and Innovation Conference on Engineering & Sciences (IEICES)*, 4 (2018) 112–115.
- [3] Y. Yoon, P.L. Truong, D. Lee, S.H. Ko, Metal-Oxide Nanomaterials Synthesis and Applications in Flexible and Wearable Sensors, *ACS Nanoscience Au*, 2 (2022) 64–92.
- [4] P. Raizada, A. Sudhaik, P. Singh, Photocatalytic water decontamination using graphene and ZnO coupled photocatalysts: A review, *Mater Sci Energy Technol*, 2 (2019) 509–525.
- [5] L. Muñoz-Fernandez, L.S. Gomez-Villalba, O. Milošević, M.E. Rabanal, Influence of nanoscale defects on the improvement of photocatalytic activity of Ag/ZnO, *Mater Charact*, 185 (2022) 111718.
- [6] S. Modi, V.K. Yadav, A. Gacem, I.H. Ali, D. Dave, S.H. Khan, K.K. Yadav, S.U. Rather, Y. Ahn, C.T. Son, B.H. Jeon, Recent and Emerging Trends in Remediation of MB Dye from Wastewater by Using Zinc Oxide Nanoparticles, *Water*, 14 (2022) 1749.
- [7] R. Al Hazmi, H. Oudghiri-Hassani, F. Al Wadaani, M. abboudi, High Performance Photocatalytic Activity of Mg²⁺ Doped Hexagonal ZnO Nanoparticles in the MB Degradation under UV Irradiation, *Moroccan Journal of Chemistry*, 4 (2016) 324–331.
- [8] H. Verma, S. Upadhyay, S. Verma, *Nanomaterials For Environmental Air Pollution Control: A Review*, 10 (2022).
- [9] J. Byun, H.A. Patel, D. Thirion, C.T. Yavuz, Charge-specific size-dependent separation of water-soluble organic molecules by fluorinated nanoporous networks, *Nature Communications*, 7 (2016) 1–10.
- [10] O.P. Egambaram, S. Kesavan Pillai, S.S. Ray, *Materials Science Challenges in Skin UV Protection: A Review*, *Photochem Photobiol*, 96 (2020) 779–797.
- [11] E.F. Bernstein, H.W. Sarkas, P. Boland, D. Bouche, Beyond sun protection factor: An approach to environmental protection with novel mineral coatings in a vehicle containing a blend of skincare ingredients, *J Cosmet Dermatol*, 19 (2020) 407–415.
- [12] P. Raizada, A. Sudhaik, P. Singh, Photocatalytic water decontamination using graphene and ZnO coupled photocatalysts: A review, *Mater Sci Energy Technol*, 2 (2019) 509–525.
- [13] K.G. Thakre, D.P. Barai, B.A. Bhanvase, A review of graphene-TiO₂ and graphene-ZnO nanocomposite photocatalysts for wastewater treatment, *Water Environment Research*, 93 (2021) 2414–2460.
- [14] J.L. Schafer, J.W. Graham, Missing data: Our view of the state of the art, *Psychol Methods*, 7 (2002) 147–177.
- [15] D. Sharpe, Chi-Square Test is Statistically Significant: Now What?, *Practical Assessment, Research, and Evaluation*, 20 (2019) 8.
- [16] P. Schober, L.A. Schwarte, Correlation Coefficients: Appropriate Use and Interpretation, *Anesth Analg*, 126 (2018) 1763–1768.
- [17] W.G. Kim, C.Y.N. Ng, Y. soon Kim, Influence of institutional DINESERV on customer satisfaction, return intention, and word-of-mouth, *Int J Hosp Manag*, 28 (2009) 10–17.
- [18] R. Beura, P. Thangadurai, Structural, optical and photocatalytic properties of graphene-ZnO nanocomposites for varied compositions, *Journal of Physics and Chemistry of Solids*, 102 (2017) 168–177.
- [19] V.N. Nguyen, D.T. Tran, M.T. Nguyen, T.T.T. Le, M.N. Ha, M.V. Nguyen, T.D. Pham, Enhanced photocatalytic degradation of MO using ZnO/graphene oxide nanocomposites, *Research on Chemical Intermediates*, 44 (2018) 3081–3095.
- [20] J. Xie, M. Li, Y. Hao, X. Meng, Y. Meng, Z. Li, Preparation of α -Fe₂O₃/ZnO composites and their photocatalytic activity under simulated sunlight irradiation, *World Journal of Engineering*, 12 (2015) 325–329.

- [21] R. Saravanan, V.K. Gupta, V. Narayanan, A. Stephen, Visible light degradation of textile effluent using novel catalyst ZnO/ γ -Mn₂O₃, *J Taiwan Inst Chem Eng*, 45 (2014) 1910–1917.
- [22] A.K.L. Sajjad, S. Sajjad, A. Iqbal, N. ul A. Ryma, ZnO/WO₃ nanostructure as an efficient visible light catalyst, *Ceram Int*, 44 (2018) 9364–9371.
- [23] Y. Zong, Z. Li, X. Wang, J. Ma, Y. Men, Synthesis and high photocatalytic activity of Eu-doped ZnO nanoparticles, *Ceram Int*, 40 (2014) 10375–10382.
- [24] C. Chen, J. Liu, P. Liu, B. Yu, Investigation of Photocatalytic Degradation of MO by Using Nano-Sized ZnO Catalysts, *Advances in Chemical Engineering and Science*, 01 (2011) 9–14.
- [25] J. Kaur, S. Bansal, S. Singhal, Photocatalytic degradation of MO using ZnO nanopowders synthesized via thermal decomposition of oxalate precursor method, *Physica B Condens Matter*, 416 (2013) 33–38.
- [26] R.Y. Hong, S.Z. Zhang, G.Q. Di, H.Z. Li, Y. Zheng, J. Ding, D.G. Wei, Preparation, characterization and application of Fe₃O₄/ZnO core/shell magnetic nanoparticles, *Mater Res Bull*, 43 (2008) 2457–2468.
- [27] M. Fu, Y. Li, S. Wu, P. Lu, J. Liu, F. Dong, Sol–gel preparation and enhanced photocatalytic performance of Cu-doped ZnO nanoparticles, *Appl Surf Sci*, 258 (2011) 1587–1591.
- [28] J.H. Zheng, Q. Jiang, J.S. Lian, Synthesis and optical properties of ZnO nanorods on indium tin oxide substrate, *Appl Surf Sci*, 258 (2011) 93–97.
- [29] V. V. Gawade, N.L. Gavade, H.M. Shinde, S.B. Babar, A.N. Kadam, K.M. Garadkar, Green synthesis of ZnO nanoparticles by using *Calotropis procera* leaves for the photodegradation of MO, *Journal of Materials Science: Materials in Electronics*, 28 (2017) 14033–14039.
- [30] L. Wang, Z. Li, J. Chen, Y. Huang, H. Zhang, H. Qiu, Enhanced photocatalytic degradation of MO by porous graphene/ZnO nanocomposite, *Environmental Pollution*, 249 (2019) 801–811.
- [31] L. V. Trandafilović, D.J. Jovanović, X. Zhang, S. Ptasińska, M.D. Dramićanin, Enhanced photocatalytic degradation of MB and MO by ZnO:Eu nanoparticles, *Appl Catal B*, 203 (2017) 740–752.
- [32] S.D. Kulkarni, S. Kumbar, S.G. Menon, K.S. Choudhari, C. Santhosh, Magnetically separable core–shell ZnFe₂O₄@ZnO nanoparticles for visible light photodegradation of MO, *Mater Res Bull*, 77 (2016) 70–77.
- [33] S. R., J.A. Jebasingh, M.V. S., P.K. Stanley, P. Ponmani, M.E. Shekinah, J. Vasanthi, Excellent Photocatalytic degradation of MB, RB and MO dyes by Ag-ZnO nanocomposite under natural sunlight irradiation, *Optik (Stuttg)*, 231 (2021) 166518.
- [34] P.M. Perillo, M.N. Atia, Solar-assisted photodegradation of MO using Cu-doped ZnO nanorods, *Mater Today Commun*, 17 (2018) 252–258.
- [35] I. Kazeminezhad, A. Sadollahkhani, Influence of pH on the photocatalytic activity of ZnO nanoparticles, *Journal of Materials Science: Materials in Electronics*, 27 (2016) 4206–4215.
- [36] O. Mekasuwandumrong, P. Pawinrat, P. Praserttham, J. Panpranot, Effects of synthesis conditions and annealing post-treatment on the photocatalytic activities of ZnO nanoparticles in the degradation of MB dye, *Chemical Engineering Journal*, 164 (2010) 77–84.
- [37] C.A. Soto-Robles, O. Nava, L. Cornejo, E. Lugo-Medina, A.R. Vilchis-Nestor, A. Castro-Beltrán, P.A. Luque, Biosynthesis, characterization and photocatalytic activity of ZnO nanoparticles using extracts of *Justicia spicigera* for the degradation of MB, *J Mol Struct*, 1225 (2021).
- [38] A. Balcha, O.P. Yadav, T. Dey, Photocatalytic degradation of MB dye by zinc oxide nanoparticles obtained from precipitation and sol-gel methods, *Environmental Science and Pollution Research*, 23 (2016) 25485–25493.
- [39] W. Shen, Z. Li, H. Wang, Y. Liu, Q. Guo, Y. Zhang, Photocatalytic degradation for MB using zinc oxide prepared by codeposition and sol–gel methods, *J Hazard Mater*, 152 (2008) 172–175.
- [40] R. Atchudan, T.N.J.I. Edison, S. Perumal, D. Karthikeyan, Y.R. Lee, Facile synthesis of zinc oxide nanoparticles decorated graphene oxide composite via simple solvothermal route and their photocatalytic activity on MB degradation, *J Photochem Photobiol B*, 162 (2016) 500–510.
- [41] Q.I. Rahman, M. Ahmad, S.K. Misra, M. Lohani, Effective photocatalytic degradation of RB dye by ZnO nanoparticles, *Mater Lett*, 91 (2013) 170–174.
- [42] S. Selvaraj, M.K. Mohan, M. Navaneethan, S. Ponnusamy, C. Muthamizchelvan, Synthesis and photocatalytic activity of Gd doped ZnO nanoparticles for enhanced degradation of MB under visible light, *Mater Sci Semicond Process*, 103 (2019) 104622.
- [43] K. Vignesh, M. Rajarajan, A. Suganthi, Visible light assisted photocatalytic performance of Ni and Th co-doped ZnO nanoparticles for the degradation of MB dye, *Journal of Industrial and Engineering Chemistry*, 20 (2014) 3826–3833.
- [44] P. Visali, R. Bhuvaneswari, Photoluminescence and enhanced photocatalytic activity of ZnO nanoparticles through incorporation of metal dopants Al and Ca, *Optik (Stuttg)*, 202 (2020).
- [45] J. Singh, A. Rath, M. Rawat, V. Kumar, K.H. Kim, The effect of manganese doping on structural, optical, and photocatalytic activity of zinc oxide nanoparticles, *Compos B Eng*, 166 (2019) 361–370.
- [46] M.S. Azmina, R.M. Nor, H.A. Rafaie, N.S.A. Razak, S.F.A. Sani, Z. Osman, Enhanced photocatalytic activity of zno nanoparticles grown on porous silica microparticles, *Applied Nanoscience (Switzerland)*, 7 (2017) 885–892.
- [47] D. Dey, G. Kaur, M. Patra, A.R. Choudhury, N. Kole, B. Biswas, A perfectly linear trinuclear zinc–Schiff base complex: Synthesis, luminescence property and photocatalytic activity of zinc oxide nanoparticle, *Inorganica Chim Acta*, 421 (2014) 335–341.
- [48] J. Yoon, S.G. Oh, Synthesis of amine modified ZnO nanoparticles and their photocatalytic activities in micellar solutions under UV irradiation, *Journal of Industrial and Engineering Chemistry*, 96 (2021) 390–396.
- [49] V. Eskizeybek, F. Sari, H. Gülce, A. Gülce, A. Avci, Preparation of the new polyaniline/ZnO nanocomposite and its photocatalytic activity for

- degradation of MB and malachite green dyes under UV and natural sun lights irradiations, *Appl Catal B*, 119–120 (2012) 197–206.
- [50] S. Akir, A. Barras, Y. Coffinier, M. Bououdina, R. Boukherroub, A.D. Omrani, Eco-friendly synthesis of ZnO nanoparticles with different morphologies and their visible light photocatalytic performance for the degradation of RB, *Ceram Int*, 42 (2016) 10259–10265.
- [51] M. Ahmad, W. Rehman, M.M. Khan, M.T. Qureshi, A. Gul, S. Haq, R. Ullah, A. Rab, F. Mena, Phytogetic fabrication of ZnO and gold decorated ZnO nanoparticles for photocatalytic degradation of RB, *J Environ Chem Eng*, 9 (2021) 104725.
- [52] T. Varadavenkatesan, E. Lyubchik, S. Pai, A. Pugazhendhi, R. Vinayagam, R. Selvaraj, Photocatalytic degradation of RB by zinc oxide nanoparticles synthesized using the leaf extract of *Cyanometra ramiflora*, *J Photochem Photobiol B*, 199 (2019) 111621.
- [53] V.V. Pham, T.D. Nguyen, P.P. Ha La, M. Thi Cao, A comparison study of the photocatalytic activity of ZnO nanoparticles for organic contaminants degradation under low-power UV-A lamp, *Advances in Natural Sciences: Nanoscience and Nanotechnology*, 11 (2020) 015005.
- [54] R.S. Patil, M.R. Kokate, D. V. Shinde, S.S. Kolekar, S.H. Han, Synthesis and enhancement of photocatalytic activities of ZnO by silver nanoparticles, *Spectrochim Acta A Mol Biomol Spectrosc*, 122 (2014) 113–117.
- [55] S. Kumar, S.K. Sharma, R.D. Kaushik, L.P. Purohit, Chalcogen-doped zinc oxide nanoparticles for photocatalytic degradation of RB under the irradiation of ultraviolet light, *Mater Today Chem*, 20 (2021) 100464.
- [56] P. Pascariu, L. Olaru, A.L. Matricala, N. Olaru, Photocatalytic activity of ZnO nanostructures grown on electrospun CAB ultrafine fibers, *Appl Surf Sci*, 455 (2018) 61–69.
- [57] H. Liu, J. Yang, J. Liang, Y. Huang, C. Tang, ZnO Nanofiber and Nanoparticle Synthesized Through Electrospinning and Their Photocatalytic Activity Under Visible Light, *Journal of the American Ceramic Society*, 91 (2008) 1287–1291.