

Mini review on the application research of nanoscale zero valent iron in water treatment

Yi, Luo

Water and Environmental Engineering Laboratory, Interdisciplinary Graduate School of
Engineering Sciences, Kyushu University

Eljamal, Osama

Water and Environmental Engineering Laboratory, Interdisciplinary Graduate School of
Engineering Sciences, Kyushu University

<https://doi.org/10.5109/7157995>

出版情報 : Proceedings of International Exchange and Innovation Conference on Engineering &
Sciences (IEICES). 9, pp.313-320, 2023-10-19. 九州大学大学院総合理工学府

バージョン :

権利関係 : Creative Commons Attribution-NonCommercial-NoDerivatives 4.0 International

Mini review on the application research of nanoscale zero valent iron in water treatment

Luo Yi¹, Osama Eljamal^{1*}

¹ Water and Environmental Engineering Laboratory, Interdisciplinary Graduate School of Engineering Sciences, Kyushu University, 6-1 Kasuga-Koen Kasuga, Fukuoka 816-8580, Japan.

*Corresponding author email: osama-eljamal@kyudai.jp

Abstract: *Nanoscale zero-valent iron (nZVI) is highly efficient in environmental pollution control technology, owing to its unique zero-valent iron core-iron oxide surface, which exhibits exceptional adsorption and reduction properties. This paper provides a comprehensive understanding of the physical and chemical properties of nano-iron, with a primary focus on the preparation of nZVI. While nZVI finds extensive application in sewage treatment, it also demonstrates outstanding performance in the remediation of soil organic matter and heavy metal pollution, delivering excellent results and displaying good fluidity.*

Keywords: Nanoscale zero valent iron; Preparation method; Wastewater treatment; Modification; Mechanism of action

1. INTRODUCTION

Nanomaterials, with dimensions between 1 and 100 nm, exhibit unique properties due to their small size, making them essential in various industries [1,2]. Among these nanomaterials, nano-zero-valent iron (nZVI) stands out for its high specific surface area, tiny size, rapid reactivity, strong reducibility, and exceptional adsorption capabilities [4].

In this article, we focus on nZVI, its preparation, and applications in environmental pollution control. We explore its core-shell structure, with a dense zero-valent iron core and an iron oxide or hydroxyl iron outer shell, enabling both reduction and adsorption functions.

We also discuss the pioneering work of Glavee et al. [5], who used sodium borohydride to synthesize nZVI, and subsequent research by Zhang et al. [6].

Throughout the article, we examine nZVI's role in soil and groundwater remediation, organic pollutant removal, and heavy metal detoxification, highlighting its significant contributions to pollution control technologies [7].

2. PREPARATION METHOD OF NANOSCALE ZERO-VALENT IRON

The preparation method of nano-zero-valent iron can be divided into two types: decomposition method and synthesis method according to the shape change of nZVI[8]. The decomposition method is to convert large particles of iron into nano-scale particles. The synthesis method is opposite, and the molecular level or even

smaller iron, converted to nanoscale. Common preparation methods are shown in Table 1.

3. APPLICATIONS OF nZVI IN WASTEWATER TREATMENT

3.1. Removal of heavy metals

Heavy metals are a class of poisonous adulterants that have a serious impact on mortal and other natural health [16]. However, it'll seriously contaminate the water body, if heavy metals wastewater from different diligence is continuously discharged into gutters and lakes without treatment. In order to break this problem, people have started exploration on nano- zero- valent iron, because nano- zero- valent iron has the advantages of strong exertion, rapid-fire response, and high junking effectiveness, which has gradationally attracted wide attention [17,18].

Adsorption-co-precipitation: For metal cations whose standard electrode potential is lower than that of iron, such as Zn^{2+} , Ba^{2+} , etc., Nanoscale zero-valent iron can be adsorbed on its surface, but they cannot be directly reduced. At this time, nano-zero-valent iron will react with water to generate a large number of hydroxide ions (OH^-), which will change the acidity and alkalinity of the particle surface, thereby combining with heavy metal ions to form a precipitate, which will be fixed on nano-zero-valent iron particles [19].

Table 1. Summary of nZVI preparation methods

No.	Production Method	Characteristics	Particle size (nm)	Reference
1	Liquid phase reduction method	Compared with other methods, it is suitable for laboratory-level research and is easy to prepare	Approx 50	[9]
2	Liquid phase reduction method	Significantly increased effective reactive surface area and stability of nZVI	29.9	[10]
3	Mechanical ball milling method	High reactivity, stability and flowability of particles	<100	[11]
4	Mechanical ball milling method	Effectively prevents nZVI from agglomerating and forming larger particles, keeping it nanoscale	<100	[12]
5	Electrodeposition method	Ultrasound can reduce the degree of particle aggregation and facilitate the generation of smaller particles	1~20	[13]
6	Green synthesis method	Extracted from plants is non-toxic and more environmentally friendly	100	[14]
7	Laser pyrolysis method	The core-shell morphology of iron-carbon nanocomposites may be affected by the gas flow in the reaction zone, and the particle size is extremely small.	3~7	[15]

Reduction-co-precipitation: suitable for metals that do not exist in water in the form of cations, such as metal Cr. nZVI can quickly reduce Cr (VI) to Cr(III), and precipitate and fix it on the surface of nZVI[20].

Adsorption- oxidation- reduction The junking of As by nano- zero- valent iron is a combination of adsorption, oxidation and reduction. The main forms of As in water are As(V) and As(III). Nano zero- valent iron can reduce As(V) to As(0) and As(III), and can also oxidize As(III) to As(V)[21, 56,57,58].

Due to the small size of nano- ZVI patches and their capability to resettle fleetly in water, they can be flexibly used for in- situ and ex-situ remediation of heavy metals in water. Still, the high price of Nanoscale zero- valent iron, and its easy agglomeration reduces the migration speed, which limits its operation in the factual heavy

metals’ wastewater treatment. thus, reducing the agglomeration miracle of nano- ZVI is of great significance for its wide operation [22, 60, 61,62, 63, 64]. In summary, due to its great efficiency in heavy metal ion removal, nano-sized zero-valent iron has received a lot of interest in the field of heavy metal ion removal. However, its use is restricted by the expensive cost and the difficulty of reunion, therefore effective improvement methods are required.[23].

3.2. Nitrate removal

Nitrogenous pollutants in water bodies can be divided into two categories: organic and inorganic. Organic nitrogen-containing pollutants are stable in structure, difficult to decompose and transform, and have a long residual time, which poses a greater risk of refractory

degradation to organisms [24, 68,69]. Among inorganic nitrogen-containing pollutants, nitrite nitrogen and nitrate nitrogen are the most harmful, which can cause serious damage to human and animal health such as methemoglobinemia, so the discharge of such substances needs to be strictly controlled [25, 70, 71].

In recent years, studies have shown that zero-valent iron shows great potential in reductive removal of nitrate in water [26]. Scientists use nano-zero-valent iron to quickly reduce nitrate in water through chemical reactions, converting it into safer substances such as nitrogen. However, this method also has some disadvantages, such as nano-zero-valent iron cannot completely reduce nitrate to nitrogen, resulting in the production of a large amount of ammonia-nitrogen during the reaction. In addition, the pH value of the reaction system also needs to be strictly controlled, which limits its application range [27, 55, 59]. Future research should concentrate on enhancing the capabilities of nZVI to more effectively convert nitrate to nitrogen and lower the cost of further processing. In order to increase the removal effectiveness of nano-zero-valent iron, scientists must also discover better techniques to regulate the pH level of the reaction system. By doing so, we may more effectively address the issue of nitrogenous pollution in water bodies.[28].

3.3. Removal of organic halogenated compounds

Organohalogenated substances are a class of pollutants ubiquitous in water and soil, mainly produced in the production and use of refrigerants, paints and pesticides [29, 65, 66, 67]. Most of these organic halogenated substances are stable in structure, difficult to degrade and highly toxic, and are easy to accumulate in the human body and the environment, so they are listed as one of the three key organic pollutants in global environmental science research (organic halogenated substances, heterocyclic compounds and polycyclic aromatic hydrocarbons) [30].

As an effective dehalogenation agent, nano-zero-valent iron has attracted global attention and is widely used in the treatment of pollutants such as halogenated alkanes, halogenated aromatics, and PCBs (polychlorinated biphenyls) [31,32]. Studies have shown that nano-zero-valent iron reacts with halogenated

hydrocarbons under anaerobic conditions, has strong reducing properties, and can convert some halogenated hydrocarbons into non-toxic substances [33].

Not only that, Nanoscale zero-valent iron is also used to treat p-NCB (p-Chloronitrobenzene) in water. Under certain dosage and initial pH conditions, it can efficiently degrade p-Chloronitrobenzene [34]. At the same time, nano-zero-valent iron can quickly and effectively convert vinyl chloride pollutants into non-toxic ethane and ethylene, and no chlorine-containing intermediate products are produced during the reaction [35].

Nano-zero-valent iron has garnered a lot of attention and is frequently utilized in real-world applications because it has demonstrated significant potential as an efficient pollution treatment technology for the elimination of both organic and inorganic halides [37,38].

4. COMMON MODIFICATION METHODS OF nZVI

Nanoscale zero-valent iron (nZVI) is effective for water pollutant removal but agglomeration limits its efficiency. Modifying nZVI is a possible solution, but current evaluation methods under ideal conditions may not be practical. Economic benefits must be considered due to the influence of material amount on pollutant removal cost [39,40].

Liu et al. [41] introduced the concept of 'electron efficiency,' which assesses the economic advantages of modified nZVI by comparing the electrons consumed during a specific time frame in the reduction process to the electrons supplied by nZVI. This approach aims to optimize costs and maximize electron utilization. However, it is important to note that while electron efficiency offers economic insights, it may not provide an accurate representation of the rate at which pollutants are removed [42].

For the evaluation of nZVI modification, Zhou et al [43]. reviewed the ways to improve the electron selectivity of nZVI and demonstrated the importance of the evaluation of this economic benefit. However, more economical and rapid evaluation methods are still needed. In many studies of ZVI nanoparticles, the methods for evaluating modified materials mainly focus on the exploration of reactivity, stability or toxicity under different

physicochemical conditions [44]. However, this disjointed approach to research may lead to disagreements in the evaluation of modified materials [45]. Therefore, the new evaluation method should evaluate the modified nano-zero-valent iron in many aspects (reactivity, stability, mobility, toxicity) and multi-factors to better meet the needs of practical applications [46].

4.1. Load modification

Loading modification is a technique for consistently and evenly dispersing nanoscale zero-valent iron (nZVI) over the surface of other materials, with the aim of preventing nZVI agglomeration and boosting the contact area to encourage the degradation of contaminants. Clay and high surface area carbon materials, which have strong adsorption capabilities and stability, are often utilized loading materials. One key strategy for creating multifunctional nZVI materials is load modification [47].

4.2. Bimetal modification

In order to increase reactivity, particularly for contaminants that need to be dehydrogenated, bimetallic modification involves combining micro zero-valent iron with another metal. Metals including palladium, platinum, nickel, copper, and silver are frequently utilized. Despite being the most effective catalyst, palladium is constrained by its greater price. A less expensive and less harmful option is copper. Even though the bimetal modification can increase the reaction's efficiency, it's important to consider any potential environmental issues that the second metal may bring about. To improve stability and application effects, it may be possible to combine multifunctional nano-zero-valent iron materials with other ways of modification [48].

4.3. Vulcanization modification

By creating a sulfide shell on the surface of nano-zero-valent iron, the modification process known as sulfurized nano-zero-valent iron (S-nZVI) increases the material's specific surface area and reducing power. The use of S-nZVI as an electron transfer medium to effectively transport electrons to target pollutants has the potential to play a part in pollutant remediation [49].

While being salt-tolerant, it has good performance in the removal of heavy metals and organic contaminants. S-nZVI may be made using a one-step approach or a two-step method, with the one-step method having a greater sulfur content and selectivity. Additionally, the bioprecipitation approach for producing S-nZVI eliminates the need of hazardous chemical sulfur reagents. The structure and homogeneity of the iron sulfide determine how long S-nZVI will last, and its outer shell can shield the core from anoxic corrosion and convert heavy metal ions to sulfide throughout the process. This modification technique has drawn a lot of interest in nZVI research and has demonstrated potential for application [50].

4.4. Surface modification

Nanoscale zero-valent iron (nZVI) can be dispersed in water by altering its surface through surface modification with coating molecules. The coating reduces inter-nanoparticle contact force and improves stability through steric hindrance. The surfactant concentration plays a significant role in this process, affecting the liquid's characteristics and surface tension [51,52].

Surface modification alters the charge on nZVI, reducing electrostatic attraction and aggregation. It also increases available surface sites for pollutant concentration reduction. However, surface alteration may limit diffusion channels, hinder electron transfer to pollutants, scavenge active radicals, and prevent dispersion of contaminants [53].

Despite the potential benefits of surface modification, it's essential to carefully consider influencing factors and drawbacks in real applications. Interaction with other substances, such as humic acid, can lead to aggregation and sedimentation of nZVI [54].

5. CONCLUSIONS AND PROSPECTS

Nano-zero-valent iron (nZVI) is a promising technology for remediating pollutants like heavy metals, halogenated compounds, and nitrates in wastewater. However, challenges such as easy aggregation and oxidation need to be addressed. To enhance its efficacy, researchers are modifying nZVI properties to improve performance, reduce costs, and extend its service life.

Though studies have revealed insights into how nZVI and its variants remove pollutants, uncertainties remain due to diverse pollutant structures. Further research is essential to fully understand the process, enabling effective nZVI application in engineering scenarios. The main challenge is applying mature revision techniques to nZVI particles prepared through artificial physical methods, enhancing engineering operations and revolutionizing water pollution mitigation.

In conclusion, overcoming aggregation and oxidation challenges and adopting advanced revision methods will accelerate nZVI's real-world applications. Continued research is crucial to comprehensively explore nZVI's potential, enabling more efficient and environmentally friendly wastewater treatment approaches and contributing to a cleaner and healthier environment.

5 REFERENCES

- [1] Gigault, J., El Hadri, H., Nguyen, B., Grassl, B., Rowenczyk, L., Tufenkji, N., ... & Wiesner, M. (2021). Nanoplastics are neither microplastics nor engineered nanoparticles. *Nature nanotechnology*, 16(5), 501-507.
- [2] Bandi, S. P., Kumbhar, Y. S., & Venuganti, V. V. K. (2020). Effect of particle size and surface charge of nanoparticles in penetration through intestinal mucus barrier. *Journal of Nanoparticle Research*, 22, 1-11.
- [3] Yu, G., Cheng, Y., & Duan, Z. (2022). Research progress of polymers/inorganic nanocomposite electrical insulating materials. *Molecules*, 27(22), 7867.
- [4] Koksharov, Y. A. (2009). Magnetism of nanoparticles: effects of size, shape, and interactions. *Magnetic nanoparticles*, 197-254.
- [5] Lee, GLAVEE G N, KLABUNDE K J, SORENSEN C M, et al. Chemistry of borohydride reduction of iron (II) and iron (III) ions in aqueous and non-aqueous media: Formation of nanoscale Fe, FeB, and Fe₂B powders[J]. *Inorganic Chemistry*, 1995, 34 (1): 28-35.
- [6] ZHANG Y L, SU Y M, ZHOU X F, et al. A new insight on the core-shell structure of zerovalent iron nanoparticles and its application for Pb (II) sequestration[J]. *Journal of Hazardous Materials*, 2013, 263: 685-693.
- [7] Wang, T., Sun, Y., Bai, L., Han, C., & Sun, X. (2023). Ultrafast removal of Cr (VI) by chitosan coated biochar-supported nano zero-valent iron aerogel from aqueous solution: Application performance and reaction mechanism. *Separation and Purification Technology*, 306, 122631.
- [8] Wang, T., Sun, Y., Bai, L., Han, C., & Sun, X. (2023). Ultrafast removal of Cr (VI) by chitosan coated biochar-supported nano zero-valent iron aerogel from aqueous solution: Application performance and reaction mechanism. *Separation and Purification Technology*, 306, 122631.
- [9] Chen X, Yao X, Yu C, et al. Hydrodechlorination of polychlorinated biphenyls in contaminated soil from an e-waste recycling area, using nanoscale zerovalent iron and Pd/Fe bimetallic nanoparticles [J]. *Environmental Science and Pollution Research*, 2014,21(7):5201- 5210.
- [10] Jamei M R, Khosravi M R, Anvaripour B. A novel ultrasound assisted method in synthesis of nzvi particles [J]. *Ultrasonics Sonochemistry*, 2014,21(1):226-233.
- [11] Ribas D, Pešková K, Jubany I, et al. High reactive nano zero-valent iron produced via wet milling through abrasion by alumina [J]. *Chemical Engineering Journal*, 2019,366:235-245.
- [12] Liang Z, Yan Q, Chen D. Degradation of p-nitrophenol by nanoscale zero-valent iron produced by Microwave-Assisted Ball Milling [J]. *Journal of Environmental Engineering*, 2018,144(3):04018003.
- [13] Chen S, Hsu H, Li C. A new method to produce nanoscale iron for nitrate removal [J]. *Journal of Nanoparticle Research*, 2004,6(6):639-647.
- [14] Fazlzadeh M, Rahmani K, Zarei A, et al. A novel green synthesis of zero valent iron nanoparticles (NZVI) using three plant extracts and their efficient application for removal of Cr(VI) from aqueous solutions [J]. *Advanced Powder Technology*, 2017,28(1):122-130.
- [15] Dumitrache F, Morjan I, Alexandrescu R, et al. Nearly monodispersed carbon coated iron nanoparticles for the catalytic growth of nanotubes/nanofibres [J]. *Diamond and Related Materials*, 2004,13(2): 362-370.
- [16] O'Carroll, D., Sleep, B., Krol, M., Boparai, H., & Kocur, C. (2013). Nanoscale zero valent iron and bimetallic particles for contaminated site remediation. *Advances in Water Resources*, 51, 104-122.
- [17] Zhang, S. H., Wu, M. F., Tang, T. T., Xing, Q. J., Peng, C. Q., Li, F., ... & Luo, J. M. (2018). Mechanism investigation of anoxic Cr (VI) removal by nano zero-valent iron based on XPS analysis in time scale. *Chemical Engineering Journal*, 335, 945-953.
- [18] Pilaquinga, F., Morey, J., Vivas-Rodríguez, M., Yáñez-Jácome, G., Fernández, L., & de las Nieves Piña, M. (2021). Colorimetric Detection and Adsorption of Mercury Using Silver Nanoparticles: A Bibliographic and Patent Review. *Nanoscience & Nanotechnology-Asia*, 11(5), 4-23.
- [19] Laucht, S. L. (2011). Trace element removal techniques with iron oxyhydroxides and the adsorption/co-precipitation removal mechanism (Doctoral dissertation, Ph. D. thesis (p 301). Australia: University of Newcastle).
- [20] Singh, R., Chakma, S., & Birke, V. (2023). Performance of field-scale permeable reactive barriers: An overview on potentials and possible

- implications for in-situ groundwater remediation applications. *Science of The Total Environment*, 858, 158838.
- [21] Ainiwaer, M., Zhang, T., Zhang, N., Yin, X., Su, S., Wang, Y., ... & Zeng, X. (2022). Synergistic removal of As (III) and Cd (II) by sepiolite-modified nanoscale zero-valent iron and a related mechanistic study. *Journal of Environmental Management*, 319, 115658.
- [22] Tang, C., Huang, Y., Zhang, Z., Chen, J., Zeng, H., & Huang, Y. H. (2016). Rapid removal of selenate in a zero-valent iron/Fe₃O₄/Fe²⁺ synergetic system. *Applied Catalysis B: Environmental*, 184, 320-327.
- [23] Tarekegn, M. M., Hiruy, A. M., & Dekebo, A. H. (2021). Nano zero valent iron (nZVI) particles for the removal of heavy metals (Cd²⁺, Cu²⁺ and Pb²⁺) from aqueous solutions. *RSC advances*, 11(30), 18539-18551.
- [24] Shi, Y., Feng, D., Ahmad, S., Liu, L., & Tang, J. (2023). Recent advances in metal-organic frameworks-derived carbon-based materials in sulfate radical-based advanced oxidation processes for organic pollutant removal. *Chemical Engineering Journal*, 454, 140244.
- [25] Liang, Y., & Feng, H. (2019). Removal and recovery of nitrogen pollutants in bioelectrochemical system. *Bioelectrochemistry Stimulated Environmental Remediation: From Bioelectrorespiration to Bioelectrodegradation*, 157-203.
- [26] O'Carroll, D., Sleep, B., Krol, M., Boparai, H., & Kocur, C. (2013). Nanoscale zero valent iron and bimetallic particles for contaminated site remediation. *Advances in Water Resources*, 51, 104-122.
- [27] Guan, X., Sun, Y., Qin, H., Li, J., Lo, I. M., He, D., & Dong, H. (2015). The limitations of applying zero-valent iron technology in contaminants sequestration and the corresponding countermeasures: the development in zero-valent iron technology in the last two decades (1994–2014). *Water research*, 75, 224-248.
- [28] Eljamal, R., Eljamal, O., Khalil, A. M., Saha, B. B., & Matsunaga, N. (2018). Improvement of the chemical synthesis efficiency of nano-scale zero-valent iron particles. *Journal of environmental chemical engineering*, 6(4), 4727-4735.
- [29] Thornton, J. (2000). Beyond risk: an ecological paradigm to prevent global chemical pollution. *International journal of occupational and environmental health*, 6(4), 318-330.
- [30] Mukhopadhyay, A., Duttagupta, S., & Mukherjee, A. (2022). Emerging organic contaminants in global community drinking water sources and supply: A review of occurrence, processes and remediation. *Journal of Environmental Chemical Engineering*, 10(3), 107560.
- [31] Rashid, R., Shafiq, I., Akhter, P., Iqbal, M. J., & Hussain, M. (2021). A state-of-the-art review on wastewater treatment techniques: the effectiveness of adsorption method. *Environmental Science and Pollution Research*, 28, 9050-9066.
- [32] Fenyvesi, É., Gruiz, K., Morillo, E., & Villaverde, J. (2019). Traditional and innovative methods for physical and chemical remediation of soil contaminated with organic contaminants. *Engineering Tools for Environmental Risk Management*, 4, 285-362.
- [33] Li, Q., Chen, Z., Wang, H., Yang, H., Wen, T., Wang, S., ... & Wang, X. (2021). Removal of organic compounds by nanoscale zero-valent iron and its composites. *Science of the Total Environment*, 792, 148546.
- [34] Zhu, L., Gao, K., Jin, J., Lin, H., & Xu, X. (2014). Analysis of ZVI corrosion products and their functions in the combined ZVI and anaerobic sludge system. *Environmental Science and Pollution Research*, 21, 12747-12756.
- [35] Deng, J., Wu, F., Gao, S., Dionysiou, D. D., & Huang, L. Z. (2022). Self-activated Ni (OH)₂ cathode for complete electrochemical reduction of trichloroethylene to ethane in low-conductivity groundwater. *Applied Catalysis B: Environmental*, 309, 121258.
- [36] Taghizadeh, M., Kebria, D. Y., Darvishi, G., & Kootenaei, F. G. (2013). The use of nano zero valent iron in remediation of contaminated soil and groundwater. *International Journal of Scientific Research in Environmental Sciences*, 1(7), 152.
- [37] Zarei, A. R., & Ghavi, A. (2016). A New Approach for the Removal of Chlorate Impurity from Military Grade Ammonium Perchlorate Using Stabilized Zero-Valent Iron Nanoparticles. *International Journal of Energetic Materials and Chemical Propulsion*, 15(3).
- [38] Mukherjee, R., Kumar, R., Sinha, A., Lama, Y., & Saha, A. K. (2016). A review on synthesis, characterization, and applications of nano zero valent iron (nZVI) for environmental remediation. *Critical reviews in environmental science and technology*, 46(5), 443-466.
- [39] Ye, H., Zhao, B., Zhou, Y., Du, J., & Huang, M. (2021). Recent advances in adsorbents for the removal of phthalate esters from water: Material, modification, and application. *Chemical Engineering Journal*, 409, 128127.
- [40] Ahmad, S., Liu, X., Tang, J., & Zhang, S. (2022). Biochar-supported nanosized zero-valent iron (nZVI/BC) composites for removal of nitro and chlorinated contaminants. *Chemical Engineering Journal*, 431, 133187.
- [41] Liu H B, Chen T H, Chang D Y, et al. Nitrate reduction over nanoscale zero-valent iron prepared by hydrogen reduction of goethite [J]. *Materials Chemistry and Physics*, 2012, 133(1):205-211.
- [42] Mirzaei, A., Chen, Z., Haghghat, F., & Yerushalmi, L. (2017). Removal of pharmaceuticals from water by homo/heterogenous Fenton-type processes—a review. *Chemosphere*, 174, 665-688.
- [43] Zhou L, Li Z, Yi Y, et al. Increasing

- the electron selectivity of nanoscale zero-valent iron in environmental remediation: A review [J]. *Journal of hazardous materials*, 2022,421:126709.
- [44] Pandey, K., Sharma, S., & Saha, S. (2022). Advances in design and synthesis of stabilized zero-valent iron nanoparticles for groundwater remediation. *Journal of Environmental Chemical Engineering*, 10(3), 107993.
- [45] LS Silva, L., A. Caldara, J., Maria Rocco, A., P. Borges, C., & V. Fonseca, F. (2019). Evaluation of nano zero-valent iron (nZVI) activity in solution and immobilized in hydrophilic PVDF membrane for drimaren Red X-6BN and bisphenol-a removal in water. *Processes*, 7(12), 904.
- [46] Ken, D. S., & Sinha, A. (2020). Recent developments in surface modification of nano zero-valent iron (nZVI): Remediation, toxicity and environmental impacts. *Environmental Nanotechnology, Monitoring & Management*, 14, 100344.
- [47] Han, X., Zhang, H., Zhang, C., Zhao, Y., Zhang, N., & Liang, J. (2021). Preparation of sepiolite nanofibers supported zero valent iron composite material for catalytic removal of tetracycline in aqueous solution. *Frontiers in Chemistry*, 9, 736285.
- [48] Sharma, G., Kumar, A., Sharma, S., Naushad, M., Dwivedi, R. P., ALOthman, Z. A., & Mola, G. T. (2019). Novel development of nanoparticles to bimetallic nanoparticles and their composites: A review. *Journal of King Saud University-Science*, 31(2), 257-269.
- [49] Li, L., Jin, H., Luo, N., Niu, H., Cai, Y., Cao, D., & Zhang, S. (2023). Sulfurized nano zero-valent iron prepared via different methods: Effect of stability and types of surface corrosion products on removal of 2, 4, 6-trichlorophenol. *Ecotoxicology and Environmental Safety*, 256, 114864.
- [50] Garcia, A. N., Boparai, H. K., Chowdhury, A. I., de Boer, C. V., Kocur, C. M., Passeport, E., ... & O'Carroll, D. M. (2020). Sulfidated nano zerovalent iron (S-nZVI) for in situ treatment of chlorinated solvents: A field study. *Water Research*, 174, 115594.
- [51] Ken, D. S., & Sinha, A. (2020). Recent developments in surface modification of nano zero-valent iron (nZVI): Remediation, toxicity and environmental impacts. *Environmental Nanotechnology, Monitoring & Management*, 14, 100344.
- [52] Phenrat, T., Long, T. C., Lowry, G. V., & Veronesi, B. (2009). Partial oxidation ("aging") and surface modification decrease the toxicity of nanosized zerovalent iron. *Environmental science & technology*, 43(1), 195-200.
- [53] Yoon, H., Pangging, M., Jang, M. H., Hwang, Y. S., & Chang, Y. S. (2018). Impact of surface modification on the toxicity of zerovalent iron nanoparticles in aquatic and terrestrial organisms. *Ecotoxicology and Environmental Safety*, 163, 436-443.
- [54] Kaifas, D., Malleret, L., Kumar, N., Fétimi, W., Claeys-Bruno, M., Sergent, M., & Doumenq, P. (2014). Assessment of potential positive effects of nZVI surface modification and concentration levels on TCE dechlorination in the presence of competing strong oxidants, using an experimental design. *Science of the total Environment*, 481, 335-342.
- [55] Khaoula Bensaida, Ibrahim Maamoun, Ramadan Eljamal, Omar Falyouna, Yuji Sugihara, Osama Eljamal, New insight for electricity amplification in microbial fuel cells (MFCs) applying magnesium hydroxide coated iron nanoparticles, *Energy Conversion and Management*, 249, 2021, 114877
- [56] Osama Eljamal, Keiko Sasaki, Tsuyoshi Hirajima, Sorption kinetic of arsenate as water contaminant on zero valent iron, *Journal of Water Resource and Protection* 2013 (5), 563-567
- [57] Ibrahim Maamoun, Omar Falyouna, Ramadan Eljamal, Khaoula Bensaida, Kazuya Tanaka, Tiziana Tosco, Yuji Sugihara, Osama Eljamal, Multi-functional magnesium hydroxide coating for iron nanoparticles towards prolonged reactivity in Cr(VI) removal from aqueous solutions, *Journal of Environmental Chemical Engineering*, Volume 10, Issue 3, 2022, 107431
- [58] Eljamal, O., Jinno, K. & Hosokawa, T. Modeling of solute transport and biological sulfate reduction using low cost electron donor. *Environ Geol* 56, 1605–1613 (2009).
- [59] Ramadan Eljamal, Ibrahim Maamoun, Khaoula Bensaida, Gulsum Yilmaz, Yuij Sugihara, Osama Eljamal, A novel method to improve methane generation from waste sludge using iron nanoparticles coated with magnesium hydroxide, *Renewable and Sustainable Energy Reviews*, Volume 158, 2022, 112192
- [60] Omar Falyouna, Khaoula Bensaida, Ibrahim Maamoun, U.P.M. Ashik, Atsushi Tahara, Kazuya Tanaka, Noboru Aoyagi, Yuji Sugihara, Osama Eljamal, Synthesis of hybrid magnesium hydroxide/magnesium oxide nanorods [Mg(OH)₂/MgO] for prompt and efficient adsorption of ciprofloxacin from aqueous solutions, *Journal of Cleaner Production*, Volume 342, 2022, 130949
- [61] Omar Falyouna, Mohd Faizul Idham, Ibrahim Maamoun, Khaoula Bensaida, UPM Ashik, Yuji Sugihara, Osama Eljamal, Promotion of ciprofloxacin adsorption from contaminated solutions by oxalate modified nanoscale zerovalent iron particles, *Journal of Molecular Liquids*, Volume 359, 2022, 119323
- [62] Ibrahim Maamoun, Khaoula Bensaida, Ramadan Eljamal, Omar Falyouna, Kazuya Tanaka, Tiziana Tosco, Yuji Sugihara, Osama Eljamal, Rapid and efficient chromium (VI) removal from aqueous solutions using nickel hydroxide nanoplates (nNiHs), *Journal of Molecular Liquids*, Volume 358, 2022, 119216
- [63] Osama Eljamal, Ibrahim Maamoun, Sami Alkhudhayri, Ramadan Eljamal, Omar Falyouna,

- Kazuya Tanaka, Naofumi Kozai, Yuji Sugihara, Insights into boron removal from water using Mg-Al-LDH: Reaction parameters optimization & 3D-RSM modeling, *Journal of Water Process Engineering*, Volume 46, 2022, 102608
- [64] Eljamal, O., Jinno, K. & Hosokawa, T. Modeling of Solute Transport with Bioremediation Processes using Sawdust as a Matrix. *Water Air Soil Pollut* 195, 115–127 (2008).
- [65] Osama Eljamal, Junya Okawauchi, Kazuaki Hiramatsu, Removal of phosphorus from water using marble dust as sorbent material, *Journal of Environmental Protection* 2012
- [66] Eljamal, O., Sasaki, K., Tsuruyama, S. et al. Kinetic Model of Arsenic Sorption onto Zero-Valent Iron (ZVI). *Water Qual Expo Health* 2, 125–132 (2011).
- [67] Eljamal, O., Okawauchi, J., Hiramatsu, K. et al. Phosphorus sorption from aqueous solution using natural materials. *Environ Earth Sci* 68, 859–863 (2013).
- [68] Ibrahim Maamoun, Omar Falyouna, Ramadan Eljamal, Mohd Faizul Idham, Kazuya Tanaka, Osama Eljamal, Bench-scale injection of magnesium hydroxide encapsulated iron nanoparticles ($n\text{Fe}0@\text{Mg}(\text{OH})_2$) into porous media for Cr(VI) removal from groundwater, *Chemical Engineering Journal*, Volume 451, Part 3, 2023, 138718
- [69] Ibrahim Maamoun, Ramadan Eljamal, Osama Eljamal, Statistical optimization of nZVI chemical synthesis approach towards P and NO_3^- removal from aqueous solutions: Cost-effectiveness & parametric effects, *Chemosphere*, Volume 312, Part 1, 2023, 137176
- [70] Mohd Faizul Idham, Omar Falyouna, Ramadan Eljamal, Ibrahim Maamoun, Osama Eljamal, Chloramphenicol removal from water by various precursors to enhance graphene oxide–iron nanocomposites, *Journal of Water Process Engineering*, Volume 50, 2022, 103289
- [71] Ibrahim Maamoun, Mostafa A. Rushdi, Omar Falyouna, Ramadan Eljamal, Osama Eljamal, Insights into machine-learning modeling for Cr(VI) removal from contaminated water using nano-nickel hydroxide, *Separation and Purification Technology*, Volume 308, 2023, 122863.